

STANDARDS AUSTRALIA

---

RECONFIRMATION

OF

AS 2001.4.22—1991

Methods of test for textiles

**Method 4.22: Colourfastness tests—Determination of colour change due to flat abrasion (frosting) of textile fabrics (screen wire method)**

---

RECONFIRMATION NOTICE

Technical Committee TX-020 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 6 July 2016.

The following are represented on Technical Committee TX-020:

Ag Research  
Australian Wool Processors Council  
AWTA Textile Testing  
Council of Textile and Fashion Industries of Australia  
Drycleaning Institute of Australia  
National Association of Testing Authorities Australia  
RMIT University  
The Textile Institute

NOTES

Currently in preview, click buy full vers.

## Australian Standard®

---

**Methods of test for textiles****Method 4.22: Colourfastness tests—  
Determination of colour change due to  
flat abrasion (frosting) of textile fabrics  
(screen wire method)**

---

## PREFACE

This Standard was prepared by the Standards Australia Committee on Testing of Textiles.

In the preparation of this Standard, cognizance was taken of the following method:

AATCC Test method 119—1984, *Colour change due to flat abrasion (frosting): screen wire method.*

The method is based upon the development described by N. B. Gobeil and P. L. Alessandro, *A proposed method to evaluate frosting potential caused by abrasive wear*, American Dyestuff Reporter Vol. 54, No 24, Page 42-49, November 22, 1965.

## FOREWORD

This test method is intended for evaluating the resistance of coloured fabrics to change in shade caused by flat abrasion. It can be used for most coloured fabrics, but is especially sensitive to the colour change of durable press cross-dyed blend fabrics, in which one fibre is abraded at a faster rate than another.

The test produces, in an accelerated manner, a localized colour change similar to that produced on some garments over relatively short periods of actual wear, where the garment is exposed to relatively mild abrasive action.

## METHOD

**1 SCOPE** This Standard sets out a method for the determination of the change in colour of textile fabrics due to flat abrasion (frosting). The method is applicable to woven and knitted textile fabrics. It is not applicable to floor coverings.

**2 REFERENCED DOCUMENTS** The following documents are referred to in this Standard:

AS	
1199	Sampling procedures and tables for inspection by attributes
2001	Methods of test for textiles
2001.1	Method 1: Conditioning procedures
2001.4.1	Method 4.1: Colourfastness tests—Definitions and general requirements

**3 PRINCIPLE** A specimen is mounted on a foam rubber cushion and rubbed multidirectionally against a wire screen mounted on a weighted head. The change in colour of the test specimen is then assessed using the Grey Scale.