

AS 2131—1987

Australian Standard[®]

**ADHESIVES—
FOR BONDING DECORATIVE
THERMOSET LAMINATES
(CONTACT ADHESIVES)**

This Australian Standard was prepared by Committee CH/17, Adhesives. It was approved on behalf of the Council of the Standards Association of Australia on 10 July 1987 and published on 1 September 1987.

The following interests are represented on Committee CH/17:

Adhesives & Sealants Manufacturers Association of Australia
Australian Chemical Industry Council
Australian Council of Furniture Manufacturers
Australian Institute of Packaging
Confederation of Australian Industry
CSIRO, Division of Building Research
Department of Defence
Footwear Manufacturers Association of Australia
Plywood Association of Australia Ltd
Printing and Allied Trades Employers Federation of Australia
Railways of Australia Committee
Society of Automotive Engineers - Australasia
Telecom Australia

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

Australian Standard[®]

**ADHESIVES — FOR BONDING
DECORATIVE THERMOSET
LAMINATES CONTACT
ADHESIVES**

First published	1978
Second edition	1987

PREFACE

This Standard was prepared by the Association's Committee on Adhesives under the direction of the Chemical Standards Board.

It is a revision of the 1978 edition and differs from it in that the method for determining bond strength in shear has been altered and a method for determining the optimum open assembly time has been included. Modifications to the doctor blade (Figure A1) have been made to improve vertical stability, facilitate gap-setting and reduce blade drag on adhesive film.

Although the Standard is applicable primarily to adhesives for decorative laminates, the adhesives will also contact-bond a wide variety of other surfaces.

CONTENTS

	Page
1 SCOPE	3
2 REFERENCED DOCUMENTS	3
3 DEFINITIONS	3
4 PRODUCT INFORMATION	3
5 SAMPLING	3
6 TEST CONDITIONS	3
7 TEST REQUIREMENTS	3
8 LABELLING AND PACKAGING	3
 APPENDICES	
A METHOD FOR DETERMINING BOND STRENGTH IN PEEL	5
B METHOD FOR DETERMINING BOND STRENGTH IN SHEAR	10
C METHOD FOR DETERMINING THE EFFECT OF ELEVATED TEMPERATURE IN SHEAR (HEAT RESISTANCE)	12
D METHOD FOR DETERMINING CLEAVAGE RESISTANCE AT ELEVATED TEMPERATURE	14
E METHOD FOR DETERMINING OPTIMUM OPEN ASSEMBLY TIME	16

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

ADHESIVES — FOR BONDING DECORATIVE THERMOSET LAMINATES
(CONTACT ADHESIVES)

1 SCOPE. This Standard applies to sprayable adhesives and brushable adhesives (including those for application by scraper) intended for the bonding, on the contact bond principle, of decorative thermoset laminated sheets to materials such as timber, metal, and particleboards.

2 REFERENCED DOCUMENTS. The following Standards are referred to in this Standard:

- AS 1309 Glossary of Terms Used in the Adhesive Industry.
- AS 1321 Methods for the Sampling and Testing of Adhesives.
Part 1 — Sampling.
Part 9 — Brookfield Viscosity of Liquid Adhesives.
Part 10— Non-volatile Matter (Solids Content).
- AS 1820 Loomstate Cotton Duck.
- AS 1863 Coated Abrasives (Technical Products).
- AS 2193 Methods for Calibration and Grading of Force-Measuring Systems of Testing Machines.
- AS 2272 Marine Plywood.
- AS K130 Decorative Thermosetting Laminated Sheet.

3 DEFINITIONS. For the purposes of this Standard the definition below applies.

Decorative thermoset laminated sheet — a laminated plastics sheet consisting essentially of layers of fibrous sheet material such as paper, impregnated with a thermosetting condensation resin, and consolidated under heat and pressure. The top layer, or layers of the sheet have a decorative colour or printed design.

Other definitions shall be in accordance with AS 1309.

4 PRODUCT INFORMATION. The supplier shall supply all necessary information on bonding procedures such as mixing, spreading, pot life, open and closed assembly times, as well as on shelf life and on non-volatile matter, and cleaning instructions and any material safety data.

The information may be on the pack, or supplied separately for industrial applications. Instructions for use, including cleaning up, shall be included with or printed on each retail pack.

5 SAMPLING. The adhesive sample for testing shall be selected in accordance with AS 1321, Part 1.

6 TEST CONDITIONS. Unless otherwise specified, all mixing and testing of the adhesive shall be carried out at a temperature of $23 \pm 2^\circ\text{C}$ and a relative humidity of 50 ± 5 percent. The adhesive shall be mixed and used exactly as prescribed by the supplier.

7 TEST REQUIREMENTS.

7.1 Viscosity. When tested by the method described in AS 1321, Part 9, sprayable grades of contact adhesive shall have a maximum Brookfield RV viscosity of 0.5 Pa.s and brushable grades (including those for application by scraper) shall have a minimum Brookfield RV viscosity not less than 0.5 Pa.s, using spindle rotation speed of 10 revolutions per min and spindle numbers 1 or 2 in both cases.

NOTES:

- Other viscosities are subject to agreement between the purchaser and the supplier.
- Viscosity may be expressed in the Brookfield DV equivalent.

7.2 Bond strength in peel. When tested in accordance with Appendix A, the mean 180 degree peel strength shall be not less than 35 N per 25 mm bonded width.

7.3 Bond strength in shear. When tested in accordance with Appendix B, the mean bond strength in tensile shear shall be not less than 700 kPa.

7.4 Effect of elevated temperature in shear (heat resistance). When tested in accordance with Appendix C, the mean temperature at which failure occurs shall be not less than 150°C .

7.5 Cleavage resistance at elevated temperature. When tested in accordance with Appendix D, the mean cleavage resistance time at 60°C shall be not less than 5 min.

7.6 Optimum open assembly time. When tested in accordance with Appendix E, the optimum open assembly time of the adhesive shall be within 10 percent of that stated by the supplier.

7.7 Accelerated ageing test. When tested in accordance with Appendix B, after the test assembly has been aged at $70 \pm 1^\circ\text{C}$ for 7 days, the mean bond strength in shear shall be not less than 700 kPa. The ageing shall be carried out after the test assembly has been prepared as described in Paragraph B5 of Appendix B.

7.8 Stability. When stored in the original unopened containers the adhesive shall comply with the requirements of Clauses 7.1 to 7.7 for at least 12 months from the date of purchase under the storage conditions recommended by the supplier. In the absence of any such recommendation, the storage temperature shall be between 5°C and 27°C .

8 LABELLING AND PACKAGING.

8.1 Labelling. Each container shall be labelled in accordance with the relevant statutory regulations.