

Australian Standard[®]

Cutback bitumen

This Australian Standard was prepared by Committee CH/25, Bitumen and Related Products (for Roadmaking). It was approved on behalf of the Council of Standards Australia on 14 March 1997 and published on 5 June 1997.

The following interests are represented on Committee CH/25:

ARRB Transport Research
Australian Asphalt Pavement Association
Australian Chamber of Commerce and Industry
Australian Institute of Petroleum
AUSTROADS
Bureau of Steel Manufacturers of Australia
New Zealand Bitumen Contractors Association
The Works Consultancy Services, New Zealand

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 95361.

AS 2157—1997

Australian Standard[®]

Cutback bitumen

Originated as AS A131—1966.
Previous edition as AS 2157—1980.
Third edition 1997.

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7337 1130 8

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee CH/25, Bitumen and Related Products (for Roadmaking), to supersede AS 2157—1980. This Standard is the result of a consensus among Australian and New Zealand representatives on the Joint Committee that it be produced as an Australian Standard.

This Standard is one of a series relating to material for roadmaking purposes, and its objective is to provide manufacturers and suppliers with requirements for medium-curing cutback bitumen for roadmaking purposes. Other Standards in the series are as follows:

AS

1160 Bitumen emulsions for construction and maintenance of pavements

1507 Road tars for pavements

2008 Residual bitumen for pavements

2150 Hot mix asphalt

The terms 'normative' and 'informative' have been used in this Standard to define the application of the appendix to which they apply. A 'normative' appendix is an integral part of a Standard, whereas an 'informative' appendix is only for information and guidance.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
1 SCOPE	4
2 REFERENCED DOCUMENTS	4
3 DEFINITION	4
4 CLASSIFICATION AND GRADING	4
5 PROPERTIES	5
6 SAMPLING	5
7 MARKING OF CONTAINERS	5
 APPENDICES	
A PURCHASING GUIDELINES	7
B SAMPLING	9

STANDARDS AUSTRALIA

Australian Standard
Cutback bitumen

1 SCOPE This Standard specifies requirements for medium-curing cutback bitumen for roadmaking purposes.

NOTE: Purchasing guidelines are set out in Appendix A.

2 REFERENCED DOCUMENTS The following documents are referred to in this Standard:

AS

2008	Residual bitumen for pavements
2341	Methods of testing bitumen and related roadmaking products
2341.2	Determination of dynamic (coefficient of shear) viscosity by flow through a capillary tube
2341.4	Determination of dynamic viscosity by rotational viscometer
2341.5	Determination of apparent viscosity by 'Shell' sliding plate micro-viscometer
2341.6	Determination of density using a hydrometer
2341.7	Determination of density using a density bottle
2341.15	Distillation of cutback bitumen
2341.16	Determination of flashpoint of cutback bitumen
3568	Oils for reducing the viscosity of residual bitumen for pavements

3 DEFINITION For the purpose of this Standard, the definition below applies.

3.1 Cutback bitumen—a product made from residual bitumen complying with AS 2008 by the addition of cutter oil complying with AS 3568 for the temporary reduction of viscosity.

4 CLASSIFICATION AND GRADING Cutback bitumen shall be classified and graded according to its dynamic viscosity at 60°C (see Table 1). The grade shall be designated and classified as follows:

Grade designation	Classification
AMC00 AMC0 AMC1	Priming classes
AMC2 AMC3 AMC4	Primer-sealing and premix classes
AMC5 AMC6 AMC7	Sealing classes