

Australian Standard

---

**MICROGRAPHIC  
ASSESSMENT OF THE  
NON-METALLIC INCLUSION  
CONTENT IN WROUGHT STEEL**

---

The following scientific, industrial and governmental organizations and departments were officially represented on the committee entrusted with the preparation of this standard:

Bureau of Steel Manufacturers of Australia  
Commonwealth Aircraft Corporation  
Confederation of Australian Industry  
Department of Defence  
Federated Chamber of Automotive Industries  
Institute of Steel Service Centres of Australia  
Metal Trades Industry Association of Australia  
Railways of Australia Committee  
Society of Automotive Engineers— Australia  
Telecom Australia  
University of New South Wales (School of Metallurgy)

---

This standard, prepared by Committee MT/18, Metallurgy, was approved by the Metals Standards Board on behalf of the Council of the Standards Association of Australia on 31 May 1978, and was published on 1 November 1978.

---

**Review of Australian Standards.** To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

---

*This standard was issued in draft form for public review as DR 76060.*

Australian Standard

---

**METHOD FOR THE  
MICROGRAPHIC  
ASSESSMENT OF THE  
NON-METALLIC INCLUSION  
CONTENT IN WROUGHT STEEL**

---

|                                |
|--------------------------------|
| First published . . . . . 1978 |
|--------------------------------|

PUBLISHED BY STANDARDS AUSTRALIA  
(STANDARDS ASSOCIATION OF AUSTRALIA)  
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 1526 0

## PREFACE

This standard was prepared by the Association's Committee on Metallography to provide a method for the micrographic assessment of the non-metallic inclusion in wrought steel products by comparison with standard diagrams.

The method specified is in general agreement with ISO 4976\*, but deviates in regard to sampling and the rating number system. The committee considered the practicability of including the standard sectioning of bars during the sampling process as given in ISO 4967, but decided against its inclusion, since it was considered impractical because of variations in the cross-sectional microstructure of wrought steel. In regard to the rating number system, classification '0' has been introduced to cover fields of observation where no inclusions of a particular class are observed and classification '6' to cover inclusions greater than 5. In addition, the requirement for examination of each polished test piece has been reduced from 100 fields to 30 fields in order to reduce the time involved in performing a test.

Attention is drawn to Appendix B, Jernkontoret and ASTM Standard Diagrams, and it is emphasized that there is no direct comparison between Plate 1 (Jernkontoret) and Plate 2 (ASTM).

\* ISO 4967 Steel—Determination of Content of Non-metallic Inclusions—Micrographic Method using Standard Diagrams.

## CONTENTS

|  | <i>Page</i> |
|--|-------------|
| FOREWORD .....                                     | 3           |
| METHOD   |             |
| 1 Scope .....                                      | 3           |
| 2 Definition .....                                 | 3           |
| 3 Principle .....                                  | 3           |
| 4 Preparation of Test Pieces .....                 | 3           |
| 5 Procedure .....                                  | 3           |
| 6 Assessment and Expression of Results .....       | 4           |
| 7 Test Report .....                                | 4           |
| APPENDICES   |             |
| A Supplementary Information .....                  | 5           |
| B Jernkontoret and ASTM Standard Diagrams .....    | 6           |
| C Example of Assessment of a Field .....           | 22          |
| D Calculation of Average Field Rating Number ..... | 24          |

## © Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

## STANDARDS ASSOCIATION OF AUSTRALIA

## Australian Standard

## METHOD FOR THE MICROGRAPHIC ASSESSMENT OF THE NON-METALLIC INCLUSION CONTENT IN WROUGHT STEEL

## FOREWORD

The method of comparison of micrographic images with standard diagrams may result in significantly different inclusion content being reported from operator to operator. Results obtained by the method outlined in this standard should therefore only be considered as semi-quantitative. It should be noted that the results obtained are not directly related

to those obtained by quantitative methods such as chemical analysis which is often used for oxygen and sulphur contents to give a measure of the oxide and/or sulphur content present.

Other methods available which give quantitative results include manual point or line counting, and automatic scanning methods.

## METHOD

**1 SCOPE.** This standard describes a method for the micrographic assessment of the non-metallic inclusion content in wrought steel products by comparison with standard diagrams.

## NOTES:

1. This standard does not set limits for the inclusion content of steels. These limits are normally specified in the product specification or determined by agreement.
2. Supplementary information necessary to complete the method is set out in Appendix A.

**2 DEFINITION.** For the purpose of this standard the following definition applies:

*Non-metallic inclusion* — non-metallic compounds and mixtures in steel resulting from the entrapment of deoxidation products or exogenous materials, such as refractories and hot topping compounds, or from the precipitation of sulphides prior to, or during, solidification.

NOTE: Inclusion type, shape, size and distribution will vary greatly depending on the grade of steel, method of deoxidation, size and shape of the ingot, amount of reduction received, and the position in the ingot from which the sample is taken.

**3 PRINCIPLE.** Inclusions in longitudinal sections in rolled or forged steels are assessed by comparison with magnified images of polished test pieces with standard diagrams which form the Jernkontoret chart (or JK chart).

These diagrams correspond to fields of view of 0.8 mm taken from a longitudinal section and observed at a magnification of 100 ×. According to the shape and distribution of the inclusions, the standard diagrams are divided into four main groups, bearing references A, B, C and D. The method of designation is based on the morphology of the inclusion and not on the constitution of the inclusion as follows:

|                   |                     |
|-------------------|---------------------|
| Group A . . . . . | sulphide type       |
| Group B . . . . . | alumina type        |
| Group C . . . . . | silicate type       |
| Group D . . . . . | globular oxide type |

NOTE: Each main group on the JK chart consists of two sub-groups, each made up of five diagrams representing increasing contents of inclusions. These divisions into sub-groups are merely intended to give examples of different thicknesses of non-metallic particles.

The diagrams on the JK chart are given in Appendix B. Plate I is taken from the Jernkontoret method and Plate II from AS 151M.

Results from the use of Plate I should not be compared directly with those obtained from Plate II. These diagrams are numbered 1 to 5 in Plate I and 0.5 to 2.5 in Plate II, the numbers increasing with the surface area of inclusions, e.g. diagram A2 indicates the shape of the inclusions observed under the microscope in accordance with Group A and that their distribution and quantity is in accordance with number 2.

**4 PREPARATION OF TEST PIECES.** To enable inclusions to be observed in the longitudinal direction of working, wrought steel products are to be sectioned in such a manner that the surface of test pieces examined shall be at right angles to the worked face and parallel to the direction of greatest elongation.

During the preparation of a test piece every care shall be taken to avoid the tearing out or deformation of inclusions, contamination of the polished surface, or rounding of the edges.

Unless otherwise specified, test pieces shall be selected from locations which are relevant to the application of the products and be of a size so as to permit a polished face having an area of not less than 200 mm<sup>2</sup>.

## NOTES:

1. For the assessment of a product which has received a large reduction during processing, e.g. strips, it may be necessary to take several test pieces from adjacent locations as a single test.
2. Where applicable, and by agreement, several ingots or several bars and billets from one heat may be examined to obtain an average field rating for that heat of steel.
3. When a rating is required to represent a large batch of steel from an ingot or a heat it is preferable to record a few fields on a large number of test pieces rather than a large number of fields on a few test pieces. In such cases, it is preferable to assess the 'worst field rating' (see Clause 6.1).

**5 PROCEDURE.** The entire polished surface shall be examined in the unetched condition using a magnification of 100 × and an actual field diameter of 0.8 mm. Any error in the magnification and in