

Australian Standard<sup>®</sup>

**Medicine measures**

**Part 1: Glass**



This Australian Standard® was prepared by Committee CH-001, Laboratory Glassware and Related Apparatus. It was approved on behalf of the Council of Standards Australia on 23 March 2009.

This Standard was published on 13 May 2009.

---

The following are represented on Committee CH-001:

- National Association of Testing Authorities Australia
  - National Measurement Institute
  - Pharmaceutical Society of Australia NSW Branch
  - Royal College of Pathologists of Australasia
  - Science Industry Australia
  - The Pharmacy Guild of Australia, NSW Branch
  - The Royal Australian Chemical Institute
  - The University of New South Wales
- 

This Standard was issued in draft form for comment as Draft S 6226.

Standards Australia wishes to acknowledge the participation of the expert individuals that contributed to the development of this Standard through their representation on the Committee and through the public comment period.

---

#### **Keeping Standards up-to-date**

Australian Standards® are living documents that reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued.

Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments that may have been published since the Standard was published.

Detailed information about Australian Standards, drafts, amendments and new projects can be found by visiting [www.standards.org.au](http://www.standards.org.au)

Standards Australia welcomes suggestions for improvements, and encourages readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.org.au](mailto:mail@standards.org.au), or write to Standards Australia, GPO Box 476, Sydney, NSW 2001.

---

Australian Standard<sup>®</sup>

**Medicine measures**

**Part 1: Glass**

Originally as part of AS 2224—1978.  
Previous edition AS 2224.1—1986.  
Second edition 2009.

**COPYRIGHT**

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia GPO Box 476, Sydney, NSW 2001, Australia

ISBN 0 7337 9142 5

## PREFACE

This Standard was prepared by the Standards Australia Committee CH-001, Laboratory Glassware and Related Apparatus, to supersede AS 2224.1—1986, *Medicine measures (including paediatric droppers)*, Part 1: *Glass—For general use*.

The objective of this Standard is to ensure that the requirements for two types of glass measure—one of tumbler form and one of conical form are achieved.

It is emphasized that the tests were devised on the basis of their relationship to practical usage. In real life situations (a) it is only the surface of the measure that comes into direct contact with its contents and (b) the contents are in contact with the measure for perhaps only a few minutes at a time or in extreme cases for up to 8 h or 12 h overnight in a hospital. An acceptable test needs to recognize such practical situations and indeed this was the philosophy of the drafting committee throughout the production of this Standard.

The term ‘normative’ has been used in this Standard to define the application of the appendix to which it applies. A ‘normative’ appendix is an integral part of a Standard.

## CONTENTS

	<i>Page</i>
1 SCOPE.....	4
2 REFERENCED DOCUMENTS .....	4
3 DEFINITIONS.....	4
4 MATERIAL .....	4
5 DESIGN AND DIMENSIONS .....	5
6 CONSTRUCTION.....	5
7 MARKINGS .....	6
8 PERFORMANCE REQUIREMENTS .....	6

## APPENDICES

A DETERMINATION OF RESISTANCE TO LEACHING.....	9
B CHECK OF ACCURACY OF CALIBRATION.....	11
C METHOD FOR ASSESSING RESISTANCE TO THERMAL SHOCK.....	12
D METHOD FOR ASSESSING PERMANENCE OF MARKINGS.....	13

## STANDARDS AUSTRALIA

**Australian Standard  
Medicine measures****Part 1: Glass****1 SCOPE**

This Standard specifies requirements for two types of glass medicine measure—one of tumbler form and one of conical form.

NOTE: Pediatric droppers are not manufactured from glass.

**2 REFERENCED DOCUMENTS**

The following documents are referred to in this Standard:

AS/NZS

2243 Safety in laboratories

2243.1 Part 1: Planning and operational aspects

2243.2 Part 2: Chemical aspects

**3 DEFINITIONS**

For the purpose of this Standard, the following definitions apply:

**3.1 Capacity at any graduation line**

The volume of distilled water at 20°C, expressed in millilitres, contained by the relevant measure at 20°C, when filled to the graduation line under test.

NOTE: The determination of the capacity of measures is described in Appendix B.

**3.2 Permanently marked**

Markings that endure for the life of the measure when it is used in measuring medicines as well as in associated cleaning processes.

NOTES:

- 1 Although markings defined here are intended to include both the glass-etched type and the pigmented type, the method of test set out in Appendix D is most unlikely to be meaningful in relation to the first type of marking as this would require dissolution of the glass surface. However, it is considered to be a minimal requirement that the second type of marking does not show deterioration when exposed to that test (see also Note to Clause 8.6.2).
- 2 Engraving of glass is particularly advised against as it causes local weakening of the glass and facilitates fracturing and breakage when exposed to mechanical and thermal stresses.

**3.3 Lead glass**

Glass with lead added in the manufacturing process.

**4 MATERIAL**

The measure shall be formed from colourless, high grade, annealed glass, free of particulate matter. The material shall not be a source of contamination to liquids contained within the measure. Lead glass shall not be used.

NOTE: The determination of resistance for leaching is described in Appendix A.