

SUPERSEDED BY

AS 2278-1986

AS 2278-1979  
UDC 621.798.16:669

# Australian Standard 2278-1979

---

## METAL AEROSOL CONTAINERS CLASSIFICATION, FILLING AND TESTING



**STANDARDS ASSOCIATION OF AUSTRALIA**

*Incorporated by Royal Charter*

THE FOLLOWING SCIENTIFIC, INDUSTRIAL, CONSUMER AND GOVERNMENTAL organizations and departments were officially represented on the committee entrusted with the preparation of this standard:

Aerosol Association of Australia  
Australian Federation of Consumer Organizations  
Australian Retailers Association  
Confederation of Australian Industry  
Department of Health Canberra  
Department of Labour and Industry, New South Wales  
Department of Labour and Industry, Victoria  
Department of Labour Relations, Queensland  
Department of Science and the Environment  
Packaging Council of Australia  
Railways of Australia Committee  
Royal Australian Chemical Institute

---

This standard, prepared by Committee PK/13, Aerosol Containers, was approved by the Packaging Standards Board on behalf of the Council of the Standards Association of Australia on 6 April 1979, and was published on 1 July 1979.

To keep abreast of progress in industry, Australian standards are regularly reviewed. Suggestions for improvements to published standards, addressed to the head office of the Association, are welcomed.

---

*This standard was issued in draft form for public review as DR 78014.*

AUSTRALIAN STANDARD

**METAL AEROSOL  
CONTAINERS—  
CLASSIFICATION, FILLING  
AND TESTING**

**AS 2278—1979**

First published (as AS Z42) .....	1967
Revised and issued as AS 2278 .....	1979

**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA  
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**

**ISBN 0 7262 1721 2**

## PREFACE

This standard was prepared by the Association's Committee on Aerosol Containers, under the direction of the Packaging Standards Board, as the revision of AS Z42—1967, which it accordingly supersedes.

The revision was undertaken both to metricate the standard and to incorporate various amendments that have previously been published. The increasing use of larger sized aerosol containers required that the standard deal with containers of brim-full capacities up to 1400 mL (previously 820 mL).

Any filled aerosol container may be potentially hazardous if it is overfilled, overpressurized or subjected to elevated temperatures. Consequently, during the revision of the standard, greater emphasis has been placed on the testing requirements of filled aerosol containers, and, where necessary, additional testing procedures have been included. An important additional requirement is that filled aerosol containers must not become liquid-full at 85°C.

In addition, the methods of testing unfilled aerosol containers have been revised to include more information concerning pass or fail requirements.

The flammability of the product to be dispensed is also an important safety consideration. A method for determining flame propagation characteristics has been included.

This standard makes reference to the following Australian standards:

- AS 1216 Code of Practice for Safe Handling of Dangerous Goods  
Part 1—Classification and Class Labels for Dangerous Goods
- AS 1517 Tinplate and Blackplate  
Part 1—Sheet  
Part 2—Coil
- AS 1866 Wrought Aluminium and Aluminium Alloy Drawn Wire, Rod, Bar and Strip for General Engineering Purpose
- AS Z47 Glossary of Packaging Terms\*

---

\*Under revision.

©Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1979

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

## CONTENTS

	<i>Page</i>
<b>SECTION 1. SCOPE AND GENERAL REQUIREMENTS</b>	
1.1 Scope .....	4
1.2 Definitions .....	4
1.3 Classification .....	4
1.4 Materials of Construction .....	4
1.5 Marking of Empty Aerosol Containers .....	5
<b>SECTION 2. FILLING REQUIREMENTS</b>	
2.1 Maximum Volume .....	6
2.2 Maximum Pressures .....	6
2.3 Special Product Requirements .....	6
2.4 Testing of Filled Aerosol Containers .....	6
2.5 Marking of Filled Aerosol Containers .....	6
<b>APPENDICES</b>	
A Testing of Unfilled Aerosol Containers .....	7
B Testing of Filled Aerosol Containers .....	8
C Special Testing for Aerosol Containers Filled with Tyre Indicator Products .....	9
D Flame Propagation .....	10

## STANDARDS ASSOCIATION OF AUSTRALIA

**Australian Standard**  
for  
**METAL AEROSOL CONTAINERS—CLASSIFICATION,  
FILLING AND TESTING**

## SECTION 1. SCOPE AND GENERAL REQUIREMENTS

**1.1 SCOPE.** This standard sets out requirements for non-refillable metal aerosol containers of up to 1400 ml. brim-full capacity and 85 mm internal diameter. It classifies aerosol containers according to their pressure requirements, and specifies the materials of construction and certain constructional and testing requirements. It also specifies the maximum volume and pressure of the contents of filled aerosol containers and provides methods of testing filled aerosol containers.

This standard does not apply to aerosol containers the contents of which are separated from the propellant by physical means such as in a barrier pack type of container.

**NOTE:** This standard applies only to aerosol containers for the packing of products which require normal protection and which are not subject to extreme conditions during transport, handling and storage. In other cases, the standard should be supplemented by discussion between the container supplier and the purchaser. In particular, the standard should not be used without further qualification to describe aerosol containers for use with dangerous goods.

**1.2 DEFINITIONS.** For the purpose of this standard the definitions given in AS Z47 and the following definitions apply:

**Aerosol container**—a non-refillable container designed to hold its intended contents at a pressure greater than atmospheric, the pressure being provided by means of a propellant, and designed to dispense those contents by means of a valve.

**Product**—the total contents of a filled aerosol container including the propellant.

**1.3 CLASSIFICATION.**

**1.3.1 Pressure.** Aerosol containers shall be classified according to the maximum pressure they are designed to withstand, as follows (see also Table 1.1):

**Low pressure container**—an aerosol container for products which will generate a pressure not exceeding 970 kPa at 55°C.

**Intermediate pressure container**—an aerosol container for products which will generate a pressure not exceeding 1400 kPa at 55°C.

**High pressure container**—an aerosol container for products which will generate a pressure not exceeding 2400 kPa at 55°C.

**1.3.2 Size.** Aerosol containers shall be grouped according to their internal diameter and brim-full capacity, as follows (see also Table 1.1):

**Group 1**—internal diameter not more than 75 mm and brim-full capacity not exceeding 820 mL.

**Group 2**—internal diameter exceeding 75 mm but not more than 85 mm, and brim-full capacity exceeding 820 mL but not more than 1400 mL.

**1.4 MATERIALS OF CONSTRUCTION.**

**1.4.1 Permissible Materials.** Aerosol containers shall be made from any of the following materials:

- (a) Carbon or alloy steel that complies with the relevant sections of AS 1517, Parts 1 or Part 2.

**TABLE 1.1**  
**CLASSIFICATION OF AEROSOL CONTAINERS**

Group	Pressure classification	Internal diameter <i>d</i> mm	Brim-full capacity <i>V</i> mL	Distort pressure* kPa	Burst pressure† kPa
1	Low	$d \leq 75$	$V \leq 820$	1100	1450
	Intermediate	$d \leq 75$	$V \leq 820$	1240	1660
	High	$d \leq 75$	$V \leq 820$	1450	1860
2	Low	$75 < d \leq 85$	$820 < V \leq 1400$	1100	1650
	Intermediate	$75 < d \leq 85$	$820 < V \leq 1400$	1240	1930
	High	$75 < d \leq 85$	$820 < V \leq 1400$	1450	2100

\*Determined in accordance with Appendix A, Paragraph A2.

†Determined in accordance with Appendix A, Paragraph A3.

**NOTE:** See also Clause 2.2 for maximum filling pressures.