

Under Revision DR 93048

Superseded by AS/NZS 2312:1994

ENDORSED AS SUITABLE FOR USE IN N.Z.

SEE ALSO SANZ MP 2312:1987

AS 2312—1984

UDC 624.014.2:691.71:620.197.6

Australian Standard[®] 2312—1984

see also

*"Guide to AS 2312"
published by WATLYL
GA1.7
3*

GUIDE TO THE PROTECTION OF IRON AND STEEL AGAINST EXTERIOR ATMOSPHERIC CORROSION



STANDARDS ASSOCIATION OF AUSTRALIA

Incorporated by Royal Charter



This Australian standard was prepared by Committee MT/14, Corrosion of Metals. It was approved on behalf of the Council of the Standards Association of Australia on 28 August 1984 and published on 7 December 1984.

received in Sales Dept 20.5.1985

The following interests are represented on Committee MT/14:

Aluminium Development Council
Australasian Corrosion Association
Australasian Institute of Metal Finishing
Australian Gas Association
Australian Institute of Steel Construction Ltd
Australian Zinc Development Association
Bureau of Steel Manufacturers of Australia
Commonwealth Scientific and Industrial Research Organization
Confederation of Australian Industry
Copper Development Association of Australia Limited
Department of Defence
Electricity Supply Association of Australia
National Association of Australian State Road Authorities
Railways of Australia Committee
Society of Automotive Engineers—Australasia
State Electrolysis Committee
Telecom Australia
University of New South Wales

Representatives of the following interest also participated in the drafting of this standard:

Department of Housing and Construction

Review of Australian Standards. To keep abreast of progress in industry, Australian standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all SAA publications will be found in the Catalogue of SAA Publications; this information is supplemented each month by SAA's journal 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn standards.

Suggestions for improvements to Australian standards, addressed to the head office of the Association, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian standard should be made without delay in order that the matter may be investigated and appropriate action taken.

AUSTRALIAN STANDARD

GUIDE TO THE PROTECTION OF IRON AND STEEL AGAINST EXTERIOR ATMOSPHERIC CORROSION

AS 2312—1984

First published.....	1980 ✓
Second edition.....	1984

PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.

ISBN 0 7262 3506 7



PREFACE

This edition of this standard was prepared under the direction of the Association's Committee on Corrosion of Metals by its subcommittee on corrosion protection of steelwork, to supersede AS 2312—1980. The standard provides guidance for architects, engineers, builders, the surface coating industry and users of protective services in general on coating systems for the protection of iron and steel against exterior atmospheric corrosion.

The subject of this standard was previously dealt with in SAA MA1, Manual on Steel Structures, Part 5—Protection of Steel from Corrosion, and the standard represents both a revision and an expansion of SAA MA1.5; whereas, however, SAA MA1.5 contained descriptive information from which a user of the document could arrive at a satisfactory method of protection, this standard is more detailed in that systems have been included with specified lives to first maintenance. Attention is drawn to the fact that the standard is also available in the MA1 format, as a revised edition of SAA MA1, so that users of the Manual will continue to have a complete set of the Part 5 of the Manual.

During drafting of the first (1980) edition of this standard, consideration was given to BS 5493* to which acknowledgement is made. During 1980 a series of seminars was held around Australia to introduce AS 2312, and to discuss aspects which related to the preparation and use of the standard. Comments forthcoming from the seminars were considered by the subcommittee as being desirable for inclusion in AS 2312 since they provided additional information and elaboration on particular subjects, and their inclusion initiated this second edition.

In providing recommendations on appropriate protection systems, the committee was aware of the large number of systems used commercially and to avoid confusion included only a limited range of systems for each type of environment.

The committee acknowledges the developments which are taking place in the protection of iron and steel and will monitor these in order to make such changes to this standard as may become necessary.

*BS 5493 Code of Practice for Protective Coating of Iron and Steel Structures Against Corrosion.

© Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1984

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

CONTENTS

	<i>Page</i>
FOREWORD	
Introduction	5
Guidance on the Use of the Standard.....	5
SECTION 1. SCOPE AND GENERAL	
1.1 Scope	9
1.2 Application	9
1.3 Referenced Documents	9
1.4 Safety and Health	9
SECTION 2. ATMOSPHERIC ENVIRONMENTS	
2.1 General	10
2.2 Atmospheric Classifications (Applicable to Steel)	10
SECTION 3. CORROSION PROTECTION SYSTEMS	
3.1 General	12
3.2 Coating/Exposure Classifications	12
3.3 Recommended Coating Systems	12
SECTION 4. PLANNING AND DESIGN FOR CORROSION PROTECTION	
4.1 General	14
4.2 Planning	14
4.3 Design	14
SECTION 5. SURFACE PREPARATION TREATMENTS	
5.1 General	25
5.2 Degreasing	25
5.3 Cleaning and Preparation using Acid Solutions (Non-immersion)	25
5.4 Abrasive Blast Cleaning	25
5.5 Pickling	26
5.6 Phosphate Conversion Coatings	26
5.7 Flame Cleaning	26
5.8 Power Tool Cleaning	26
5.9 Hand Tool Cleaning	27
5.10 Protection of Steel During Extended Fabrication	27
SECTION 6. METALLIC COATINGS FOR CORROSION PROTECTION	
6.1 General	28
6.2 Hot Dip Galvanizing	28
6.3 Metal Spray Coatings	29
6.4 Electroplated Coatings	29
6.5 Roofing and Cladding Materials—Steel Base	30
SECTION 7. PAINT COATING SYSTEMS FOR CORROSION PROTECTION	
7.1 General	31
7.2 Design Considerations	31
7.3 Coating Systems Reference Numbers	31
7.4 Effects of Delays During Painting	32
7.5 Paint Coating Systems	32
7.6 Selection of Colour	32
7.7 Heat Resisting Paints	32

SECTION 8. PAINTING AND PAINT APPLICATION METHODS

8.1	General	43
8.2	Type of Paint	43
8.3	Preparation of the Substrate	43
8.4	Climatic Conditions	43
8.5	Sequence of Operations	43
8.6	Methods of Application	44
8.7	Standard of Workmanship	44
8.8	Time Requirements	44
8.9	Paint Thickness	46
8.10	Paint Storage	46
8.11	Health Hazards and Safety Precautions	46

SECTION 9. WRAPPING TAPES FOR CORROSION PROTECTION

9.1	General	49
9.2	Petroleum-impregnated Tapes	49
9.3	Plastics Tapes	49

SECTION 10. MAINTENANCE OF PROTECTIVE COATING SYSTEMS

10.1	General	52
10.2	Recommended Criteria for Assessing When to Paint or Repair	52
10.3	Pretreatment Before Prepainting	52
10.4	Repainting	53
10.5	Repairs to Welded Structures and of Minor Damage to Coatings	54

SECTION 11. INSPECTION AND TESTING

11.1	General	55
11.2	Authority	55
11.3	Preliminary Discussions	55
11.4	Duties of Inspectors	55
11.5	Final Inspection	56
11.6	Guidance on the Use of Thickness Gauges	56

SECTION 12. PREPARATION OF COATING SPECIFICATIONS

12.1	General	58
12.2	Content	58

APPENDICES

A	Atmospheric Corrosion of Carbon Steels in Various Australian Climates	60
B	Description of Paint Types	62
C	Economics of Corrosion Protection	67

ANNEX. LIST OF REFERENCED DOCUMENTS

73

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

for

GUIDE TO THE PROTECTION OF IRON AND STEEL AGAINST EXTERIOR
ATMOSPHERIC CORROSION

FOREWORD

Introduction

This standard gives recommendations for the selection and specification of protective measures against atmospheric corrosion that are to be applied to structural steelwork. It is written on the assumption that a decision has been taken to use such measures.

It is important at the design stage to determine the prime reasons for requiring corrosion protection, as these can influence the type of protection system to be specified. For instance, there are many situations in which corrosion protection may not be necessary nor economically feasible because the corrosion rate is too low to affect the integrity of the structure, or an appropriate allowance of section thickness could be made for corrosion in the design. Under these circumstances a protection system may be applied for reasons other than structural integrity, e.g. aesthetics.

Examples where protection against structurally damaging corrosion may not be required are as follows:

- Temporary steelwork.
- Interiors of most closed and many partly open buildings.
- Steel exposed for short periods only, e.g. during construction.
- Hot and dry climates.
- Steel surrounded by an adequate thickness of concrete.
- Underground piling (depending on the surface soil conditions).
- Hermetically sealed interiors of hollow steel members.
- Structures which are approaching the end of their economic lives.

The painting of the interiors of buildings where low corrosive conditions normally prevail is covered by AS 2311. Whereas AS 2311 allows the common practice of 'wire brush clean and prime' on steel components such as roof trusses and ceiling joists, this standard deals with the more corrosive situations found in the external atmosphere, where steel is subject to the action of the elements, and atmospheres inside some industrial buildings in which corrosive agents are released, e.g. pickling shops.

This standard also includes recommendations for the protection of steel for reasons other than the prevention of structural damage caused by corrosion, such as—

- aesthetics
- increasing the level of light in work areas
- the protection of inaccessible points in marginally corrosive situations
- a form of insurance in situations regarded basically as being of low corrosivity but where there is some doubt about the assessment.

The prime reason(s) for the application of a corrosion protection system having been decided, this standard offers a selection of systems based on expected service lives to first maintenance in various environments. The systems recommended herein represent acceptable standards which may be used for the purpose and which are based on good industrial practice and usage. Nevertheless, it must be borne in mind that local knowledge of any corrosion problem may influence the decisions taken in the selection of an appropriate system.

Many of the systems outlined will provide equal performance in the field. The system chosen will depend on many factors such as—

- supplies of materials
- location
- available equipment
- labour
- cost.

This standard has been prepared in sections so as to be of the greatest benefit to the user. Reference to each of the sections is of the utmost importance where a specification for an appropriate system is being prepared.

Guidance on the Use of the Standard

This standard cannot be called up unaccompanied by the detail intended to be derived from it.

For each contract the owner or designer should draw up a complementary protection schedule detailing the surface preparation, the coating system, methods, conditions of application and inspection procedures.

As a consequence, the calling up of this standard without the complementary specification renders such cross-referencing invalid.

The following information highlights the various steps which need to be taken in using this standard to the best advantage.

The most frequent use to which this standard is expected to be put is for the protection of steel structures where it has been decided that such action is required.

When a decision has been taken to protect a structure, certain basic steps should be undertaken. These include the following:

- (a) Decide a life requirement to first maintenance for the coating systems chosen, based on the requirements of the structure.
- (b) Identify the exposure conditions and select an appropriate group of systems.
- (c) Identify the microenvironment, compare and select a particular system from within the group of systems chosen in step (b) above.
- (d) Specify the system as completely as possible.