

Australian Standard™

**Dezincification resistance of copper alloys**



This Australian Standard was prepared by Committee MT-014, Corrosion of Metals. It was approved on behalf of the Council of Standards Australia on 25 May 2006. This Standard was published on 13 June 2006.

---

The following are represented on Committee MT-014:

Australian Corrosion Association  
Australasian Institute of Metal Finishing  
Australian Chamber of Commerce and Industry  
Australian Electrolysis Committee  
Australian Paint Manufacturer's Federation  
Australian Paint Approval Scheme  
Austroads  
Bureau of Steel Manufacturers of Australia  
Department of Defence  
Division of Building, Construction and Engineering, CSIRO  
Galvanizers Association of Australia  
Telstra  
United Water International  
Water Corporation of Western Australia  
Corrosion consultants  
Water Services Association of Australia (WSAA)  
Water Authority of Western Australia

---

### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Web Shop at [www.standards.com.au](http://www.standards.com.au) and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

Australian Standards™ and other products and services developed by Standards Australia are published and distributed under contract by SAI Global, which operates the Standards Web Shop.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.org.au](mailto:mail@standards.org.au), or write to the Chief Executive, Standards Australia, GPO Box 476, Sydney, NSW 2001.

---

*This Standard was issued in draft form for comment as DR 06197.*

Australian Standard™

**Dezincification resistance of copper alloys**

Original as AS 2345—1980.  
Previous edition 1992.  
Third edition 2006.

**COPYRIGHT**

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia, GPO Box 476, Sydney, NSW 2001, Australia

ISBN 0 7337 7493 8

## PREFACE

This Standard has been prepared by the Australian members of the Joint Standards Australia/Standards New Zealand Committee MT-014, Corrosion of Metals, to supersede AS 2345—1992, *Dezincification resistance of copper alloys*.

After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian Standard rather than an Australian/New Zealand Standard.

The objective of this revision is to reconfirm the procedures, and update the reference documents and formatting.

The test method given in Appendix C of this Standard is based on the International Organization for Standardization publication ISO 6509:1981, *Corrosion of metals and alloys—Determination of dezincification resistance of brass*, but contains more detailed information on the testing procedure especially in respect to the measurement of dezincification.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the appendix to which they apply. A ‘normative’ appendix is an integral part of a Standard, whereas an ‘informative’ appendix is only for information and guidance.

## CONTENTS

	<i>Page</i>
FOREWORD.....	4
1 SCOPE.....	5
2 REFERENCED DOCUMENTS.....	5
3 DEFINITIONS.....	5
4 GENERAL REQUIREMENTS.....	6
APPENDICES	
A PURCHASING GUIDELINES.....	8
B LISTING OF EXAMPLES OF CATEGORY I ALLOYS .....	9
C TEST METHOD FOR THE ASSESSMENT OF THE SUSCEPTIBILITY TO DEZINCIFICATION OF COPPER ALLOYS CONTAINING ZINC.....	11
D GENERAL INFORMATION ON FACTORS WHICH AFFECT THE RESISTANCE OF COPPER ALLOYS TO DEZINCIFICATION.....	17

## FOREWORD

It is generally accepted that copper alloys that contain not more than 15 percent zinc and alpha brasses that are inhibited by the presence of adequate levels of arsenic or antimony are resistant to the corrosion phenomenon called 'dezincification' when in service in water or soil environments. In addition, some alpha-beta brasses can be dezincification resistant provided they have certain structural characteristics and the alpha phase is inhibited.

An accelerated test method is given in this Standard for the assessment of the susceptibility of brasses, and other copper alloys containing zinc, to dezincification. It enables the measurement of depth but does not give information on the mode of dezincification.

## STANDARDS AUSTRALIA

### Australian Standard Dezincification resistance of copper alloys

#### 1 SCOPE

This Standard specifies procedures for determining the resistance of copper-base alloys containing zinc to the form of corrosion termed 'dezincification', in two steps as follows:

- (a) Alloys are categorized into two groups based on their chemical composition which is used to assess their susceptibility to dezincification.
- (b) Alloys assessed to be resistant to dezincification on the basis of chemical composition do not require testing. Alloys considered to be susceptible can be further evaluated by testing them under accelerated laboratory conditions after the completion of all manufacturing stages. Following this test and where the specified acceptance criteria are met, such alloys can also be regarded as resistant to dezincification.

This Standard also specifies the acceptance criteria for the dezincification resistance of copper/zinc alloy components designed for use in contact with potable water or soils.

NOTE: Advice and recommendations on information to be supplied by the purchaser at the time of enquiry or order are contained in Appendix A.

#### 2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

1565 Copper and copper alloys—Ingots and castings

1566 Copper and copper alloys—Rolled flat products

2738 Copper and copper alloys—Compositions and designations of refinery products, wrought products, ingots and castings

AS/NZS

1567 Copper and copper alloys—Wrought rods, bars and sections

MP 52 Manual of authorization procedures for plumbing and drainage products

#### 3 DEFINITIONS

For the purpose of this Standard, the definitions below apply.

##### 3.1 Dezincification

Corrosion of copper/zinc alloys involving loss of zinc leaving a residue of spongy or porous copper.

##### 3.2 Dezincification-resistant copper/zinc alloys

Alloys having the appropriate chemical composition and physical characteristics to enable them to meet the dezincification test requirements of this Standard.

##### 3.3 Test piece

A piece prepared for testing and made from a test specimen by some mechanical operation.