

Australian Standard<sup>®</sup>

---

**Materials for solar collectors for  
swimming pool heating**

**Part 1: Rubber materials**

---

This Australian Standard was prepared by Committee CS/28. It was approved on behalf of the Council of Standards Australia on 21 May 1990 and published on 17 September 1990.

---

The following interests are represented on Committee CS/28:

Australian and New Zealand Solar Energy Society  
Australian Gas Association  
CSIRO, Division of Building, Construction and Engineering  
Department of Business and Consumer Affairs, N.S.W.  
Department of Administrative Services, Australian Construction Services  
Department of Industrial Relations and Employment, N.S.W.  
Department of Mines and Energy, N.T.  
Department of Primary Industries and Energy  
Electricity Supply Association of Australia  
Department of Energy, N.S.W.  
Engineering and Water Supply Department, S.A.  
Gas and Fuel Corporation of Victoria  
Master Plumbers and Mechanical Services Association of Victoria  
Melbourne and Metropolitan Board of Works  
Metal Trades Industry Association of Australia  
Solar Energy Industries Association of Australia  
Trade Practices Commission  
University of New South Wales  
Victorian Solar Energy Council

Additional interests participating in preparation of Standard:

Plastics Institute of Australia  
Rubber Manufacturers' Association of Australia

---

*Review of Australian Standards.* To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

---

*This Standard was issued in draft form for comment as DR 89014.*

Australian Standard<sup>®</sup>

---

**Materials for solar collectors for  
swimming pool heating**

**Part 1: Rubber materials**

---

First published as AS 2369.1—1990.

PUBLISHED BY STANDARDS AUSTRALIA  
(STANDARDS ASSOCIATION OF AUSTRALIA)  
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 6308 7

## PREFACE

This Standard was prepared by the Standards Australia Committee on Solar Water Heating, in response to proposals from the Victorian Solar Energy Council, and the Rubber Manufacturers' Association of Australia.

Heating of swimming pools to extend the swimming season is becoming popular in the cooler regions of Australia, and solar heating is being recognized as cost effective for this purpose. A Standard for solar heating of swimming pools has been prepared, and in addition to this it was felt that a Standard specifying the necessary properties of collectors was needed. The use of rubber collector strips is common both for household and public pool heating, and this Part of the Standard deals with rubber (EPDM) materials.

The requirements of this Standard are based on well established test methods for elastomeric materials. The tests have been selected for their relevance to collector performance and service life.

Although this Standard cannot quantify service life due to the difficulty in defining and controlling the many factors which affect solar collectors, the criteria used herein are based on the performance of materials that have been shown to have a satisfactory performance in pool heating applications.

## CONTENTS

	<i>Page</i>
1 SCOPE .....	3
2 REFERENCED DOCUMENTS .....	3
3 GENERAL .....	3
4 FORMULATION .....	3
5 TEST PIECES .....	3
6 REQUIREMENTS .....	4
7 DETERMINATION OF PROPERTIES OF THE MATERIAL .....	4
8 TESTS ON MATERIAL AS MANUFACTURED .....	5
9 TESTS ON MATERIAL AFTER AGEING .....	5
10 TESTS ON MATERIAL AFTER EXPOSURE TO CHEMICALS .....	5
11 MARKING .....	5
APPENDIX A. EXPOSURE TO ULTRA VIOLET LIGHT .....	6

## © Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

## STANDARDS AUSTRALIA

## Australian Standard

## Materials for solar collectors for swimming pool heating

## Part 1: Rubber materials

**1 SCOPE.** This Standard specifies the properties of ethylene propylene diene rubbers (EPDM) used in the manufacture of unglazed collectors intended for solar heating of swimming pools. The Standard is applicable to materials used for collectors which take the form of tubing, or absorber strips comprising water passages joined by a web.

The requirements of this Standard are based on the assumption that the solar pool heating system in which these materials are used will be installed in accordance with AS 3634, and that the pool water will be maintained in accordance with AS 3633.

**2 REFERENCED DOCUMENTS.** The documents below are referred to in this Standard.

## AS

- |        |   |
|--------|---|
| 1180   | Methods of test for hose made from elastomeric materials<br>Method 5A: Hydrostatic pressure — Burst test<br>Method 5B: Hydrostatic pressure — Proof test  |
| 1683   | Methods of test for rubber<br>Method 11: Tension testing of vulcanized rubber<br>Method 15: Indentation hardness of rubber and plastics by means of a durometer<br>Method 19: Rubber test mixes — Preparation, mixing and vulcanization — Equipment and procedures<br>Method 24: Rubber — Vulcanized — Determination of resistance to ozone cracking — Static strain test |
| 2433   | Plastics — Method for exposure to ultraviolet lamps   |
| 2620   | Domestic garden hose  |
| 2620.1 | Part 1: Reinforced hose   |
| 3633   | Private swimming pools — Water quality  |
| 3634   | Solar heating systems for swimming pools  |

## ISO

- |        |   |
|--------|---|
| 188    | Rubber, vulcanized — Accelerated ageing or heat resistance tests                      |
| 4661/1 | Rubber, vulcanized — Preparation of samples and test pieces<br>Part 1: Physical tests |

**3 GENERAL.** The materials required to be evaluated under three conditions —

- (a) as manufactured (qualification tests);
- (b) after ageing in air, water, and
- (c) after exposure to chemicals.

Conditions (b) and (c) are not cumulative, and are applied to separate test pieces.

**4 FORMULATION.** The formulation and conditions of cure employed in the manufacture of materials for solar absorbers shall be such that the materials will satisfactorily withstand the service conditions and meet the requirements of this Standard. As part of the formulation, the mix may include the addition of a suitable chemical for the purpose of inhibiting the growth of micro-organisms. Any such chemical shall, as present in the final cured material, be essentially insoluble in normal treated pool water, as described in AS 3633.

Any change in the formulation or conditions of manufacture will generally necessitate re-assessment of the material, particularly with regard to resistance to ozone, ultraviolet light, burst pressure, and common pool chemicals.

**5 TEST PIECES.** The test pieces required for the tests described in Clauses 7.1 to 7.3, and 7.6 and 7.7, shall be prepared from flat sheet, in accordance with AS 1683.19 and shall be satisfactorily cured.

The test piece required in Clauses 7.4 and 7.5 shall be a sample of the finished tube or absorber strip containing multiple water passages. The free length of tube or strip, after attachment of fittings shall be nominally 1 m.

Test pieces shall be prepared generally in accordance with ISO 4661/1.