

Australian Standard 2373, Part 1—1980

CONTROL CABLES FOR ELECTRICITY SUPPLY SYSTEMS

Part 1—GENERAL CONTROL CABLES

[Title allocated by Designation Cataloguing Authority:

CABLE, POWER, ELECTRIC (Part 1, Supply General Control)
NATO Supply Classification 6145]



STANDARDS ASSOCIATION OF AUSTRALIA

Incorporated by Royal Charter



THE FOLLOWING SCIENTIFIC, INDUSTRIAL AND GOVERNMENTAL ORGANIZATIONS and departments were officially represented on the committee entrusted with the preparation of this standard:

Australian-British Trade Association
Australian Electrical and Electronic Manufacturers Association
Confederation of Australian Industry
Defence Standardization Committee
Department of Construction
Department of Transport
Electrical Approvals Authorities
Electrical Contractors Associations of Australia
Electrical Testing Laboratories
Electricity Supply Association of Australia
Metals Industry Organizations
Railways of Australia Committee
Representative of SAA Committee EL/2
Telecom Australia

This standard, prepared by Committee EL/2, Electric Wires and Cables, was approved on behalf of the Council of Standards Association of Australia on 5 May 1980, and was published on 1 August 1980.

To keep abreast of progress in industry, Australian standards are subject to continuous review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that their standards are up-to-date. Full details of all SAA publications will be found in the Annual List of Australian Standards; these details are supplemented by monthly listings in the SAA journal 'The Australian Standard'. Information on the Annual List and 'The Australian Standard' may be obtained from any sales office of the Association, where details are also available of the current status of individual standards. Suggestions for improvements to published standards, addressed to the head office of the Association, are welcomed.

This standard was issued in draft form for public review as DR 78161.

AUSTRALIAN STANDARD

**CONTROL CABLES FOR ELECTRICITY
SUPPLY SYSTEMS**

**Part 1
GENERAL CONTROL CABLES**

AS 2373, Part 1-1980

First published 1980

**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**

ISBN 0 7262 1979 7



5 AUG 1980

PREFACE

This standard was prepared by the Association's Committee on Electric Wires and Cables, at the request of the Electricity Supply Association of Australia.

The standard is Part 1 of a two-part standard for multicore and twisted pair cables used for control, supervisory, protection and instrumentation circuits both within power station and substation confines and to and from these stations. Part 1 covers general control cables and Part 2* covers aerial control cables.

The nominal cross-sectional areas of conductors of 0.5 mm² and above are taken from AS 1125, Conductors in Insulated Electric Cables and Flexible Cords, and are identical with the values recommended in IEC 228, Nominal Cross-sectional Areas and Composition of Conductors of Insulated Cables. For areas below 0.5 mm², only single strand conductors have been specified, namely 0.2 mm² and 0.35 mm².

Only two types of insulation are provided for in this standard, namely polyethylene (PE) and PVC. The thicknesses of insulation for cables having conductors of nominal cross-sectional area of 0.5 mm² and above are based on values specified in AS 3191, Electric Flexible Cords, and AS 3147, PVC Insulated Electric Cable and Flexible Cables for Working Voltages 0.6/1 kV.

Two non-metallic sheath materials are provided in the standard, namely polyethylene and moisture resistant PVC compound.

The standard also provides for bedding, armouring, moisture barriers, metal sheaths and oversheaths.

Requirements for bending radii for control cables are under consideration.

The standard makes reference to the following standards:

- AS 1026 Impregnated Paper Insulated Cables for Electricity Supply at Working Voltages up to and Including 35 kV
- AS 1049 Polyethylene Insulation and Sheath of Telecommunication Cables
- AS 1125 Conductors in Insulated Electric Cables and Flexible Cords
- AS 1660 Methods of Test for Electric Cables and Flexible Cords (Including Conductors, Insulation and Sheath)
 - Part 2 — Test Methods for Insulation, Sheath and Braid
 - Part 3 — Test Methods for Complete Cable.
- AS 1931 High Voltage Testing Techniques
- AS 3147 PVC Insulated Electric Cables and Flexible Cables.
- AS 3191 Electric Flexible Cord
- AS C91 Lead and Lead Alloy Sheaths of Electric Cable

* In course of preparation.

© Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1980
 Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

CONTENTS

	<i>Page</i>
SPECIFICATION	
1 Scope	4
2 Definitions	4
3 Operating Voltage	4
4 Conductors	4
5 Insulation	4
6 Number of Cores and Configuration	5
7 Length of Lay of Cores	5
8 Fillers and Binders	5
9 Binder Tapes	5
10 Identification of Cores	5
11 Belt Insulation	5
12 Metallic Screens	5
13 Moisture Barrier	6
14 Metal Sheath	6
15 Non-metallic Sheath	7
16 Bedding	7
17 Armour	7
18 Oversheath Over Armour	7
19 Insect-resistant Barrier	7
20 Fire Tests	7
21 Testing — General	7
22 Marking	7
23 Construction and Dimensions	8
APPENDICES	
A High Voltage Test	12
B Maximum d.c. Resistance of 0.20 mm ² and 0.35 mm ² Solid Circular Conductors	13
C Information Required When Enquiry or Order	14
D Environmental Stress Cracking Test	15
E Colours of Manufacturers' Identification Threads	18
TABLES	
1 Colour Code for Twisted Pair Construction	6
2 Lay-up Information for Twisted-pair Cables	6
3 Average Thickness of Lead-alloy Sheath	7
4 Tests — Criteria, Category and Reference	9
5 Dimensions of Unarmoured Multicore Cables	10
6 Dimensions of Twisted-Pair Cables	10
7 PVC or PE Oversheath Thickness for Armoured Cables	11

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard
 for
CONTROL CABLES FOR ELECTRICITY SUPPLY SYSTEMS

PART 1 — GENERAL CONTROL CABLES

1 SCOPE. This standard specifies screened and unscreened PVC insulated multicore control cable and screened polyethylene (PE) insulated twisted-pair control cables for voltages up to and including 0.6/1 kV for use in conjunction with electricity supply systems.

It applies to cables intended for use in control, supervisory, protection and instrumentation circuits within power station and substation confines, between one station and another and radiating from stations. Control cables complying with this standard may be used in industrial applications.

It does not apply to cables used solely for telecommunication purposes.

2 DEFINITIONS. For the purpose of this standard the definitions relating to conductors in AS 1125 and the following definitions apply:

2.1 Core — the conductor with its insulation but not including any protective covering.

2.2 Wavelength or length of lay — the axial distance between each successive crest of the waveform or turns of the helix formed by a core of a multicore cable or core of a pair or pairs of twisted-pair cable.

2.3 Lay-up — the assembling of cores in a waveform or helical configuration to impart a degree of flexibility.

2.4 Control cable — cable used for control, measuring, protection and communication circuits.

2.5 Voltage designation — for cables for a.c. systems, the rated voltages U_0 and U expressed in the form U_0/U ; or for cables for d.c. systems, the rated voltage U_0 .

where —

U_0 is the r.m.s. power frequency voltage to earth of the supply system or d.c. voltage of the supply system for which the cable is designed; and

U is the r.m.s. power frequency voltage between phases of the supply system and for which the cable is designed.

2.6 Routine tests — tests made by the manufacturer on all finished cable lengths to demonstrate the integrity of the cable.

2.7 Special tests — tests made by the manufacturer on samples of completed cable, or components taken from a completed cable, so as to verify that the finished product meets the design specifications.

2.8 Type tests — tests required to be made by the manufacturer before supplying on a general commercial basis a type of cable covered by this standard in order to demonstrate satisfactory performance characteristics to meet the intended application. These tests are of such a nature that, after they have been made, they need not be repeated, unless changes are made in the cable materials or design which might change the performance characteristics.

3 OPERATING VOLTAGE. The rated voltage U_0/U recognized for the purpose of this standard is 0.6/1 kV.

4 CONDUCTORS. Conductors shall be of annealed copper of the type indicated in the appropriate tables of dimensions (Tables 5 and 6) and for conductor sizes of 0.5 mm² and above shall comply with the appropriate requirements and dimensions in AS 1125. Conductors below 0.5 mm² shall comply with the relevant requirements of AS 1125 and the maximum d.c. resistance at 20°C shall be as given in Appendix B.

Although acceptable, the tinning of conductors is not required by this standard. Where such tinning is provided, the wires taken from the finished conductor shall not be required to pass the tinning test specified in AS 1125.

5 INSULATION.

5.1 Material. The insulation material shall be one of the following compounds:

- (a) PE — 03 grade polyethylene, complying with the appropriate requirements of AS 1049 (for twisted-pair control cables).
- (b) PVC — V-75 moisture-resistant grade polyvinyl chloride complying with the appropriate requirements of AS 3147 (for multicore control cables).