

Australian Standard[®]

SAA PACKAGING CODE

Part 16—FLEXIBLE PACKAGING

This Australian standard was prepared by Committee PK/25, Packaging Code. It was approved on behalf of the Council of the Standards Association of Australia on 3 December 1985 and published on 3 February 1986.

The following interests are represented on the committee responsible for this draft Australian standard:

Adhesives and Sealants Manufacturers Association
Agricultural and Veterinary Chemicals Association of Australia
Airline Company
Australian Institute of Packaging
Australian Timber Producers Council
Bureau of Steel Manufacturers of Australia
Canmakers Institute of Australia
Confederation of Australian Industry
Department of Defence
Department of Primary Industry
Department of Industry, Technology and Commerce
Glass Packaging Institute of Australia
Packaging Council of Australia
Plastics Institute of Australia Incorporated
Printing and Allied Trades Employers Federation of Australia
Railways of Australia Committee
Technical Association of the Australian and New Zealand Pulp and Paper Industry (Appita)
Victorian Sawmillers Association.

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

First published 1986

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

This standard was issued in draft form for comment as DR 84131.

ISBN 0 7262 4043 5

PREFACE

This standard was prepared by the Association's Packaging Code Committee under the direction of the Packaging Standards Board.

The purpose of this standard is to provide information on and assistance with the use of flexible packaging, e.g. regenerated cellulose film, plastics films, aluminium foil and flexible laminates. Since flexible packaging has many and varied applications, no detailed guidance can be given as the individual circumstances will dictate the type of flexible packaging. Companies specializing in this field may be relied upon to assist the prospective user of flexible packaging.

Some plastics will permit fumigation of the contents of a bag (i.e. gas penetration) if a number of bags are placed under a gas-proof sheet. Alternatively, some plastics bags are sufficiently impermeable to permit in-situ fumigation of individual bags, e.g. by placing phosphine-generating tablets inside a bag.

The subject of insect penetration needs to be considered as even aluminium foil packages are not resistant to boring insects such as the lesser grain borer (*Rhyzopertha dominica*). Furthermore, the warehouse beetle (*Trogoderma variabile*) is a pest of packaged foods in the USA and now that it is present in Australia, it could behave in a similar manner (see AS 2400, Part 4).

The wording in this draft standard has been kept relatively simple but the use of some technical terms is unavoidable. Where explanation of these terms is needed, reference should be made to AS 2400, Part 1.

The SAA Packaging Code has been divided into parts dealing with specific subjects, as follows:

Part	Title
1	Glossary of Packaging Terms*
2	Basic Principles of Packaging Practice*
3	Mechanical aids in Package Handling*
4	Protection Against Spoilage of Packages and their contents by Micro-organisms, Insects, Mites and Rodents*
5	Metal Protection
6	Paper and Board, Wrappers and Containers
7	Timber Containers
8	Textile Bags, Sacks and Wrappings
9	Metal Containers
	9.1 Metal Cans and Tubes*
	9.2 Steel Drums*
10	Cushioning Materials
11	Cordage
12	Adhesive Closing and Sealing Tapes
13	Tensional Strapping*
14	Adhesives for Packaging*
15	Glass Containers and Closures*
16	Flexible Packaging
17	Packaging in Plastics containers*
18	Use of Desiccants in Packaging*
19	Packaging for Airfreight*
20	Handling of Goods in Freight Containers*
21	Packaging of Dangerous Goods
22	Closures*
23	Shrink and Stretch Wrapping*

During the preparation of the SAA Packaging Code, account was taken of material included in BS 1133, Packaging Code, and the assistance obtained from this source is acknowledged.

* Published.

CONTENTS

	<i>Page</i>
1 Scope	5
2 Referenced Documents	5
3 Definitions	5
4 Regenerated Cellulose Film	6
5 Polyethylene Film	8
6 Polypropylene Film	11
7 Polyvinyl Chloride (PVC) Film and Sheeting	13
8 Polystyrene Film and Sheeting	15
9 Polyester Film	17
10 Vinylidene Chloride Copolymer	17
11 Polyamide (Nylon)	17
12 Aluminium Foil	17
13 Polyacrylonitrile	19
14 Polyvinyl Alcohol	19
15 Other Films	19
16 Multilayer Structures (Laminates)	19
17 Odour and Taint	20
 ANNEXES	
A Typical Oxygen and Water Vapour Transmission Rate	20
B Various Materials Used in Multilayer Structures	21
C Some Multilayer Structures and Their Uses	24

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard
SAA PACKAGING CODE

PART 16—FLEXIBLE PACKAGING

1 SCOPE. This standard gives a general description of, and provides information on, nomenclature, availability, properties, end-uses and some methods of test for flexible packaging, e.g. regenerated cellulose film, plastics films and aluminium foil, and gives general guidance on the use of these materials in laminates.

NOTE: Description of some semi-rigid plastics material has been included (to complete the picture) notwithstanding the title of the standard.

2 REFERENCED DOCUMENTS. The following standards are referred to in this standard:

AS 1145	Method for Determination of tensile properties of plastics materials.	BS 3177	Method For Determining the Permeability to Water Vapour of Flexible Sheet Materials Used For Packaging
AS 1326	Polyethylene (Polyethene) Film for Packaging and Allied Purposes	BS 3757	Specification for Rigid PVC Sheet
AS 1734	Wrought Aluminium and Aluminium Alloy Flat Sheet, Coiled Sheet and Plate for General Engineering Purposes.	ISO 2528	Sheet materials—Determination of water vapour transmission rate—Disk method.
AS 2070	Plastics Materials for Food Contact Use.		
AS 2400	SAA Packaging Code Part 1— Glossary of Packaging Terms Part 4— Protection Against Spoilage of Packages and their contents by Microorganisms, Insects, Mites and Rodents Part 23— Shrink and Stretch Wrapping		
AS 2609	Materials Used for the Packaging of Food and Beverages Methods for the Assessment of Odour and Taint Part 1—Sensory method Part 2—Instrumental methods		
ASTM D256	Tests for Impact Resistance of Plastics and Electrical Insulating Materials		
ASTM D746	Test for Brittleness Temperature of Plastic and Elastomers by Impact		
ASTM E-96	Water Vapour Transmission of Materials		
ASTM D882	Tests for Tensile Properties of Thin Plastics Sheeting		
ASTM D 985	Oxygen Gas Transmission Rate Through Plastic Film & Sheeting Using a Coulometric Sensor		
BS 1763	Thin PVC Sheeting (Calendered, Flexible, Unsupported)		
BS 2739	Thick PVC Sheeting (Calendered, Flexible, Unsupported)		
BS 2782	Methods of Testing Plastics		

3 DEFINITIONS. For the purpose of this standard, the definitions in AS 2400, Part 1, and the following apply:

3.1 Biaxial orientation—the process of heating and stretching a film in both machine and transverse direction. Film may then be heat-set to provide stability at elevated temperatures. Shrinkable grades are not heat-set. Monoaxially oriented films are also available.

3.2 Copolymer—the product of the polymerization of two or more monomer materials (e.g. ethylene and vinyl acetate to yield EVA).

3.3 Corona discharge—chemical and physical modification of the surface of a film by subjecting it to an electric discharge which normally increases the surface energy of the film, making it more receptive to inks, adhesives, etc.

3.4 Cross-linked—a polymer may be subjected to a chemical reaction or to ionizing radiation which will cause the polymeric chains to chemically link together at many points along the chain.

3.5 Film—

- (a) Thin sheeting of arbitrarily limited thickness.
- (b) A flat section of plastics material, usually thermoplastic, with a thickness generally less than 500 μ .

3.6 Blown film—film of an extrudable polymer produced by an extrusion-blow method into a continuous tube. The tube is slit in a variety of ways to yield flat film, centrefold film, J-fold film, etc. Gussets may also be formed.

3.7 Cast film—film of an extrudable polymer which is cast in a single continuous sheet onto a chilled roller. Polymer solutions may also be cast into a chemical bath where the polymer is regenerated into a continuous film.

3.8 Coated film—normally a base film which carries a surface coating to provide properties such as sealability, gas barrier, etc.

3.9 Oriented film—film which has been subjected to the process of orientation (see Biaxial orientation).

3.10 Heat set—during the process of orienting a film it may be subjected to a heat treatment while it is held in the stretched form. This treatment relieves the stresses caused by orienting the film and provides heat stability to the film up to the heat-set temperature.