

AS 2434.1

under Revision on see DR99278 CP

SUPERSEDED BY:

AS 2434.1-1999

AS 2434.1—1991

REFERENCE COPY
INFORMATION CENTRE
STANDARDS AUSTRALIA

Australian Standard®

Methods for the analysis and testing of lower rank coal and its chars

Part 1: Determination of the total moisture content of lower rank coal

STANDARDS AUSTRALIA 

STANDARDS AUSTRALIA
22 JAN 1991
SYDNEY INFO. CENTRE

Currently in preview, click here for full version

This Australian Standard was prepared by Committee MN/1, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 21 September 1990 and published on 11 February 1991.

The following interests are represented on Committee MN/1:

Australasian Institute of Mining and Metallurgy
Australian Coal Association
Australian Coal Industry Research Laboratories
Australian Institute of Energy
Bureau of Steel Manufacturers of Australia
Australian Coal Preparation Society
Confederation of Australian Industry
CSIRO, Division of Coal and Energy Technology
Department of Minerals and Energy, N.S.W.
Department of Resource Industries, Qld
Electricity Supply Association of Australia
Institution of Engineers, Australia
Joint Coal Board
National Association of Testing Authorities, Australia
Queensland Coal Board
Royal Australian Chemical Institute
Standing Committee on Coalfield Geology of New South Wales
University of New South Wales
University of Queensland

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

Australian Standard®

**Methods for the analysis and
testing of lower rank coal and its
chars**

**Part 1: Determination of the total
moisture content of lower rank coal**

First published as AS 2434.1—1981.
Second edition 1991.

PREFACE

This Standard was prepared by the Standards Australia Subcommittee on Lower Rank Coal under the supervision of the Committee on Coal and Coke and the direction of the Minerals Standards Board, to supersede AS 2434.1, *Methods for the analysis and testing of brown coal and brown coal char Part 1: Determination of the moisture content of brown coal*.

This edition has been expanded to include a single-stage method, in which the sample is dried in nitrogen, and an azeotropic distillation method.

Procedures for the determination of the moisture in coal and coke as set out in AS 1038, *Methods for the analysis and testing of coal and coke*, are not applicable to lower rank coal, because of its high moisture content.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the Head Office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

| | <i>Page</i> |
|---|-------------|
| SECTION 1 SCOPE AND GENERAL | |
| 1.1 SCOPE | 4 |
| 1.2 REFERENCED DOCUMENTS | 4 |
| 1.3 DEFINITIONS | 4 |
| 1.4 SAFETY | 4 |
| 1.5 SAMPLING AND SAMPLE PREPARATION | 4 |
| 1.6 REPORTING OF RESULTS | 4 |
| 1.7 PRECISION | 4 |
| 1.8 TEST REPORT | 5 |
| SECTION 2 TWO-STAGE METHOD | |
| 2.1 SCOPE OF SECTION | 6 |
| 2.2 PRINCIPLE | 6 |
| 2.3 REAGENTS | 6 |
| 2.4 APPARATUS | 6 |
| 2.5 TEST SAMPLE | 6 |
| 2.6 PROCEDURE | 6 |
| 2.7 CALCULATIONS | 7 |
| SECTION 3 SINGLE-STAGE METHOD | |
| 3.1 SCOPE OF SECTION | 8 |
| 3.2 PRINCIPLE | 8 |
| 3.3 REAGENTS | 8 |
| 3.4 APPARATUS | 8 |
| 3.5 TEST SAMPLE | 8 |
| 3.6 PROCEDURE | 8 |
| 3.7 CALCULATION | 8 |
| SECTION 4 AZEOTROPIC DISTILLATION | |
| 4.1 SCOPE OF SECTION | 9 |
| 4.2 PRINCIPLE | 9 |
| 4.3 REAGENT | 9 |
| 4.4 APPARATUS | 9 |
| 4.5 TEST PORTION | 9 |
| 4.6 PROCEDURE | 9 |
| 4.7 CALCULATION | 10 |

STANDARDS AUSTRALIA

Australian Standard

Methods for the analysis and testing of lower rank coal and its chars

Part 1: Determination of the total moisture content of lower rank coal

SECTION 1 SCOPE AND GENERAL

1.1 SCOPE This Standard sets out three methods for the determination of the total moisture content of lower rank coal. The first method is a two-stage procedure applicable to large (500 g) samples. The second method involves drying under a stream of flowing nitrogen, and is applicable only to laboratory samples of mass of about 10 g. The third method comprises an azeotropic distillation with toluene, and is applicable to a sample mass of 200 g to 500 g.

This Standard is applicable to bed-moist coals or analysis samples, where the moisture is expected to exceed 15 percent.

1.2 REFERENCED DOCUMENTS The following documents are referred to in this Standard:
AS

- 1038 Methods for the analysis and testing of coal and coke.
- 1038.16 Part 16: Acceptance and reporting of results
- 1152 Test sieves
- 2243 Safety in laboratories
- 2418 Glossary of terms relating to solid mineral fuels
- 2434 Methods for the analysis and testing of lower rank coal and its chars
- 2434.7 Part 7: Determination of moisture in the analysis sample of lower rank coal
- 2508 Safe storage and handling information cards for hazardous materials
- 2706 Numerical values—Rounding and interpretation of limiting values

1.3 DEFINITIONS For the purpose of this Standard, the definitions given in AS 2418 apply.

1.4 SAFETY For information on laboratory safety, reference should be made to the relevant parts of AS 2243 and AS 2508.

1.5 SAMPLING AND SAMPLE PREPARATION Where determinations on bed-moist coal are required, it is important that samples are taken as soon as the coal is mined or cored, and as close as possible to the extraction process. Sampling shall be in accordance with recognized sampling procedures.

Once the sample has been taken, it shall be stored immediately in moisture-tight containers, preferably in double-thickness plastic bags.

The gross sample shall then be mixed as well as possible within the bag and, if a soft coal, broken up into small pieces.

NOTE: Often, and particularly in the case of bore core samples enclosed in plastic tubing, water is visible on the plastic tubing/container walls. Generally, the quantity of water is not significant in terms of total moisture content of the sample; however, where the quantity of water is considered significant, its mass should be determined by air-drying, and it should be included in the 'free' or total moisture calculation.

The gross sample shall be crushed as soon as possible, so as to pass a sieve of 11.2 mm aperture.

A subsample of 1000 g shall be taken for the two-stage method. Where the moisture content is less than 20 percent, a similar subsample size shall be used for the azeotropic method. For greater than 20 percent moisture content, a 400 g to 500 g subsample only shall be used for the latter method.

For the single-stage method, a 100 g subsample of ≤ 11.2 mm shall be crushed as soon as possible, so as to pass a sieve having a 4.0 mm aperture and complying with AS 1152.

All subsamples shall be stored in moisture-tight containers prior to analysis. Precautions shall be taken to prevent loss of moisture during handling, crushing and subsampling operations.

1.6 REPORTING OF RESULTS The result, the mean of duplicate determinations, shall be reported to the nearest 0.1 percent, rounded in accordance with AS 2706.

1.7 PRECISION The repeatability should not exceed 0.5 percent absolute. Otherwise reference shall be made to AS 1038.16.

NOTE: No value for reproducibility is quoted for determinations carried out in different laboratories, because of the difficulty of maintaining constant moisture content during transportation between laboratories.