

Australian Standard[®]

**NON-DESTRUCTIVE TESTING—
DETERMINATION OF THICKNESS**

**Part 3 — USE OF ULTRASONIC
TESTING**

This Australian standard was prepared by Committee MT/7, Non-destructive Testing of Metals and Materials. It was approved on behalf of the Council of the Standards Association of Australia on 24 June 1985, and published on 6 September 1985.

The following interests are represented on Committee MT/7:

- Australian Atomic Energy Commission
- Australian Institute for Non-destructive Testing
- Australian Pipeline Industry Association
- Australian Welding Institute
- Bureau of Steel Manufacturers of Australia
- Commonwealth Aircraft Corporation Limited
- Confederation of Australian Industry
- Department of Defence
- Department of Industrial Relations, N.S.W.
- Electricity Supply Association of Australia
- Institute of Australian Foundrymen
- Metal Trades Industry Association of Australia
- Ministry of Employment and Training Victoria
- National Association of Australian State Road Authorities
- National Association of Testing Authorities, Australia
- Pipeline Authority
- Railways of Australia Committee
- Society of Automotive Engineers — Australasia

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

First published 1985

This standard was issued in draft form for comment as DR 82205.

PREFACE

This standard was prepared by the Association's Committee on Non-destructive Testing of Metals and Materials, at the request of industry. It provides a method for the measurement of thickness by non-destructive testing, and is one of a series of standards on thickness measurements; others in the series are as follows:

Part 1 Determination of the Wall Thickness of Pipe by the Use of Radiography

Part 2 Determination of the Remaining Wall Thickness of Corroded Pipe by the Use of Radiography

During preparation of the standard, consideration was given to the following documents issued by the Japanese Society for Non-destructive Inspection:

NDIS 2105 — Evaluation of Performance Characteristics of Portable Pulse-echo Ultrasonic Thickness Meter

NDIS 2408 — Thickness Measuring Method using Portable Pulse-echo Ultrasonic Thickness Meters.

CONTENTS

	<i>Page</i>
METHOD	
1 Scope	4
2 Application	4
3 Referenced Documents	4
4 Definitions	4
5 Equipment	4
6 Calibration	5
7 Preparation of Test Surface	5
8 Single Spot — Single Measurement Method (SS)	5
9 Single Spot — Double Measurement Method (SD)	5
10 Multiple Spot Measurement Method (MS)	5
11 Close Grid Survey Method (CG)	6
12 Open Grid Measurement Method (OG)	6
13 Record of Results	6
14 Test Report	6
APPENDICES	
A Supplementary Information	7
B Guidance on the Determination of Thickness at Elevated Temperatures	8
C Factors Affecting Probe Selection	9
D Nominal Velocity of Sound in Some Common Materials	10
E Determination of Thickness by the Use of Correction Factors and Charts	11
F Factors Affecting Results and Order of Accuracy	13
G Notes on Methods of Measurement	15

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

for

NON-DESTRUCTIVE TESTING — DETERMINATION OF THICKNESS

PART 3 — USE OF ULTRASONIC TESTING

1 SCOPE. This standard sets out five methods for the determination of thickness of material based on the use of ultrasonic pulse-echo principles where scanning and reflecting surfaces are substantially parallel. The methods are as follows:

- (a) Single spot — single measurement (SS).
- (b) Single spot — double measurement (SD).
- (c) Multiple spot measurements (MS).
- (d) Close grid survey method (CG).
- (e) Open grid method (OG).

NOTES:

1. Supplementary information required to augment the standard is set out in Appendix A.
2. Factors affecting the results and order of accuracy achieved are given in Appendix F.

2 APPLICATION. Methods described in this standard are suitable for the determination of thickness of materials where surface temperature is within the range of -10°C to 60°C and where the velocity of sound through the material is either known or can be determined.

The methods may be used where surface temperature is lower than -10°C , or higher than 60°C , but in such cases special precautions are required.

The methods may also be used where Base Line Survey or Key Point Survey concepts are applied as follows:

2.1 Base Line Survey. Base Line Survey entails the measurement of components at nominated locations on new items or alternatively at the time of commissioning of new plant. Results can then be kept on record for comparison against subsequent measurements taken after service use. In addition, initial survey results can be compared to nominated design or drawing thicknesses for construction checking purposes.

2.2 Key Point Survey. Key Point Survey entails routine repeat testing at specific nominated positions on operating components. The locations of key test points are usually determined from anticipated performance characteristics of the component or alternatively from the performance history of the component. Duration between surveys is similarly determined. The Key Point Survey concept allows component performance to be monitored in terms of section loss at the test location, thus allowing maintenance and repair scheduling to be carried out on an ordered basis.

In the application of this standard, the order of accuracy shall be the accuracy of the test equipment. Additional factors affecting ultimate accuracy of the test depend upon conditions peculiar to individual applications, such

as the state of the reflecting and contact surfaces. Flat, smooth surfaces are ideal for accurate measurements, whereas irregular surfaces can cause variable ultrasonic response (see Appendix C).

Small pits or pinholes may not be detected because of insufficient reflecting surface.

NOTE: Guidance on the determination of thickness at elevated temperatures is given in Appendix B.

3 REFERENCED DOCUMENTS. The following standards are referred to in this standard:

- AS 1929 Non-destructive Testing — Glossary of Terms
 AS 2083 Calibration Blocks and Their Methods of Use in Ultrasonic Testing.

4 DEFINITIONS. For the purpose of this standard, the terms and definitions given in AS 1929 and the following apply:

4.1 Nominal thickness (T_n) — specified material thickness at the time of manufacture.

NOTE: Nominal thickness is usually specified in product standards and shown on drawings.

4.2 Indicated thickness (T_i) — thickness indicated by the ultrasonic test before the application of correction factors.

4.3 Reported thickness (T_r) — indicated thickness corrected for material and temperature variations between the material under test and the calibration block.

4.4 Testing authority — test laboratory or establishments which provide non-destructive testing services.

4.5 Delay block spacer — a block of material used between the test surface and the probe to prevent overheating of the probe and for measuring thin sections.

5 EQUIPMENT.

5.1 General. Ultrasonic instruments for thickness determinations shall use one of the following systems:

- (a) A-scan presentation.
- (b) Digital display.
- (c) Meter display.

5.2 A-scan presentation.

5.2.1 General. Equipment shall be capable of displaying an ultrasonic echo with sufficient definition to permit measurements within ± 1 percent over the test range.