

<sup>Dup.</sup>  
Superseded by AS 2503.2-1996

AS 2503.2—1983  
UDC 666.76:620.1:543

# Australian Standard 2503.2—1983

---

## CHEMICAL ANALYSIS OF REFRATORIES AND REFRACTORY MATERIALS Part 2—ALUMINOSILICATE REFRACTORY MATERIALS

[Title allocated by Defence Cataloguing Authority:  
CHEMICAL ANALYSIS OF REFRATORIES AND REFRACTORY  
MATERIALS, PART 2—ALUMINOSILICATE REFRACTORY MATERIALS]

---



**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA  
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**

*Incorporated by Royal Charter*



This Australian standard, initially prepared under the direction of the Chemical Standards Board, and completed by Committee MN/7, Refractories, under the direction of the Minerals Standards Committee, was approved on behalf of the Council of the Standards Association of Australia on 27 July 1983 and published on 7 October 1983.

---

The following interests are represented on Committee MN/7:

Australasian Institute of Mining and Metallurgy  
Bureau of Steel Manufacturers of Australia  
Cement and Concrete Association of Australia  
Commonwealth Scientific and Industrial Research Organization  
Electricity Supply Association of Australia  
Institute of Australian Foundrymen (N.S.W. Division)  
Institute of British Foundrymen (Australian Branch)  
Refractories Manufacturers' Association of Australia  
University of New South Wales

---

*Review of Australian Standards.* To keep abreast of progress in industry, Australian standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all SAA publications will be found in the Annual List of Australian Standards; this information is supplemented each month by SAA's journal 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn standards.

Suggestions for improvements to Australian standards, addressed to the head office of the Association, are welcomed. Notification of any inaccuracies or ambiguity found in an Australian standard should be made without delay in order that the matter may be investigated and appropriate action taken.

First published (included in AS R28) .....	1965
AS 2503.2, first published .....	1983

© Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1983

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

*This standard was issued in draft form for comment as DR 78028.*

ISBN 0 7262 3115 0

## PREFACE

This standard was prepared by the Association's Committee on Refractories as the second part of a standard being prepared to supersede AS R28—1965. It deals with the chemical analysis of aluminosilicate refractory materials. Separate parts of this standard deal with the analysis of the other refractory materials in the series, as follows:

Part 1 Silica Refractory Materials

Part 3 High Alumina Refractory Materials\*

Part 4 Magnesite and Dolomite Refractory Materials\*

Part 5 Chrome-bearing Refractory Materials\*

Since this standard was circulated in draft form for comment in 1978, a revision of format has been undertaken to bring the details into complete compliance with the requirements of SAA MP34, Guide to the Layout and Preparation of Standard Methods of Chemical Analysis, as well as to incorporate other modifications.

Changes in the standard were motivated by a requirement for the updating of analytical methodology, instrumental techniques having replaced many of the former classical analysis methods.

The committee acknowledges the documented work of ISO/TC 33, Refractories, and the reference standard BS 1902, Methods of Testing Refractory Materials, which were used as source materials in the development of this standard. For selection of the test sample, reference is made to AS 2497, Sampling Procedures for Acceptance Testing of Shaped Refractory Products, which was developed by another subcommittee of the Committee on Refractories.

---

\*In course of preparation.



## CONTENTS

	<i>Page</i>
<b>SECTION 1. SCOPE AND GENERAL</b>	
1.1 Scope	5
1.2 Referenced Documents	5
1.3 Definition	5
1.4 Repeatability	5
1.5 Principle	6
<b>SECTION 2. SAMPLING AND SAMPLE PREPARATION</b>	
2.1 Scope of Section	7
2.2 Gross Sampling	7
2.3 Preparation of Sample	7
<b>SECTION 3. DETERMINATION OF LOSS ON IGNITION</b>	
3.1 Scope of Section	8
3.2 Apparatus	8
3.3 Procedure	8
<b>SECTION 4. DETERMINATION OF SILICON, PHOSPHORUS, ALUMINUM, IRON(III), TITANIUM(IV) AND MANGANESE(II) OXIDES</b>	
4.1 Scope of Section	9
4.2 Reagents	9
4.3 Apparatus	10
4.4 Procedure	11
<b>SECTION 5. DETERMINATION OF CALCIUM, MAGNESIUM, SODIUM, POTASSIUM AND LITHIUM OXIDES</b>	
5.1 Scope of Section	16
5.2 Reagents	16
5.3 Apparatus	16
5.4 Procedure	16
<b>SECTION 6. TEST REPORT</b>	
	17
<b>APPENDIX A. SCHEME OF ANALYSIS FOR ALUMINOSILICATE REFRACTORY MATERIALS</b>	
A1 Ignition Loss; Analysis for $\text{SiO}_2$ , $\text{P}_2\text{O}_5$ , $\text{Al}_2\text{O}_3$ , $\text{Fe}_2\text{O}_3$ , $\text{TiO}_2$ , $\text{MnO}$	18
A2 Analysis for $\text{CaO}$ , $\text{MgO}$ , $\text{Na}_2\text{O}$ , $\text{K}_2\text{O}$ , $\text{Li}_2\text{O}$	20

## STANDARDS ASSOCIATION OF AUSTRALIA

## Australian Standard

## CHEMICAL ANALYSIS OF REFRACTORIES AND REFRACTORY MATERIALS

## PART 2—ALUMINOSILICATE REFRACTORY MATERIALS

## SECTION 1. SCOPE AND GENERAL

**1.1 SCOPE.** This standard sets out methods for the sampling, preparation of sample and analysis of aluminosilicate refractories and refractory materials. Procedures are described for determining—

- the loss on ignition; and
- the chemical composition, viz the amount of silicon, phosphorus, aluminium, iron, titanium, manganese, calcium, magnesium, sodium, potassium and lithium present, expressed as the oxides of these elements.

Table 1.1 illustrates the typical composition of aluminosilicate refractories and the associated form of expression.

**TABLE 1.1**  
**COMPOSITION OF ALUMINOSILICATE REFRACTORY MATERIALS**

Constituent	Expressed as	Range percent
Silicon dioxide	SiO <sub>2</sub>	5 to 93
Aluminium oxide	Al <sub>2</sub> O <sub>3</sub>	5 to 46
Calcium oxide	CaO	0 to 5
Iron(III) oxide	Fe <sub>2</sub> O <sub>3</sub>	0 to 5
Potassium oxide	K <sub>2</sub> O	0 to 5
Titanium(IV) dioxide	TiO <sub>2</sub>	0 to 2
Magnesium oxide	MgO	0 to 1
Phosphorus pentoxide	P <sub>2</sub> O <sub>5</sub>	0 to 1
Manganese(II) oxide	MnO	0 to 0.5
Sodium oxide	Na <sub>2</sub> O	0 to 0.5
Lithium oxide	Li <sub>2</sub> O	0 to 0.5

**1.2 REFERENCED DOCUMENTS.** The following standards are referred to in this standard:

- AS 1152 Test Sieves\*  
 AS 2243 Safety in Laboratories  
 Part 2—Chemical  
 AS 2497 Sampling Procedures for Acceptance Testing of Shaped Refractory Products  
 AS CK19 Code of Recommended Practice for the Chemical Analysis of Materials by Ultraviolet Visible Spectrophotometry

**1.3 DEFINITION.** For the purpose of this standard, the following definition applies:

**Aluminosilicate refractory**—a refractory or refractory material in which the aluminium oxide content is not more than 46 percent (m/m).

**1.4 REPEATABILITY.** Duplicate determinations shall be carried out in all cases. The analyses shall be repeated if the difference between duplicate determinations exceeds the following limits:

- For aluminium oxide or other constituent in the sample exceeding 30 percent (m/m) ..... 0.3 percent max.
- For silicon dioxide or other constituent amounting to between 10 percent and 30 percent (m/m) ..... 0.2 percent max.
- For constituents amounting to between 5 percent and 10 percent (m/m) ..... 0.1 percent max.
- For constituents amounting to less than 5 percent (m/m) ..... 0.05 percent max.

\*In course of revision.