

Australian Standard<sup>®</sup>

---

**Aluminium and aluminium alloys—  
Sampling for chemical and  
spectrochemical analysis**

---

This Australian Standard was prepared by Committee CH/10, Analysis of Metals. It was approved on behalf of the Council of Standards Australia on 4 July 1997 and published on 5 September 1997.

---

The following interests are represented on Committee CH/10:

AMDEL

Australasian Institute of Mining and Metallurgy

Australasian Railway Association

Australian Aluminium Council

Australian Chamber of Commerce and Industry

Australian Chamber of Manufacturers

Bureau of Steel Manufacturers

Copper Technical Data Centre

Metal Trades Industry Association of Australia

National Association of Testing Authorities Australia

The Royal Australian Chemical Institute

University of New South Wales

Additional interests participating in preparation of Standard:

Superintendent Companies and Aluminium Smelters

---

*Review of Australian Standards.* To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

---

Australian Standard<sup>®</sup>

---

**Aluminium and aluminium alloys—  
Sampling for chemical and  
spectrochemical analysis**

---

Originated as AS 2612—1983.  
Second edition 1997.

## PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee CH/10 on the Analysis of Metals to supersede AS 2612—1983.

This Standard is the result of a consensus among representatives of the Joint Committee to produce it as an Australian Standard.

The objective of this Standard is to update procedures in accordance with technological developments for the methods of sampling aluminium and aluminium alloys for chemical and spectrochemical analysis.

Sampling is the major source of variation in the determination of metals content of an alloy or the pure metal. Sampling personnel are required under this Standard to follow prescribed sampling procedures. These procedures may be varied provided that the analytical laboratory has demonstrated that the analyte concentrations determined in the product of the alternative sampling procedure are comparable with that of the bulk.

The Committee recognized that there is considerable variation in the type of moulds available and in current use for the provision of the ideal sample. Though vacuum moulds may provide an improved sample compared with book and centre-pour moulds, they are not widely used in Australia. They have not been included in the scope of this Standard. Book moulds have been omitted due to their lack of use.

Numbers of samples and sampling frequency are also considered outside of the scope of this Standard.

## © Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

## CONTENTS

	<i>Page</i>
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE .....	4
1.2 DEFINITIONS .....	4
1.3 APPARATUS .....	4
SECTION 2 SAMPLING OF MOLTEN METAL	
2.1 GENERAL .....	7
2.2 PREPARATION OF THE MOULD CAVITY .....	7
2.3 SAMPLING PROCEDURE .....	7
2.4 SAMPLE QUALITY .....	8
SECTION 3 SAMPLING OF CAST FORMS AND WROUGHT PRODUCTS	
3.1 GENERAL .....	9
3.2 INGOT SAMPLING BY SAWING .....	9
3.3 INGOT SAMPLING BY DRILLING .....	9
3.4 SAMPLING OF OTHER SHAPES .....	9
SECTION 4 PREPARATION OF THE SAMPLE FOR SPECTROCHEMICAL ANALYSIS	
4.1 GENERAL .....	12
4.2 PROCEDURE .....	12
4.3 ANALYSIS .....	12
4.4 DIRECT EXCITATION OF CAST FORMS OR WROUGHT PRODUCT ...	12
4.5 PREPARATION OF REMELT SAMPLES .....	12
SECTION 5 PREPARATION OF THE SAMPLE FOR CHEMICAL ANALYSIS	
5.1 FROM DISC SAMPLES .....	14
5.2 FROM OTHER PAPERS .....	14

## STANDARDS AUSTRALIA

## Australian Standard

**Aluminium and aluminium alloys—Sampling for  
chemical and spectrochemical analysis**

## SECTION 1 SCOPE AND GENERAL

**1.1 SCOPE** This Standard sets out methods for obtaining a representative sample of aluminium and aluminium alloys and procedures for the preparation of laboratory samples required for the determination of their chemical composition by both chemical and spectrochemical analysis. The procedures are suitable for use in manufacturing control, material and product acceptance, and research and development.

**1.2 DEFINITIONS** For the purpose of this Standard, the definitions here apply.

**1.2.1 Batch**—products of uniform chemical and physical composition derived as one of the following:

- (a) The product from any discrete production period in which casting conditions remained substantially constant.
- (b) A single furnace charge.

**1.2.2 Cast forms**—item of aluminium or aluminium alloy which has not been subject to deformation. Examples include an ingot, a semi-finished product obtained by continuous casting and a shaped casting.

**1.2.3 Chemical method of analysis**—method for the determination of chemical composition in which the sample is subjected to chemical reaction.

**1.2.4 Laboratory sample**—part or all of the preliminary sample brought to a required condition for analysis.

**1.2.5 Preliminary sample**—the sample ladled from the molten metal or that taken from the ingot from which the laboratory sample is prepared which is representative of the batch.

**1.2.6 Spectrochemical method of analysis**—method for the determination of chemical composition in which the determination of composition is carried out without subjecting the sample to chemical reaction, e.g. an atomic emission spectrometric method or an X-ray fluorescence spectrometric method.

**1.2.7 Test portion**—that part of the laboratory sample which is actually analysed.

**1.2.8 Wrought product**—item of aluminium or aluminium alloy which has been subject to deformation by extrusion, rolling, drawing, forging or some other method. Examples include a bar, a billet, a plate, a strip, a tube and a wire.

**1.3 APPARATUS**

**1.3.1 Centre-pour mould**—of steel or cast iron construction. A typical centre-pour mould is shown in Figure 1.

**1.3.2 Ladle**—capable of holding a minimum of 250 g of molten metal.

**1.3.3 Lathe**—capable of machining a consistent, smooth, flat surface and preferably having an automatic cross feed.