

AS 2614

SUPERSEDED BY:

AS 2614-1998

~~REFERENCE COPY
INFORMATION CENTRE
STANDARDS AUSTRALIA~~

AS 2614—1983
UDC 669.3:620.113

Ref. Revision see DR97444

Australian Standard 2614—1983

**COPPER AND COPPER ALLOYS
SAMPLING FOR CHEMICAL
ANALYSIS AND ELECTRICAL
RESISTIVITY**



**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**

Incorporated by Royal Charter



This Australian standard was prepared by Committee CH/10, Analysis of Metals. It was approved on behalf of the Council of the Standards Association of Australia on 27 January 1983 and published on 9 May 1983.

The following interests are represented on Committee CH/10:

- Aluminium Development Council
- Australasian Institute of Mining and Metallurgy
- Australian Lead Development Association
- Australian Mineral Development Laboratories
- Australian Tin Information Centre
- Australian Zinc Development Association
- Bureau of Steel Manufacturers of Australia
- Confederation of Australian Industry
- Copper Producers' Association of Australia
- Department of Defence
- Electricity Supply Association of Australia
- Metal Trades Industry Association of Australia
- National Association of Testing Authorities
- Railways of Australia Committee
- Royal Australian Chemical Institute

To keep abreast of progress in industry, Australian standards are subject to continuous review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that their standards are up-to-date. Full details of all SAA publications will be found in the Annual List of Australian Standards; these details are supplemented by listings in the SAA monthly journal 'The Australian Standard' Information on the Annual List and 'The Australian Standard' may be obtained from any sales office of the Association, where details are also available of the current status of individual standards. Suggestions for improvements to published standards, addressed to the head office of the Association, are welcomed.

First published1983

This standard was issued in draft form for comment as DR 81143 and DR 81334.

PREFACE

This standard was prepared by a subcommittee of the Association's Committee on the Analysis of Metals under the direction of the Chemical Standards Board. The method of taking the sample and preparing it for analysis is an important preliminary to the analytical procedure.

Copper and copper alloys are manufactured in a number of different forms and a different sampling procedure is required for each form. A procedure for the sampling of copper cathode for *impurity* analysis is currently the subject of a great deal of discussion within the international copper industry. Samples taken by the procedures in this standard are not recommended for use for the determination of impurities.

This standard sets out methods for the selection and preparation of samples of copper refinery shapes, and copper and copper alloys that have been cast or reduced to their final form by mechanical working. It comprises two Parts as follows:

Part 1—Sampling of Refined Copper Shapes

Part 2—Sampling of Wrought Copper and Copper Alloys and Cast Copper Alloys for Chemical Analysis.

An appendix sets out the general theory for the sampling of non-ferrous metals. This provides details of the most accurate methods of sampling which, however, may not be practical in all situations.

Other appendices deal with the sampling of molten metal for general control purposes, and suggested procedures for cathode sampling.

© Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1983

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.



CONTENTS

	<i>Page</i>
PART 1—SAMPLING OF REFINED COPPER SHAPES	
1.1 Scope of Part	5
1.2 Referenced Document	5
1.3 Definitions	5
1.4 Selection of Primary Sample	5
1.5 Preparation of Laboratory Samples	5
1.6 Preparation of Test Samples....	6
PART 2—SAMPLING OF WROUGHT COPPER AND COPPER ALLOYS AND CAST COPPER ALLOYS FOR CHEMICAL ANALYSIS	
2.1 Scope of Part	7
2.2 Referenced Documents	7
2.3 Definitions	7
2.4 Primary Sampling Procedures	7
2.5 Laboratory and Test Sampling Procedure	8
APPENDICES	
A Sampling Theory	10
B Sampling Molten Metal for the Chemical Analysis of Copper Shapes	12
C Advice on Cathode Sampling Techniques	13

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

for

**COPPER AND COPPER ALLOYS—SAMPLING FOR CHEMICAL ANALYSIS
AND ELECTRICAL RESISTIVITY****PART 1. SAMPLING OF REFINED COPPER SHAPES**

1.1 SCOPE OF PART. This Part of the standard sets out the method for the selection and preparation of samples of copper refinery shapes to determine compliance with the chemical composition and electrical resistivity requirements of AS 1279. The prescribed refinery shapes are cathodes, horizontally cast wirebars and vertically cast cakes and billets. The cathode sampling method is not recommended for any purpose other than direct determination of copper and determination of electrical resistivity for compliance with AS 1279.

1.2 REFERENCED DOCUMENT. The following standard is referred to in this Part:
AS 1279 Copper Refinery Shapes

1.3 DEFINITIONS. For the purpose of this Part, the following definitions apply:

1.3.1 Lot—for the purpose of sampling, one of the following:

- A discrete quantity of cathodes of generally uniform quality. Normally, the lot is a contract unit or sub-unit.
- The production from any discrete 8 h period for a continuous melting furnace, provided that casting conditions remained substantially constant.
- A single furnace charge for a reverberatory furnace.

NOTES:

- By agreement between supplier and purchaser, the lot may be of some other quantity or form.
- Different shapes, shapes of different sizes, and shapes cast from different furnaces are considered as separate lots.

1.3.2 Primary sample—the total amount of material withdrawn from the cathodes or cast shapes comprising the lot.

1.3.3 Laboratory sample—the part (or parts) of the pieces considered to represent the primary sample.

NOTE: For internal control purposes, and possibly through agreement with consumers, sampling from molten metal may be appropriate. Appendix B contains information on this. Sampling from molten metal is not within the scope of this Part of the standard.

1.3.4 Test sample—a suitable part of the laboratory sample containing the same constituents in the same proportions as they occur in the primary sample, and sufficiently divided to permit laboratory analysis and preparation for resistivity testing, as required.

1.4 SELECTION OF PRIMARY SAMPLE.

1.4.1 Cathodes. Advice on selection of a primary sample for determination of copper content and electrical resistivity is given in Appendix C.

1.4.2 Cast shapes. For cast refinery shapes, the primary sample shall comprise not less than the following:

- One lot of cast refinery shapes from a single furnace charge shall be represented by three sample shapes taken near the beginning, middle and end of the casting period.
- One lot of production from a continuous melting furnace shall be represented by one sample shape for each 2 h of casting, with sampling to be carried out at 2-hourly intervals.

NOTE: Another primary sample may be specified by agreement between supplier and purchaser.

1.5 PREPARATION OF LABORATORY SAMPLES.

1.5.1 Cathodes. Advice is given in Appendix C on methods for the preparation of laboratory samples from cathodes for determination of copper content and electrical resistivity.

1.5.2 Wire Bars. A central cross-sectional piece shall be sawn from the bar. The piece shall be from 10 mm to 50 mm in thickness. Loose dirt shall be buffed from the outer surface.