

Australian Standard™

**Copper and copper alloys—
Sampling for chemical and
spectrochemical analysis,
and physical testing**

This Australian Standard was prepared by Committee CH/10, Analysis of Metals. It was approved on behalf of the Council of Standards Australia on 10 July 1998 and published on 5 September 1998.

The following interests are represented on Committee CH/10:

Australasian Institute of Mining and Metallurgy
Australasian Railway Association
Australian Aluminium Council
Australian Chamber of Manufactures
Copper Technical Data Centre, Australia
National Association of Testing Authorities, Australia
The Royal Australian Chemical Institute
University of New South Wales

Additional interests participating in preparation of Standard:

Superintendent Companies and Aluminium Smelters

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard' which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 97444.

Australian Standard™

**Copper and copper alloys—
Sampling for chemical and
spectrochemical analysis,
and physical testing**

Originated as AS 2614—1983.
Second edition 1998.

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee CH/10, Analysis of Metals to supersede AS 2614—1983, *Copper and copper alloys—Sampling for chemical analysis and electrical resistivity*.

This Standard is the result of a consensus among representatives of the Joint Committee to produce it as an Australian Standard.

The technique used for taking samples is as important as the actual analytical method. Therefore sampling techniques for copper and copper alloys need to be defined in order to ensure that the procedures used in different laboratories analyzing these metals will be as uniform as possible.

Sampling is the major source of variation in the determination of metals content of an alloy or the pure metal. Sampling personnel are required under this Standard to follow prescribed sampling procedures. These procedures may be varied provided that the analytical laboratory has demonstrated that the analyte concentrations determined in the product of the alternative sampling procedure are comparable with that of the bulk.

Number of samples and sampling frequency are also considered outside of the scope of this Standard

The term 'normative' has been used in this Standard to define the application of the appendix to which it applies. A 'normative' appendix is an integral part of a Standard.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE AND GENERAL	4
1.2 DEFINITIONS	4
1.3 APPARATUS	4
SECTION 2 SAMPLING OF MOLTEN METAL	
2.1 GENERAL	11
2.2 PROCEDURE	11
SECTION 3 SAMPLING OF CATHODE, CAST FORMS OR WROUGHT PRODUCT	
3.1 GENERAL	13
3.2 SAMPLING	13
SECTION 4 PREPARATION OF THE SAMPLE FOR SPECTROCHEMICAL ANALYSIS	
4.1 GENERAL	15
4.2 PROCEDURE	15
4.3 ANALYSIS	15
4.4 DIRECT EXCITATION OF CAST FORMS OR WROUGHT PRODUCT ...	15
4.5 PREPARATION OF REMELT SAMPLE	15
SECTION 5 PREPARATION OF THE SAMPLE FOR CHEMICAL AND PHYSICAL TESTING	
5.1 CHEMICAL ANALYSIS	16
5.2 PHYSICAL TESTING	16
APPENDIX A CATHODE SAMPLING	17

STANDARDS AUSTRALIA

Australian Standard

Copper and copper alloys—Sampling for chemical and spectrochemical analysis, and physical testing

SECTION 1 SCOPE AND GENERAL

1.1 SCOPE This Standard sets out methods for obtaining a representative sample of copper and copper alloys and procedures for the preparation of laboratory sample, required for the determination of their chemical composition by both chemical and spectrochemical analysis. The samples are taken either from molten metal, cathode, cast forms or wrought product. This Standard is also suitable for sampling copper and copper alloys for selective physical tests.

1.2 DEFINITIONS For the purpose of this Standard, the definitions below apply.

1.2.1 Batch—products of uniform chemical and physical composition derived as one of the following:

- (a) The product from any discrete production period in which casting conditions remain substantially constant.
- (b) A single furnace charge.
- (c) Part or whole of a cathode shipment.

1.2.2 Cast forms—items of copper or copper alloy which have not been subject to deformation. Examples include ingot, semi-finished product obtained by continuous casting (e.g. billet, slab and cake) and shaped castings.

1.2.3 Chemical method of analysis—method for the determination of chemical composition in which the sample is subjected to chemical reaction.

1.2.4 Laboratory sample—part or all of the preliminary sample brought to a required condition for analysis.

1.2.5 Preliminary sample—the sample ladled from the molten metal or that taken from final products from which the laboratory sample is prepared, which is representative of the batch.

1.2.6 Spectrochemical method of analysis—method for the determination of chemical composition in which the determination of composition is carried out without subjecting the sample to chemical reaction, e.g. an atomic emission spectrometric method or an X-ray fluorescence spectrometric method.

1.2.7 Test portion—that part of the laboratory sample which is actually analysed.

1.2.8 Wrought product—items of copper or copper alloy which have been subject to deformation by rolling, drawing, forging or some other method. Examples include bar, billet, plate, strip, rod, tube and wire.

1.3 APPARATUS

1.3.1 Moulds—of steel or cast iron construction. A number of mould shapes are used in the industry comprising book moulds, centre-pour moulds, chill moulds, dip moulds and moulds unique to a specific manufacturer. The final mould shape is dependent upon the