

Under Revision See D295790
superseded by AS 2666-1996

AS 2666—1983
UDC 665.93:676.811.3

check if you
really need this

Australian Standard 2666—1983

PRESSURE SENSITIVE ADHESIVE LABEL STOCK— PAPER



STANDARDS ASSOCIATION OF AUSTRALIA
Incorporated by Royal Charter



This Australian standard was prepared by Committee MS/44, Pressure Sensitive Labels. It was approved on behalf of the Council of the Standards Association of Australia on 27 September 1983 and published on 4 November 1983.

The following interests are represented on Committee MS/44:

Australian Retailers Association
Confederation of Australian Industry
Department of Defence
Packaging Council of Australia
Plastics Institute of Australia Incorporated
Printing and Allied Trades Employers Federation of Australia
Railways of Australia Committee
Roll Label Ticket and Tag Manufacturers Association of N.S.W.
Screen Printers Association of Australia

Review of Australian Standards. To keep abreast of progress in industry, Australian standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of SAA publications will be found in the Annual List of Australian Standards; this information is supplemented each month by SAA's journal 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn standards.

Suggestions for improvements to Australian standards, addressed to the head office of the Association, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This standard was issued in draft form for comment as DR 82220.

AUSTRALIAN STANDARD

**PRESSURE SENSITIVE
ADHESIVE LABEL STOCK—
PAPER**

AS 1656—1983

First published1983

**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**

ISBN 0 7262 3204 1



NOV 1983

PREFACE

This standard was prepared by the Association's Committee on Pressure Sensitive Labels at the request of the Department of Defence which, in the first instance, required standards for all types of label stock as a basis for standards for pressure sensitive labels to be converted from this stock.

This standard is one of a series of standards to be prepared for both the label stock with backing of paper, plastics, laminated foil, metal or textile and a wide variety of labels converted from this stock.

©Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1983

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

CONTENTS

	<i>Page</i>
SECTION 1. SCOPE AND GENERAL REQUIREMENTS	
1.1 Scope	4
1.2 Referenced Documents.....	4
1.3 Classification	4
1.4 Materials and Construction	4
1.5 Die Cutting Properties	4
1.6 Packaging and Marking	4
SECTION 2. PERFORMANCE REQUIREMENTS	
2.1 General Surface Properties	6
2.2 Colour	6
2.3 Gloss	6
2.4 Opacity	6
2.5 Tensile Strength	6
2.6 Migration	6
2.7 Colourfastness to Artificial Light	6
2.8 Adhesion	6
2.9 Initial Tack	6
2.10 Resistance to Shear (Holding Power)	6
2.11 Accelerated Ageing	6
2.12 Lay-flat Properties	6
2.13 Release (For Backing)	6
2.14 Release (For Backing) at Specified Speed	6
2.15 Translucency of Release Backing	6
APPENDICES	
A Purchasing Guidelines	7
B Method for Determining Mass Per Unit Area of Release Backing	9
C Method for Determining Thickness of Release Backing	10
D Method for Determining Capacity of Label Stock	11
E Method for Determining Tensile Strength of Label Stock	12
F Method for Determining Migration Characteristics in Label Stock	13
G Method for Determining Adhesion of Label Stock	14
H Method for Determining Initial Tack of Label Stock	15
J Method for Determining Resistance to Shear (Holding Power) of Label Stock	16
K Method for Determining Release Value for Backing	17
L Method for Determining Translucency of Release Backing—Visual Method	18
M Method for Determining Translucency of Release Backing—Instrumental Method	20

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard
for
PRESSURE SENSITIVE ADHESIVE LABEL STOCK—PAPER

SECTION 1. SCOPE AND GENERAL REQUIREMENTS

1.1 SCOPE. This standard specifies requirements for general purpose, pressure sensitive adhesive (PSA) paper label stock.

Label stock is intended for conversion to many types of paper labels for use on a variety of clean, smooth, flat or moderately curved surfaces at temperate conditions.

NOTE: Purchasing guidelines are provided in Appendix A.

1.2 REFERENCED DOCUMENTS. The following standards are referred to in this standard:

- AS 1301 Methods of Test for Pulp and Paper
Method P426s Thickness of Single Sheets of Paper, Paperboard and Corrugated Fibreboard
- AS 1580 Methods of Test for Paints and Related Materials
Method 213.2 Dry Hiding Power—Contrast Ratio
Method 601.1 Colour—Visual Comparison
Method 601.2 Colour — Instrumental Measurement of Colour Difference Using the 'Colormaster' Differential Colorimeter
Method 601.3 Colour — Instrumental Measurement of Colour Difference Using the Colour Eye
Method 602.1 Visual Assessment of Gloss
Method 602.2 Specular Gloss
Method 602.3 Visual Assessment of Gloss (Bollman)
- AS 1635 Methods of Test for Pressure Sensitive Adhesive Tapes
Method 3.1 Adhesion Strength
- AS 2001 Methods of Test for Textiles
2001.1.21 Colourfastness Tests—
Method 21 Determination of Colourfastness to Light Using an Artificial Light Source (Mercury Vapour-Tungsten Filament-Internally Phosphor-coated Lamp)
- AS 1993 Methods for Calibration and Grading of Force-measuring Systems of Testing Machines.

1.3 CLASSIFICATION. Label stock shall be one of two classes, viz—

- Class I Permanent
Class II Removable

The class shall be as specified by the purchaser (see Appendix A, Paragraph A3(c)).

1.4 MATERIALS AND CONSTRUCTION

1.4.1 General. Label stock shall consist of paper with a backing coat of adhesive and a protective release backing which shall be readily and completely removable.

1.4.2 Paper. The paper shall be of wood-free quality and the thickness, when measured in accordance with AS 1301, P426s shall be uniform within a tolerance of $\pm 5 \mu$.

1.4.3 Release backing

1.4.3.1 Mass per unit area. When release backing is tested in accordance with Appendix B, the mass per unit area shall be as specified by the purchaser (see Appendix A, Paragraph A3(d)).

1.4.3.2 Thickness. When release backing is tested in accordance with Appendix C, the thickness shall be as specified by the purchaser (see Appendix A, Paragraph A3(d)).

The thickness of test specimens taken from any area of the web shall not vary by more than ± 5 percent of their average.

1.4.4 Form. Label stock may be in sheet form or roll form wound on a core, as specified by the purchaser (see Appendix A, Paragraph A3(e)).

The core shall have sufficient rigidity to resist distortion and wear under normal conditions of transportation and use.

Roll label stock may be slit as specified by the purchaser (see Appendix A, Paragraph A3(f)).

The number of splices shall not exceed 2 per 500 m or 3 per 1000 m of roll stock.

1.4.5 Dimensions and tolerances. The dimensions and tolerances for label stock shall be as specified by the purchaser (see Appendix A, Paragraph A3(g)).

The internal diameter of the core shall be $76.0 + 1.0, -0$ mm.

1.5 DIE CUTTING PROPERTIES. Label stock shall be capable of being readily, cleanly and completely die cut.

1.6 PACKAGING AND MARKING.

1.6.1 Packaging. Label stock shall be packed so that it is adequately protected from damage in transportation and from deterioration due to climatic conditions. Rolls shall be protected so that they will not adhere to each other or to the primary pack.