

Dup.

Under Revision

WITHDRAWN: 19971105

See SA 95012

~~LOAN COPY~~
INFORMATION CENTRE
STANDARDS AUSTRALIA

SUPERSEDED BY:

AS/NZS 3750.13:1997

AS 2674—1983
UDC 667.638.2.'37.25.'36.211

Australian Standard 2674—1983

PAINTS FOR STEEL STRUCTURES—EPOXY PRIMER (TWO-PACK)



STANDARDS ASSOCIATION OF AUSTRALIA
Incorporated by Royal Charter



This Australian standard was prepared by Committee CH/3, Paints and Related Materials. It was approved on behalf of the Council of the Standards Association of Australia on 11 October 1983 and published on 2 December 1983.

The following interests are represented on Committee CH/3:

Australasian Corrosion Association
Australasian Zinc Development Association
Australian Paint Manufacturers Federation
Australian Retailers Association
Confederation of Australian Industry
Department of Defence
Government Paint Committee
National Association of Australian State Road Authorities
National Association of Testing Authorities, Australia
Oil and Colour Chemists Association, Australia
Railways of Australia Committee
Royal Australian Institute of Architects

Review of Australian Standards. To keep abreast of progress in industry, Australian standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all SAA publications will be found in the Annual List of Australian Standards; this information is supplemented each month by SAA's journal 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn standards.

Suggestions for improvements to Australian standards, addressed to the head office of the Association, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This standard was issued in draft form for comment as DR 81320.

AUSTRALIAN STANDARD

**PAINTS FOR STEEL
STRUCTURES—EPOXY PRIMER
(TWO-PACK)**

AS 2674—1983

First published1983

**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**

ISBN 0 7262 3231 9



PREFACE

This standard was prepared by the Association's Committee on Paints and Related Materials, under the direction of the Chemical Standards Board. It is one of a series of product standards for the paints cross-referred to in AS 2312, Guide to the Protection of Iron and Steel against Exterior Atmospheric Corrosion.

Matters considered to be contractual in nature, i.e. subject to agreement, are not covered by the body of the standard but are referred to in Appendix A.

The standard relies essentially on product performance with specified properties for compliance; however, some compositional requirements are included.

CONTENTS

SECTION 1. SCOPE AND GENERAL		
1.1	Scope	3
1.2	Uses	3
1.3	Referenced Documents	3
1.4	Definitions	3
1.5	Safety Precautions	3
SECTION 2. MATERIAL REQUIREMENTS AND PROPERTIES		
2.1	Composition	4
2.2	Properties	4
SECTION 3. PACKAGING AND LABELLING		
3.1	Packaging	6
3.2	Labelling	6
APPENDICES		
A	Purchasing Guidelines	7
B	Guidance on the Use and Application of Epoxy Primer	8
C	Preparation of Test Panels	10
D	Notes on Paint Testing	11
ANNEX. LIST OF REFERENCED DOCUMENTS		12

© Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1983

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

for

PAINTS FOR STEEL STRUCTURES—EPOXY PRIMER (TWO-PACK)

SECTION 1. SCOPE AND GENERAL

1.1 SCOPE. This standard specifies requirements for a two-component epoxy priming paint, intended to be used for the protection of iron and steel against exterior atmospheric corrosion. The paint is suitable for application by spraying (conventional air or airless). It may also be applied by roller or, for small areas, by brush.

NOTES:

1. Information required to be supplied with the purchase order is set out in Appendix A.
2. This standard does not deal with two-pack epoxy primers for steel pigmented with zinc dust. These are covered by AS 2204.

1.2 USES. Paint complying with this standard is intended to be used as a primer in paint systems for the protection of iron and steel against corrosion involving wet and damp areas, high humidity, coastal/marine and industrial fall out.

This paint complies with the provisions of Paint Reference No 6 and may be used with the appropriate intermediate and top coats in systems MP6-E and MP6-F of AS 2312.

NOTE: Additional information on the use and application of epoxy primer is given in Appendix B.

1.3 REFERENCED DOCUMENTS. A list with titles of the standards referred to in this standard is given in the Annex.

1.4 DEFINITIONS. For the purpose of this standard, the definitions given in AS 1310 and the following apply:

1.4.1 Component—the term used to describe each of two parts of the paint which, when mixed together, form a pigmented epoxy primer.

1.4.2 Paint—the mixture of the two components in the proportions recommended by the manufacturer.

1.5 SAFETY PRECAUTIONS. Epoxy paints contain epoxy resin and organic amines in chemical combinations. During mixing and application, protective clothing such as overalls and gloves should be worn to minimize skin contact (see Appendix B).