

Australian Standard[®]

**FIBRE REINFORCED PLASTICS
(FRP) ALUMINIUM ALLOY GAS
CYLINDERS—HOOP
OVERWRAPPED**

[Title allocated by Defence Cataloguing Authority:
CYLINDERS, COMPRESSED GAS (FRP, Aluminium..NSC 8120)]

This Australian standard was prepared by Committee ME/2, Gas Cylinders. It was approved on behalf of the Council of the Standards Association of Australia on 25 October 1984 and published on 31 January 1985.

The following interests are represented on Committee ME/2:

Aluminium Development Council
Australasian Steamship Owners Federation
Australian Chamber of Commerce
Australian Liquefied Petroleum Gas Association Ltd.
Australian Underwater Federation
Board of Fire Commissioners, N.S.W.
Bureau of Steel Manufacturers of Australia
Confederation of Australian Industry
Department of Defence
Department of Employment and Industrial Affairs, N.T.
Department of Industrial Affairs, W.A.
Department of Industrial Relations, N.S.W.
Department of Labour and Industry, T.S.
Department of Labour and Industry, V.
Department of Labour, S.A.
Department of Mines and Energy, N.T.
Department of Mines, Qld.
Department of Territories and Local Government
Railways of Australia Committee

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This standard was issued in draft form for comment as DR 82003.

Australian Standard[®]

**FIBRE REINFORCED PLASTICS
(FRP) ALUMINIUM ALLOY GAS
CYLINDERS—GOP
OVERWRAPPED**

First published 1985

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 3615 2

PREFACE

This standard was prepared by the Association's Committee on Gas Cylinders. It is based on a submission from the Commonwealth Industrial Gases Limited and provides for very specialized processes.

FRP aluminium alloy gas cylinders offer higher stored capacity to mass ratios than available with conventionally manufactured cylinders, and are expected to have application in portable breathing apparatus and where mass is critical. The technology was developed for the United States space program.

The standard provides for hoop overwrapped construction only, and not for totally overwrapped construction.

This standard specifies a bonfire test to establish the performance of the complete cylinder system. Performance in this test depends on the valve and safety relief device (if fitted) as well as the cylinder and the cylinder lading. It is therefore necessary for the purchaser to specify any required departures from the method given in this standard.

This standard specifies a maximum stretch under the hydrostatic test stretch and a permanent volume increase related to total volume increase at test pressure. This is the departure from the usual Australian practice of relating permanent volume increase to original internal volume and will require measurement of total volume increase in accordance with AS 2337, Gas Cylinder Test Stations.

CONTENTS

	<i>Page</i>
SPECIFICATION	
1 Scope	3
2 Referenced Documents	3
3 Definitions	3
4 Overwrap Materials	3
5 Design of Liner	3
6 Design of Overwrapped Cylinder	4
7 Manufacture	4
8 Examination	5
9 Tests	5
10 Records and Certificates	6
11 Marking	7
12 Preparation for Examination	7
APPENDICES	
A Suggested Minimum Information to be Supplied by the Purchaser	8
B Typical Properties for Type E and Type S2 Fibreglass	9
C Suggested Form for Stress Analysis Results	10
D Selection and Number of Cylinders for Examination and Testing	11
E Minimum Information and Suggested Form of Manufacturer's Certificate	12

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

for

FIBREGLASS REINFORCED PLASTICS (FRP) ALUMINIUM ALLOY
GAS CYLINDERS—HOOP OVERWRAPPED

1 SCOPE. This standard specifies requirements for the materials, design, manufacture, inspection, pressure tests and markings of aluminium alloy gas cylinders reinforced by hoop overwrapping with fibre reinforced plastics (FRP), intended for storage and transport of compressed gases, and of water capacity exceeding 0.10 kg but not exceeding 130 kg.

NOTES:

- Appendix A lists the suggested minimum information that should be supplied by the purchaser when ordering gas cylinders covered by this standard.
- Appendix E provides a suggested format for a certificate for recording of data that is to be given to the purchaser.

2 REFERENCED DOCUMENTS. The following documents are referred to in this standard:

AS 1544	Methods for Impact Tests on Metals Part 3—Charpy U-notch and Key-hole Notch	
AS 1777	Aluminium Cylinders for Compressed Gases—Seamless—0.1 kg to 130 kg	
AS 2030.1	SAA Gas Cylinders Code Part 1—Cylinders for Compressed Gases Other than Acetylene	
AS 2337	Gas Cylinder Test Stations	
AS 2473	Valves for Compressed Gas Cylinders (Threaded Outlet)	
ANSI B1.20.3	Dryseal Pipe Threads (Inch)	
ANSI B1.20.4	Dryseal Pipe Threads (Metric)	
ANSI B1.20.5	Gauging for Dryseal Pipe Threads (Inch)	
ANSI B57.1 CGA V-1 CSA B96	Compressed Gas Cylinder Valve Outlet and Inlet Connections	
ASTM D 2343		Test Method for Tensile Properties of Glass Fiber Strands, Yarns and Roving used in Reinforced Plastics
ASTM D 2344		Test Method for Apparent Inter-laminar Shear Strength of Parallel Fiber Composites by Short-beam Method
DIN 4761	Gas Cylinder Valves	
MIL-STD-60346B April 1975	Military Specifications, Roving, Glass, Fibrous (For Filament Winding Applications).	

DEFINITIONS. For the purpose of this standard, the definitions given in AS 2030.1 and the following apply:

3.1 Inspector—a person, acceptable to the Inspecting Authority, who ensures and certifies that all the inspections specified herein have been carried out and that the cylinders comply with all the requirements of the standard.

3.2 Autofrettage pressure—the pressure within the overwrapped cylinder at which the required distribution of stresses between the liner and the overwrap is established.

3.3 Liner—the seamless aluminium alloy gas cylinder to which the overwrap is applied.

3.4 Overwrap—the reinforcement of filament and resin system applied over the liner.

3.5 Hoop wrap—winding of filament in a substantially circumferential pattern over the cylindrical portion of the liner so that the filament does not transmit any significant stresses in a direction parallel to the cylinder longitudinal axis.

4 OVERWRAP MATERIALS.

4.1 Filament. The filament shall be glass fibre filament commercially known as Type S2 or Type E Fibreglass, or any other fibre, as approved by the relevant Inspecting Authority.

NOTE: Typical properties for Type S2 and Type E fibreglass are given in Appendix B.

When determined in accordance with ASTM D 2343, the filament tensile strength shall be not less than—

- for Type S2 Fibreglass 2760 MPa; or
- for Type E Fibreglass 1380 MPa.

4.2 Resin. The resin shall be epoxy with amide or anhydride curing agent, or any material otherwise approved by the relevant Inspecting Authority. The resin shall be translucent to facilitate inspection.

4.3 Fibre reinforced plastics specimen. When determined in accordance with ASTM D 2344, the shear strength of a test specimen constructed of the filament and resin specified in Clauses 4.1 and 4.2 shall be not less than 35 MPa.

5 DESIGN OF LINER. The design of the liner shall be in accordance with AS 1777, with the following additional requirements:

- The design test pressure of the liner shall be not less than 50 percent of the design test pressure of the overwrapped cylinder.
- The liner design burst pressure shall be not less than 80 percent of the design test pressure of the overwrapped cylinder.
- The design of the liner shall ensure that the overwrapped cylinder complies with Clause 9.4.2.
- The design of the liner shall ensure that the liner, after autofrettage, will not buckle owing to compressive forces induced by the overwrap when the internal and external pressures are equalized at atmospheric pressure.
- The design of the liner ends shall ensure that the stress intensity (Von Mises) in the liner ends is less than the stress intensity in the liner cylindrical portion, at the design test pressure.