

Australian Standard™

Coal petrography

**Part 1: Preparation of coal samples
for incident light microscopy**



S t a n d a r d s Australia

This Australian Standard was prepared by Committee MN/1, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 15 February 2000 and published on 13 April 2000.

The following interests are represented on Committee MN/1:

Australasian Institute of Mining and Metallurgy

Australian Coal Association

Australian Coal Preparation Society

Australian Institute of Energy

Bureau of Steel Manufacturers of Australia

Coalfield Geology Council of N.S.W.

CSIRO, Division of Energy Technology

Department of Mines & Energy, Qld

Electricity Supply Association of Australia

Institution of Engineers, Australia

Minerals Council of Australia

University of Newcastle

University of New South Wales

University of Queensland

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using the current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for the improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, PO Box 1055, Strathfield, NSW 2135.

Australian Standard™

Coal petrography

**Part 1: Preparation of coal samples
for incident light microscopy**

Originated as AS 2061—1977.
Second edition 1989.
Revised and redesignated as AS 2856.1—2000.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
PO Box 1055, Strathfield, NSW 2135, Australia

ISBN 0 7337 3310 7

PREFACE

This Standard was prepared by the Standards Australia Committee MN/1, Coal and Coke to supersede AS 2061—1989, *Preparation of coal samples for incident light microscopy*. It is one of a suite of Standards which applies specifically to coal petrography.

The other Standards in this suite are:

AS

2856 Coal petrography

2856.2 Part 2: Maceral analysis

2856.3 Part 3: Methods for microscopical determination of the reflectance of coal macerals

CONTENTS

	<i>Page</i>
1 SCOPE.....	3
2 REFERENCED DOCUMENTS.....	3
3 PRINCIPLE	3
4 MATERIALS.....	3
5 APPARATUS	4
6 SAMPLING.....	5
7 PREPARATION OF GRAIN MOUNT.....	5
8 SURFACE PREPARATION.....	6
9 SAMPLE STORAGE.....	6

STANDARDS AUSTRALIA

Australian Standard Coal petrography

Part 1: Preparation of coal samples for incident light microscopy

1 SCOPE

This Standard describes recommended procedures for the preparation of polished coal samples. The procedures are suitable for all ranks of coal. The resulting polished samples are adequate for characterization of coals using various methods of incident light microscopy.

Coal samples prepared according to the procedures recommended in this Standard may be used for maceral or microlithotype analysis, for measuring maceral reflectance, or for fluorescence analysis.

The data obtained from such testing can be used to determine coal rank and coal composition, to correlate seams, and to provide information on the utilization characteristics of coal.

2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:
AS

- | | |
|--------|--|
| 1152 | Specification for test sieves |
| 4264 | Coal and coke—Sampling |
| 4264.1 | Part 1: Higher rank coal—Sampling procedures |

3 PRINCIPLE

A sample is crushed and sieved, the appropriate sieve aperture varies with the type of material being studied. A representative portion of the sized material is then split off, mixed with a binding agent, poured into moulds and formed into grain mounts. The grain mounts are ground to expose an adequate number of sample grains and, also, to form a very flat surface. This surface is then finely polished so that it is virtually free from scratches and suitable for analysis.

Lump sections may be mounted and polished using similar techniques.

4 MATERIALS

4.1 Binding material

Any suitable binder may be used. A suitable binder should have the following attributes:

- If a liquid, it should be fluid enough to impregnate the coal and to allow air bubbles to escape during mixing. When set, it should securely hold the coal grains during grinding and polishing and should be capable of being ground flat and substantially scratch-free as a result of the grinding and polishing procedure.
- It should not react with coal, minerals or immersion oil.
- Cold-setting binders are preferred, but if a thermo-setting binder is used it should be sufficiently fluid to impregnate the coal at a temperature not exceeding 80°C.