

Australian Standard[®]

**CARBON-MANGANESE STEEL
CYLINDERS FOR COMPRESSED
GASES—
SEAMLESS—
0.1 kg to 500 kg**

[Title allocated by Defence Cataloguing Authority:
CYLINDER, COMPRESSED GAS (Carbon-Manganese
Steel) (NSC 8120)]

This Australian standard was prepared by Committee ME/2, Gas Cylinders. It was approved on behalf of the Council of the Standards Association of Australia on 28 February 1986 and published on 2 June 1986.

The following interests are represented on Committee ME/2:

Aluminium Development Council
Australasian Steamship Owners Federation
Australian Chamber of Commerce
Australian Liquefied Petroleum Gas Association Ltd.
Australian Underwater Federation
Australian Welding Institute
Board of Fire Commissioners, N.S.W.
Bureau of Steel Manufacturers of Australia
Confederation of Australian Industry
Department of Defence
Department of Employment and Industrial Affairs, Qld
Department of Employment and Industrial Affairs, N.C.
Department of Industrial Relations, N.S.W.
Department of Labour, S.A.
Department of Labour and Industry, Tas.
Department of Mines, Qld
Department of Mines and Energy, N.T.
Department of Occupational Health, Safety and Welfare, W.A.
Department of Territories
Fire Protection Industry Association of Australia Ltd
Insurance Council of Australia Ltd
Railways of Australia Committee

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

Australian Standard[®]

**CARBON-MANGANESE STEEL
CYLINDERS FOR COMPRESSED
GASES—
SEAMLESS—
0.1 kg to 500 kg**

First published (as AS B110, and AS B111) 1952
AS 2873 first published 1986

Incorporating:
Amdt 1—1987

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 4186 5

PREFACE

This standard was prepared by the Association's Committee on Gas Cylinders. It supersedes AS B110—1952, Manganese Steel Cylinders for the Storage and Transport of Permanent Gases and AS B111—1952, Manganese Steel Cylinders for the Storage and Transport of High Pressure Liquefiable Gases.

Changes introduced in this standard include the following:

- (a) Requirements are now expressed in SI units.
- (b) Hydrostatic and pulsation type tests are included.
- (c) The impact test has been omitted as it was considered to be not relevant for the thicknesses involved and the conditions of use in Australia.
- (d) The maximum permissible stress value at the hydrostatic test pressure, for calculation purposes, is 343 MPa. This value equals that specified in AS B111. There was a difference of 0.3 percent between the values specified in AS B110 and AS B111, but no justification is seen for maintaining this difference as the steel, test pressure, and safety relief device provisions are identical.

The hydrostatic and pulsation type tests may be waived where the design is that already used for a cylinder accepted as complying with AS B110 or AS B111, and proved to be suitable by experience under Australian service conditions.

The term 'new design' is not yet defined, but the following features are considered to be relevant and may be adopted for such a definition by the Inspection Authorities:

- (i) Manufacture in a different factory.
- (ii) Manufacture by a different process.
- (iii) Manufacture from steel of different nominal chemical compositions.
- (iv) A different heat treatment.
- (v) A base profile or base thickness change relative to the cylinder diameter and calculated minimum wall thickness.
- (vi) A length increase of the cylinder of more than 50 percent (cylinders with an L/D ratio less than 3 must not be used as reference cylinders for any new design with an L/D ratio greater than 3).
- (vii) A diameter change of more than 5 percent.
- (viii) An increase in hydraulic test pressure that requires a change in design wall thickness.

Notwithstanding (viii) above, it is considered that where a gas cylinder is to be used in a lower pressure duty than that for which design approval has been given, it is not to be deemed as being of new design.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
1 SCOPE	4
2 REFERENCED DOCUMENTS	4
3 DEFINITIONS	4
4 STEEL	4
5 DESIGN	4
6 MANUFACTURE	5
7 HEAT TREATMENT	5
8 TESTING	5
9 RECORD AND TEST CERTIFICATE(S)	6
10 MARKING	6
11 PREPARATION FOR DESPATCH	6
 APPENDICES	
A SUGGESTED MINIMUM INFORMATION TO BE SUPPLIED BY THE PURCHASER	7
B DESIGN AND BATCH TESTS SPECIFIED IN THIS STANDARD	8
C TENSILE TEST PIECE	10
D METHODS FOR DERIVING THE PERCENTAGE INCREASE OF WATER CAPACITY AFTER HYDROSTATIC TYPE TEST RUPTURE	11
E SUGGESTED FORM OF MANUFACTURER'S CERTIFICATE	13

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

for

CARBON-MANGANESE STEEL CYLINDERS FOR COMPRESSED GASES—
SEAMLESS—0.1 kg to 500 kg

1 SCOPE. This standard specifies requirements for the steel, design, manufacture, testing, and marking of seamless gas cylinders manufactured from carbon-manganese steel and intended to contain compressed gases, of water capacity not less than 0.1 kg and not greater than 500 kg.

NOTE: Appendix A lists the suggested minimum information that should be supplied by the purchaser when ordering gas cylinders covered by this standard.

2 REFERENCED DOCUMENTS. The following standards are referred to in this standard:

AS 1050	Methods for the Analysis of Iron and Steel
AS 1213	Iron and Steel—Methods of Sampling
AS 1391	Methods for Tensile Testing of Metals
AS 2030.1	SAA Gas Cylinders Code, Part 1—Cylinders for Compressed Gases Other than Acetylene
AS 2337	Gas Cylinder Test Stations
AS 2505.1	Methods for Bend and Related Testing of Metals, Part 1—Sheet, Strip and Plate
AS K1	Methods for the Sampling and Analysis of Iron and Steel
BS 5045	Transportable Gas Containers Part 1—Seamless Steel Containers
ISO 2566/1	Steel—Conversion of Elongation Values, Part 1—Carbon and Low Alloy Steels

3 DEFINITIONS. For the purpose of this standard, the definitions given in AS 2030.1 and the following definition apply:

Inspector—a person, acceptable to the Inspecting Authority, who ensures and certifies that all the inspections specified herein have been carried out and that the cylinders comply with all the requirements of this standard.

4 STEEL.

4.1 Steelmaking process. The steel shall be made by the open hearth, basic oxygen, or an electric furnace process. The steelmaker should supply to the cylinder manufacturer a certificate showing the process of steel manufacture.

NOTES:

- The basic oxygen process means the process of making steel in a basic converter blown with commercially pure oxygen.
- Additional refining by vacuum-arc-remelt (VAR), electroslag-refining (ESR) or vacuum degassing is permitted.

4.2 Chemical analysis. A chemical analysis of the steel from each ladle shall be made to determine the proportions of the specified elements. The method of sampling shall be in accordance with AS 1213, and the

analysis procedures shall be not less accurate than the procedures specified in AS 1050 and AS K1, as appropriate.

The chemical analysis of the steel shall comply with Table 1, and the steelmaker should supply to the cylinder manufacturer a certificate showing the chemical analysis of elements listed in Table 1.

TABLE 1
CHEMICAL ANALYSIS

Element	Analysis, percent	
	Min.	Max.
Carbon	—	0.40
Manganese	0.30	1.75
Silicon	—	0.30
Sulphur	—	0.050
Phosphorus	—	0.050

4.3 Identification. Steel sections shall be individually identified for record purposes.

4.4 Steelmaker's inspection facilities. Facilities for inspection of the steel at the steelmaker's works shall be afforded to the representative of the cylinder manufacturer.

5 DESIGN.

5.1 Minimum thickness. The minimum thickness of steel shall be not less than the greater of those calculated from the following equations:

$$t = 2.5 \left(\frac{D_i}{T} \right)^{1/2} \quad \text{and} \quad t = \frac{P D_h}{2f + P_h}$$

where

t = minimum finished thickness of the steel, in millimetres

D = external diameter of cylinder, in millimetres

D_i = nominal internal diameter of cylinder, in millimetres

P_h = test pressure (see AS 2030.1), in megapascals

f = maximum permissible stress in steel at the hydrostatic test pressure, in megapascals. For calculation purposes, this is to be taken as 343 MPa

T = specified minimum tensile strength of the steel, in megapascals.

NOTE: T refers to minimum tensile strength verified by tests in Clause 8, i.e. following heat treatment.

5.2 Valve protection and neck thread. Valve openings shall incorporate valve protection where required by AS 2030.1, and in accordance with AS 2030.1.