

Australian Standard™

Alumina

**Part 2: Determination of particles
passing a 20 µm aperture sieve**

This Australian Standard was prepared by Committee. MN-009, Alumina and Materials used in Aluminium Production. It was approved on behalf of the Council of Standards Australia on 11 November 2003 and published on 29 December 2003.

The following are represented on Committee MN-009:

Australasian Institute of Mining and Metallurgy

Australian Aluminium Council

Minerals Council of Australia

The Royal Australian Chemical Institute

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

Australian Standard™

Alumina

**Part 2: Determination of particles
passing a 20 µm aperture sieve**

Revised and reissued as AS 2879.2—1991.
Second edition 2003.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 5640 9

PREFACE

This Standard was prepared by the Standards Australia Committee MN-009, Alumina and Materials used in Aluminium Production, as one of a series of Standards for the testing of alumina. This Standard supersedes AS 2879.2—1991.

The objective of this Standard is to provide a standardized method for determining the quantity of particles in a sample of alumina that passes through a 20 μm sieve.

The terms 'normative' and 'informative' have been used in this Standard to define the application of the appendix to which they apply. A 'normative' appendix is an integral part of a Standard, whereas an 'informative' appendix is only for information and guidance.

Currently in preview, click buy full version.

CONTENTS

	<i>Page</i>
1 SCOPE	4
2 REFERENCED DOCUMENTS	4
3 PRINCIPLE	4
4 SAFETY	4
5 REAGENTS	4
6 APPARATUS	5
7 SAMPLING AND SAMPLE PREPARATION	5
8 PROCEDURE	6
9 CALCULATION AND EXPRESSION OF RESULTS	8
10 PRECISION	8
11 QUALITY CONTROL	8
12 TEST REPORT	9

APPENDICES

A RESULTS OF TEST PROGRAMME	10
B DETERMINATION OF EFFECTIVE APERTURE OF THE TEST SIEVE	11

STANDARDS AUSTRALIA

Australian Standard
Alumina**Part 2: Determination of particles passing a 20 µm aperture sieve****1 SCOPE**

This Standard sets out a wet-sieving procedure for the determination of the percentage by mass of particles of smelter-grade alumina passing a 20 µm aperture sieve.

This procedure is applicable for aluminas with a $-20\ \mu\text{m}$ content up to 4%.

2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

2243 Safety in laboratories (series)

2850 Chemical analysis—Interlaboratory test programs—for determining precision of analytical method(s)—Guide to the planning and conduct

2879 Alumina

2879.1 Part 1: Determination of loss of mass at 500°C and 1000°C

4538 Guide to the sampling of alumina

4538.2 Part 2: Preparation of samples

ISO

3310 Test sieves—Technical requirements and testing

3310-3 Part 3: Test sieves of electroformed sheets

3 PRINCIPLE

A test sample of alumina is sieved on a 20 µm electroformed sieve, using acetone, and the retained material is determined gravimetrically after drying at 300°C.

4 SAFETY

For information on laboratory safety, reference should be made to the relevant parts of AS 2243.

Chemicals used may be hazardous or toxic and reference should be made to the appropriate Material Safety Data Sheets.

CAUTION: ACETONE PRESENTS A FLAMMABILITY RISK AND SHOULD BE USED IN A SUITABLE EXTRACTION HOOD.

5 REAGENTS**5.1 A.R. grade acetone****5.2 Desiccant**

Phosphorous pentoxide, activated alumina and molecular sieves have been found to be suitable. Silica gel is not a suitable desiccant.