

Australian Standard™

Alumina

**Part 4: Determination of specific
surface area by nitrogen adsorption**

This Australian Standard was prepared by Committee MN-009, Alumina and Materials used in Aluminium Production. It was approved on behalf of the Council of Standards Australia on 14 March 2003 and published on 25 March 2003.

The following are represented on Committee MN-009:

Australasian Institute of Mining and Metallurgy

Australian Aluminium Council

Minerals Council of Australia

The Royal Australian Chemical Institute

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

Australian Standard™

Alumina

**Part 4: Determination of specific
surface area by nitrogen adsorption**

Originated as AS 2879.4—1991.
Second edition 2003.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 5140 7

PREFACE

This Standard was prepared by the Standards Australia Committee MN-009, Alumina and Materials used in Aluminium Production, to supersede AS 2879.4—1991.

The major change in this edition is the inclusion of a multi-point method.

This Standard is one of a series of Standards for the testing of alumina.

The term 'informative' has been used in this Standard to define the application of the appendix to which it applies. An 'informative' appendix is only for information and guidance.

CONTENTS

	<i>Page</i>
FOREWORD	3
1 SCOPE	4
2 REFERENCED DOCUMENTS	4
3 PRINCIPLE	4
4 SAFETY	4
5 REAGENTS	4
6 APPARATUS	5
7 SAMPLING AND SAMPLE PREPARATION	5
8 PROCEDURE	5
9 CALCULATION AND REPORTING OF RESULTS	6
10 PRECISION	6
11 QUALITY CONTROL	7
12 TEST REPORT	7
APPENDICES	
A THE DIFFERENCE BETWEEN SINGLE AND MULTIPOINT DETERMINED BY SSA	8
B RESULTS OF TEST PROGRAMME	9

FOREWORD

In the development of this method, the temperature for degassing (150°C) was chosen after testing various smelter-grade aluminas (SGAs). It was found that temperatures above 150°C changed the state of some samples with respect to the surface area, presumably through the partial calcination of the hydrated alumina, which is present to some degree in smelter-grade alumina.

Modern instruments now allow multi-point surface area analysis to be carried out easily. It is recommended a multi-point surface area analysis be carried out whenever possible but single-point analysis is still acceptable. The test report should indicate whether the result is a single-point or multi-point result.

STANDARDS AUSTRALIA

Australian Standard
Alumina**Part 4: Determination of specific surface area by nitrogen adsorption****1 SCOPE**

This Standard sets out an instrumental method for the determination of specific surface area (SSA) of smelter-grade alumina by nitrogen adsorption by a single or multi-point method. A multi-point method is recommended due to the higher accuracy obtained; if a single-point method is used a lower result will be obtained.

NOTE: Appendix A provides an explanation why this is the case.

The Standard is applicable to aluminas having a surface area between 50 m²/g and 90 m²/g.

2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

2243 Safety in laboratories (series)

2850 Chemical analysis—Interlaboratory test programs—For determining precision of analytical method(s)—Guide to the planning and conduct

4538 Guide to the sampling of alumina

4538.2 Part 2: Preparation of sample

3 PRINCIPLE

The method is based on the ability of a material to adsorb nitrogen molecules on its surface at the boiling point of liquid nitrogen. The instrument determines the quantity of nitrogen gas necessary to form a monolayer of gas molecules on the sample surface. The surface area can then be calculated based on the basic theory by Brunauer-Emmett-Teller.* A test sample is degassed at 50 °C. The degassing process can be carried out using either vacuum or a flowing nitrogen stream. After degassing, the sample is weighed. This mass, and the monolayer volume determined by the instrument, is used to calculate the specific surface area.

4 SAFETY

For information on laboratory safety, reference should be made to the relevant parts of AS 2243.

CAUTION: CARE SHOULD BE TAKEN WHEN HANDLING CRYOGENIC LIQUIDS.

5 REAGENTS**5.1 Liquid nitrogen**

With a boiling point of −196 °C at 1 atm. pressure (101.3 kPa).

* S. BRUNAUER, P.H. EMMETT and E. TELLER, *J. Am Chem. Soc.* 60, p.309 (1938).