

Australian Standard™

**Heavy mineral sand concentrates—  
Sampling**

**Part 2: Sampling from stationary  
situations**

This Australian Standard was prepared by Committee MN-004, Heavy Mineral Sands. It was approved on behalf of the Council of Standards Australia on 1 October 2003 and published on 1 December 2003.

---

The following are represented on Committee MN-004:

Australian Institute of Mining and Metallurgy

Chamber of Minerals and Energy of Western Australia

Additional interests participating in the preparation of this Standard:

Producers of heavy mineral sand concentrates

---

### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at [www.standards.com.au](http://www.standards.com.au) and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.com.au](mailto:mail@standards.com.au), or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

---

*This Standard was issued in draft form for comment as DR 03357.*

Australian Standard™

**Heavy mineral sand concentrates—  
Sampling**

**Part 2: Sampling from stationary  
situations**

Revised as AS 2884.2—1993.  
Second edition 2003.

**COPYRIGHT**

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd  
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 5577 1

## PREFACE

This Standard was prepared by the Standards Australia Committee MN-004, Heavy Mineral Sands to supersede AS 2884.2—1993, *Heavy mineral sand concentrates—Sampling, Part 2: Sampling from stationary situations*.

The objective of this Standard is to provide sampler and superintending companies with a method for safely obtaining samples of heavy mineral sands for analytical purposes when the preferred method of sampling from a moving stream is not possible.

This revision confirms the method of sampling from stationary situations. Editorial changes have been made to bring the Standard into line with current style.

The term 'informative' has been used in this Standard to define the application of the appendix to which it applies. An 'informative' appendix is only for information and guidance.

## CONTENTS

	<i>Page</i>
1 SCOPE.....	4
2 REFERENCED DOCUMENTS.....	4
3 DEFINITIONS.....	4
4 PRINCIPLES OF SAMPLING.....	6
5 ESTABLISHING A SAMPLING SCHEME.....	11
6 MASS OF INCREMENT.....	11
7 NUMBER OF INCREMENTS AND SAMPLING UNITS.....	12
8 MASS OF GROSS SAMPLES AND PARTIAL SAMPLES.....	16
9 SAMPLING LARGE QUANTITIES OF CONCENTRATE.....	18
10 SAMPLING CONCENTRATES IN PACKED FORM.....	20
11 STOPPED-BELT SAMPLING.....	21
12 PACKING AND MARKING OF SAMPLE.....	21
APPENDIX A SAMPLING IMPLEMENTS.....	23

## STANDARDS AUSTRALIA

## Australian Standard

## Heavy mineral sand concentrates—Sampling

## Part 2: Sampling from stationary situations

**1 SCOPE**

This Standard sets out methods for the sampling of heavy mineral sands from stationary situations to provide samples for chemical analysis, physical testing and determination of moisture. Stopped-belt sampling is specifically included.

The methods of sampling outlined in this Standard should be considered only where the preferred method of sampling from a moving stream is not possible.

The preparation of samples taken by methods outlined in this Standard is covered in AS 2884.3.

Clauses 4 to 8 provide general sampling theory that may not be relevant to sampling from stationary situations.

**2 REFERENCED DOCUMENTS**

The following documents are referred to in this Standard:

AS

1152	Specification for test sieves
2884	Heavy mineral sand concentrates—Sampling
2884.3	Part 3: Preparation of samples
2884.4	Part 4: Determination of precision and bias

**3 DEFINITIONS**

For the purpose of this Standard, the definitions below apply.

**3.1 Bias**

The tendency to obtain a value that is either persistently higher or persistently lower than the reference value. In practice, it is the difference between the reference value and the average result obtained from a large number of determinations using a biased method.

**3.2 Coefficient of variation**

The ratio of the standard deviation to the mean value, expressed as a percentage.

**3.3 Constant-mass division**

The method of sample division in which the retained portion is of uniform mass.

**3.4 Divided increment**

The quantity of concentrate obtained by division of the increment to decrease its mass.

**3.5 Division**

The process of decreasing the sample mass (without modification of the particle size of the constituent pieces) whereby one or more representative parts of the sample are retained.