

Australian Standard[®]

Cellulose-cement products

Part 1: Corrugated sheets

This Australian Standard was prepared by Committee BD/40, Fibre Cement Building Products. It was approved on behalf of the council of Standards Australia on 28 October 1991 and published on 17 January 1992.

The following interests are represented on Committee BD/40:

Australian Institute of Building
Australian Institute of Building Surveyors
Australian Uniform Building Regulations Coordinating Council
Confederation of Australian Industry
Department of Administrative Services—Australian Construction Services

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 91040.

Australian Standard[®]

Cellulose-cement products
Part 1: Corrugated sheets

First published as AS 2908—1987.
Revised and redesignated AS 2908.1—1992.
Incorporating:
Amdt 1—1994

PREFACE

This Standard was prepared by the Standards Australia Committee on Fibre Cement Building Products, to supersede AS 2908—1987, *Cellulose cement products—Corrugated sheets for roofing and cladding*. The technical content is generally similar, but the scope of the Standard has been expanded to allow for varying sheet profiles.

The sheets specified in this Standard may be installed in accordance with AS 1639, *The design and installation of corrugated fibre-reinforced cement roofing and wall cladding*.

So that the best use is made of corrugated cellulose-cement sheets for roofing and cladding, it is recommended that this series be read in conjunction with AS 1639.

The standard forms part of a series which is as follows:

AS	
2908	<i>Cellulose-cement products</i>
2908.1	Part 1: <i>Corrugated sheets</i> (this Standard)
2908.2	Part 2: <i>Flat sheets</i>

CONTENTS

	<i>Page</i>
1 SCOPE	3
2 REFERENCED DOCUMENTS	3
3 CLASSIFICATION	3
4 COMPOSITION	3
5 PHYSICAL REQUIREMENTS	3
6 DIMENSIONS AND TOLERANCE	3
7 BENDING STRENGTH	4
8 WATERTIGHTNESS	4
9 RESISTANCE TO HOT WATER SOAKING	4
10 MARKING	4
APPENDICES	
A ASSESSMENT OF COMPLIANCE WITH THIS STANDARD	5
B DETERMINATION OF THE STRENGTH OF CORRUGATED CELLULOSE-CEMENT SHEETS	6
C DETERMINATION OF THE WATERTIGHTNESS OF CORRUGATED CELLULOSE-CEMENT SHEETS	8
D DETERMINATION OF RESISTANCE TO HOT WATER SOAKING OF CORRUGATED CELLULOSE-CEMENT SHEETS	10

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS AUSTRALIA

Australian Standard

Cellulose-cement products

Part 1: Corrugated sheets

1 SCOPE This Standard sets out requirements for corrugated cellulose-cement sheets for use primarily as roofing and cladding. It also applies to autoclaved sheets in which the cement is partially replaced by ground silica.

The sheets are finished with one of the following:

- (a) Their natural colour.
- (b) Colouring matter added to their composition.
- (c) Coloured or uncoloured adherent coatings on their surfaces.

This Standard does not apply to asbestos-fibre-reinforced sheets.

NOTE: Advisory information on alternative methods of determining compliance with this Standard is given in Appendix A.

2 REFERENCED DOCUMENTS The following documents are referred to in this Standard.

AS

- 1199 Sampling procedures and tables for inspection by attributes
 1399 Guide to AS 1199—Sampling procedures and tables for inspection by attributes
 2193 Methods for calibration and grading of force-measuring systems of testing machines
 2490 Sampling procedures and charts for inspection by variables for percent defective
 3900 Quality systems—Guide to selection and use
 3904 Quality systems—Guide to quality management and quality system elements

ISO

Guide 44 General rules for ISO or IEC international third party certification scheme for products

3 CLASSIFICATION Corrugated sheets covered by this Standard shall be divided into three classifications according to the depth of corrugation, as given in Table 1.

NOTE: It is recommended that the classification of a corrugated sheet material be specified in all appropriate technical literature.

TABLE 1
PROFILE DEPTH CLASSIFICATION

Profile class	Corrugation depth mm	
	Less than	Not less than
1	50	45
2	60	50
3	75	60

4 COMPOSITION Corrugated cellulose-cement sheets complying with this Standard shall consist primarily of an inorganic hydraulic binder, or a calcium silicate formed by a chemical reaction of a silicious and calcareous material, reinforced by cellulose fibres to which other organic or synthetic fibres may be added. The addition of process aids, fillers and pigments which are compatible with the cellulose-cement mixture is acceptable.

5 PHYSICAL REQUIREMENTS Corrugated sheets shall generally be rectangular in shape and be corrugated such that the crowns of the corrugations are parallel within the tolerances specified in Clause 6. The finished sheets shall be clean, with neatly trimmed edges and free from visible defects.

6 DIMENSIONS AND TOLERANCES The dimensions and tolerances on corrugated cellulose-cement sheets shall be as follows:

- (a) *Length*: 1200 mm to 3000 mm rising by increments of 300 +5, -10 mm.
- (b) *Width*:
 - (i) *Class 1*: 1080 +10, -5 mm.
 - (ii) *Class 2*: 1150 +10, -5 mm.
 - (iii) *Class 3*: 1093 +10, -5 mm.
- (c) *Thickness*—when measured at T, as shown in Figure 1: 6.0 +1.5 -10 mm.
- (d) *Pitch*—when measured at P, as shown in Figure 1:
 - (i) *Class 1*: 150 +0, -10 mm.
 - (ii) *Class 2*: 180 +0, -10 mm.
 - (iii) *Class 3*: 210 +0, -10 mm.