

AS 2920

Superseded by AS/NZS 4256.1:1994, AS/NZS 4256.2:1994,
AS/NZS 4257.1:1994, AS/NZS 4257.2:1994, AS 2920—1987
AS/NZS 4257.6:1994 and AS/NZS 4257.7:1994. UDC 691.175.743:692.232.4

WITHDRAWN
TAS. December 1994.

Australian Standard® 2920—1987

UNPLASTICIZED POLY VINYL CHLORIDE (UPVC) WALL CLADDING



STANDARDS ASSOCIATION OF AUSTRALIA
Incorporated by Royal Charter

This Australian standard was prepared by Committee PL/22, Plastics Building Sheets. It was approved on behalf of the Council of the Standards Association of Australia on 14 November 1986 and published on 5 January 1987.

The following interests are represented on Committee PL/22:

Australian Institute of Building
Australian Institute of Building Surveyors
CSIRO, Division of Building Research
Housing Industry Association, NSW Division
Ministry of Consumer Affairs, Victoria
National Building Technology Centre
Plastics Institute of Australia Inc.
Royal Australian Institute of Architects

Review of Australian Standards. To keep abreast of progress in industry, Australian standards are subject to periodic revision and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all SAA publications will be found in the Catalogue of SAA Publications; this information is supplied each month by SAA's journal 'The Australian Standard', which subscribing members receive and which gives details of new publications, new editions and amendments, and of withdrawn standards.

Suggestions for improvements to Australian standards, addressed to the head office of the Association, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian standard should be made without delay in order that the matter may be investigated and appropriate action taken.

AUSTRALIAN STANDARD

UNPLASTICIZED POLY VINYL CHLORIDE (UPVC) WALL CLADDING

AS 2920—1987

First published1987



PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.

ISBN 0 7262 4463 5

6 JAN 1987

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

for

UNPLASTICIZED POLY VINYL CHLORIDE (UPVC) WALL CLADDING

1 SCOPE. This standard sets out the requirements for uncoated, opaque, UPVC sheets extruded and formed into profiles for use with accessories as external wall cladding.

NOTE: Advisory information on alternative methods of determining compliance of a 'lot' with this standard is given in Appendix A.

2 APPLICATION. This standard is primarily intended to apply to UPVC wall cladding attached to new construction wall structures or over existing walls in accordance with AS 2921*.

3 REFERENCED DOCUMENTS. The following standards are referred to in this standard:

- AS 1199 Sampling Procedures and Tables for Inspection by Attributes
- AS 1399 Guide to AS 1199, Sampling Procedures and Tables for Inspection by Attributes
- AS 1530 Methods for Fire Tests on Building Materials, Components and Structures Part 3—Test for Early Fire Hazard Properties of Materials
- AS 1821-23 Suppliers Quality Control Systems
- AS 2000 Guide to AS 1821-23, Suppliers Quality Control Systems
- AS 2001.4.1 Methods of Test for Textiles Part 4.1—Colourfastness Tests—Definitions and General Requirements
- AS 2193 Methods for Calibration and Loading of Force-measuring Systems of Testing Machines
- AS 2433 Plastics—Method for Exposure to Ultraviolet Light
- AS 2464.6 Methods of Testing Thermal Insulation Part 6—Steady State Thermal Transmittance Properties by Means of the Guarded Hotplate
- AS CK24† Code of Practice for Outdoor Weathering of Plastics in the Australian Environment Part 1—Commercial Products
- AS 2920 Unplasticized Poly Vinyl Chloride (UPVC) Wall Cladding—General Installation Requirements

4 TYPE. Cladding shall be classified as follows:

Type A—cladding with a bending strength of not less than 350 Nm/m and a bending rigidity of not less than 20 Nm.

Type B—cladding with a bending strength of not less than 25 Nm/m and a bending rigidity of not less than 0.10 Nm.

Values of bending strength and bending rigidity are determined in accordance with Clause 10.5.

Type A cladding can be used fixed directly to structural framing. Type B cladding can only be used when fully and continuously supported over structural framing or over existing walling.

5 DEFINITIONS. For the purpose of this standard the following definitions apply:

5.1 Cladding—any material used to face a building or structure.

5.2 Nominal width—total width after profiling or manufacturing to finished goods width.

5.3 Cover width—total amount of cover available from the cladding or facing after allowing for overlaps.

5.4 Thickness—thickness of the material constituting the wall of the cladding, distinct from the thickness of the profile.

NOTE: The material may be of a fine cellular texture or the cladding may be double-walled.

5.5 Accessories—other UPVC products required to complete the finished wall system.

6 APPEARANCE. Cladding and accessories shall be uniform in colour, opacity and finish. Cladding and accessories shall be free from scratches, dents, blisters and inclusions which would affect performance in service.

NOTE: Defects described in Clause 6 cannot be completely quantified. Where the presence, size or frequency of any of these are considered to be of concern, agreements should be made between the purchaser/Approving Authority/certifying body (as appropriate), and the manufacturer. This may be achieved by the provision of acceptable type samples.

Where defects are present and the product is submitted for acceptance, the manufacturer should be able to demonstrate fitness for purpose.

7 DIMENSIONAL REQUIREMENTS.

7.1 Length. When measured in accordance with Appendix B, the tolerance on a nominated length of any cladding shall be +10, - 5 mm.

7.2 Width. When measured in accordance with Appendix B, the tolerances on width shall be:

- (a) ± 2 mm on a nominated width of cladding.
- (b) Individual measurements of width shall not vary from the mean determination of width by more than ± 1 mm per 100 mm of width.

7.3 Squareness. When cut to length, the ends of cladding shall not deviate from a true right angle by more than 2 mm for each 100 mm of cladding width when measured in accordance with Appendix B.

7.4 Straightness. When measured in accordance with Appendix B, straightness of cladding shall not deviate by more than 5 mm for any 1 m of length.

* In course of preparation.

† In process of revision. Revised standard will be AS 1745.1.