



Gold and gold bearing alloys

Part 1: Determination of gold content (less than 30%)—Gravimetric (fire assay) method

STANDARDS
Australia



AS 3515.1:2019

This Australian Standard ® was prepared by CH-010, Analysis Of Metals. It was approved on behalf of the Council of Standards Australia on 29 January 2019.

This Standard was published on 1 March 2019.

The following are represented on Committee CH-010:

- Australasian Institute of Mining and Metallurgy
- Australian Chamber of Commerce and Industry
- Bureau of Steel Manufacturers of Australia
- Geoscience Australia
- International Copper Association Australia
- Jewellers Association of Australia
- Materials Australia
- National Association of Testing Authorities Australia

This Standard was issued in draft form for comment as DR AS 3515.1:2018.

Keeping Standards up-to-date

Ensure you have the latest versions of our publications and keep up-to-date about Amendments, Rulings, Withdrawals, and new projects by visiting:

www.standards.org.au

ISBN 978 1 76072 381 1



Gold and gold bearing alloys

Part 1: Determination of gold content (less than 30%)—Gravimetric (fire assay) method

Origin: technical AS 3515.1—1996.
Second edition 2005.
This edition 2019.

COPYRIGHT

© Standards Australia Limited 2019

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Cth).

Preface

This Standard was prepared by Standards Australia Committee CH-010, Analysis of Metals, to supersede AS 3515.1—2005, *Gold and gold bearing alloys, Part 1: Determination of gold content (less than 30%)—Gravimetric method*.

The objective of this Standard is to set out gravimetric procedures for the determination of gold content less than 30 % by gravimetric (fire assay) methods.

The major changes in this edition are as follows:

- (a) Inclusion of purity of proof in the calculation of the surcharge.
- (b) Exclusion of alloys containing iridium in the scope.
- (c) The use of either vacuum tube sampling method or dip sampling as the preferred sampling techniques.
- (d) A warning on appropriate safety protocols for end users of this Standard.
- (e) Editorial amendments and consistency with other Standards in the series.

This Standard is part of a series for AS 3515, as follows:

AS 3515.1, *Gold and gold bearing alloys, Part 1: Determination of gold content (less than 30 %) — Gravimetric (fire assay) method* (this Standard)

AS 3515.2, *Gold and gold bearing alloys, Part 2: Determination of gold content (30% to 99.5%)—Gravimetric (fire assay) method*

AS 3515.3, *Gold and gold bearing alloys, Part 3: Determination of gold content (greater than 99.5 %) — Gravimetric (fire assay) method*

AS 3515.4, *Gold and gold bearing alloys, Part 4: Determination of gold content (greater than 99.95%)—Inductively coupled plasma—Atomic emission spectrometry*

The term “informative” has been used in this Standard to define the application of the appendix to which it applies. An “informative” appendix is for information and guidance only.

Contents

Preface	ii
Section 1 Scope and general	1
1.1 Scope.....	1
1.2 Normative references.....	1
1.3 Definitions.....	1
1.4 Reagents.....	3
1.5 Apparatus.....	5
Section 2 Sample preparation and preliminary determination	4
2.1 General.....	4
2.2 Sample inspection and preparation.....	4
2.3 Preliminary determination of the approximate total precious metals, gold, silver and total base metals content.....	4
2.3.1 General.....	4
2.3.2 Test portion preparation.....	4
2.3.3 Cupellation.....	5
2.3.4 Re-inquarting.....	5
2.3.5 Parting.....	5
2.3.6 Calculations.....	6
2.4 Criteria for selection of determination method.....	6
Section 3 Total precious metals content less than 40 %	6
3.1 Scope of section.....	6
3.2 Principle.....	7
3.3 Number of determinations.....	7
3.4 Proof tests.....	7
3.5 Preparation of test portion and proof.....	7
3.6 Cupellation.....	8
3.7 Parting.....	8
3.8 Calculations.....	9
3.8.1 Change in mass of proof.....	9
3.8.2 Determination of surcharge.....	9
3.8.3 Adjusted mass of the gold cornet from the sample or test portion.....	10
3.8.4 Gold content.....	10
Section 4 Total precious metals content is 40 % or greater	10
4.1 Scope of section.....	10
4.2 Principle.....	10
4.3 Number of determinations.....	10
4.4 Proof tests.....	10
4.5 Preparation of the test portion and proof.....	11
4.6 Cupellation.....	11
4.7 Parting.....	12
4.8 Calculations.....	12
4.8.1 Change in mass of proof.....	12
4.8.2 Determination of surcharge.....	13
4.8.3 Adjusted mass of the gold cornet.....	13
4.8.4 Gold content.....	13
Section 5 Precision and acceptance of results	13
5.1 Precision.....	13
5.2 Acceptance of results.....	14
5.2.1 Reference Standard.....	14
5.2.2 Test results.....	14
5.3 Test report.....	14
Appendix A (informative) Methods of sampling bullion	15

Bibliography 19

Currently in preview, click buy full version

Australian Standard®

Gold and gold bearing alloys

Part 1: Determination of gold content (less than 30%)—Gravimetric (fire assay) method

WARNING — THE USE OF THIS STANDARD MAY INVOLVE HAZARDOUS MATERIALS, OPERATIONS AND EQUIPMENT. THIS STANDARD DOES NOT PURPORT TO ADDRESS ALL OF THE SAFETY PROBLEMS ASSOCIATED WITH ITS USE. IT IS THE RESPONSIBILITY OF THE USER OF THIS STANDARD TO ESTABLISH APPROPRIATE SAFETY AND HEALTH PRACTICES AND DETERMINE THE APPLICABILITY OF REGULATORY LIMITATIONS PRIOR TO USE.

Section 1 Scope and general

1.1 Scope

This Standard sets out gravimetric procedures for the determination of gold content in the range 0.2 % to 30 % in gold and gold bearing alloys with < 2 % nickel, < 0.05 % rhodium, < 0.05 % tungsten, < 0.05 % tin, < 1 % platinum and < 3 % palladium. This method is not suitable for alloys containing iridium.

Two methods of gold determination are specified:

- (a) The first method is used when the total precious metal content is less than 40 %.
- (b) The second method is used when the total precious metal content is 40 % or greater.

NOTE 1 Recommended methods of sampling bullion for use with this Standard are provided in [Appendix A](#).

NOTE 2 The presence of the following elements may cause difficulties in obtaining a homogeneous sample: iron, lead, antimony, nickel or arsenic.

NOTE 3 A preliminary assay may first be performed to determine the gold, silver and base metal present.

1.2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document.

NOTE Documents referenced for informative purposes are listed in the Bibliography.

ISO 3696, *Water for analytical laboratory use—Specification and test methods*

1.3 Definitions

For the purpose of this Standard, the definitions below apply.

1.3.1

bullion

an alloy of gold and silver with variable amounts of one or more of the base metals

1.3.2

cornet

an alloy of gold and silver after it has been hammered, annealed and fashioned into a roll, prior to parting