

Australian Standard[®]

**ACRYLONITRILE BUTADIENE
STYRENE (ABS) PIPES AND
FITTINGS FOR PRESSURE
APPLICATIONS**

**Part 2—SOLVENT CEMENT
FITTINGS**

This Australian Standard was prepared by Committee PL/1, ABS Pipe Systems. It was approved on behalf of the Council of the Standards Association of Australia on 25 October 1987 and published on 4 January 1988.

The following interests are represented on Committee PL/1:

Australian Mining Industry Council
Australian Shippers Council
Council of Australian Food Technology Associations Incorporated
Department of Local Government Queensland
Electricity Commission of New South Wales
Electricity Supply Association of Australia
Engineering and Water Supply Department South Australia
Hunter District Water Board
Melbourne and Metropolitan Board of Works
Metropolitan Water Sewerage and Drainage Board, N.S.W.
Plastics Institute of Australia
Water Authority of Western Australia
Water Supply and Sewerage Department Queensland

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 86110.

AS 3518.2—1988

Australian Standard[®]

**ACRYLONITRILE BUTADIENE
STYRENE (ABS) PIPES AND
FITTINGS FOR PRESSURE
APPLICATIONS**

**Part 2—SOLVENT CEMENT
FITTINGS**

First published as AS 3518.2—1988.

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 4788 7

PREFACE

This Standard was prepared by the Association's Committee PL/1, ABS Pipe Systems, acting under the authority of the Plastics Standards Board, following a request from the Plastics Institute of Australia.

Most fittings used in ABS pipelines up to nominal size 200 mm are of solvent cement types, consequently this Standard initially covers only these fittings. Socket dimensions have been specified to ensure an interference fit between pipe and fitting.

Companion Standard AS 3518.1 specifies requirements for ABS pipes up to 200 mm nominal size.

A test is currently being developed to measure the effect of long term pressure cycling on plastics piping systems, and may be included in a future edition of this Standard.

CONTENTS

	<i>Page</i>
1. SCOPE	3
2. REFERENCED DOCUMENTS	3
3. DEFINITIONS	3
4. NOTATION	3
5. CLASSIFICATION	3
6. EFFECT OF TEMPERATURE ON MAXIMUM WORKING PRESSURE	3
7. COMPOSITION	3
8. GENERAL REQUIREMENTS	4
9. PERFORMANCE REQUIREMENTS	4
10. MARKING	5

APPENDICES

A DETERMINATION OF COMPLIANCE OF A LOT	6
B METHOD FOR DETERMINING THE DIMENSIONS OF FITTINGS	7
C METHOD FOR HYDROSTATIC PRESSURE TESTING OF ABS PRESSURE FITTINGS	9
D METHOD FOR HIGH TEMPERATURE STRESS-RELIEF TESTING OF ABS FITTINGS	13
E METHOD FOR DETERMINING THE EFFECT OF WATER	14

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

ACRYLONITRILE BUTADIENE STYRENE (ABS) PIPES AND FITTINGS FOR
PRESSURE APPLICATIONS

PART 2—SOLVENT CEMENT PIPE FITTINGS

1 SCOPE. This Standard specifies requirements for moulded acrylonitrile butadiene styrene (ABS) fittings for solvent cement jointing to ABS pipes up to 200 mm nominal size complying with AS 3518.1.

2 REFERENCED DOCUMENTS. The following Standards are referred to in this Standard:

AS 1199	Sampling Procedures and Tables for Inspection by Attributes.
AS 1349	Bourdon Tube Pressure and Vacuum Gauges.
AS 1399	Guide to AS 1199, Sampling Procedures and Tables for Inspection by Attributes.
AS 1821- AS 1823	Suppliers Quality Systems.
AS 1984	Vernier Callipers (Metric Series).
AS 2000	Guide to AS 1821-23, Suppliers Quality Systems.
AS 2070	Plastics Materials for Food Contact Use.
AS 2101	Internal Micrometers (including Stick Micrometers) (Metric Series).
AS 2102	External Micrometers (Metric Series).
AS 2490	Sampling Procedures and Charts for Inspection by Variables for Percent Defective.
AS 2831	Thermometers—Solid Stem—Long and Short—For Precision Use.
AS 3518.1	Acrylonitrile Butadiene Styrene (ABS) Pipes and Fittings for Pressure Applications Part 1—Pipes.
ISO 727	Fittings of Unplasticized Polyvinyl Chloride (PVC-U), Chlorinated Polyvinyl Chloride (PVC-C) or Acrylonitrile/Butadiene Styrene (ABS) with Plain Sockets for Pipes under Pressure—Dimensions of Sockets—Metric Series.

3 DEFINITIONS. For the purpose of this Standard, the definitions below apply.

3.1 Fitting—any component other than pipes or tubes intended for connection to or installation in a pipeline, e.g. bend, connector, junction, trap, collar, socket, straight fitting, tap or valve.

3.2 Saddle—a shaped plate used to reinforce a pipe wall where a branch is to be connected.

3.3 ABS solvent cement—a solvent blend capable of softening the surface of ABS plastics for the purpose of jointing.

3.4 Solvent cemented joint—a joint made of certain types of plastics piping in which the contact surfaces are both coated with solvent cement. The joint is then made by pressing the softened surfaces together.

4 NOTATION. The following notation shall apply in this Standard:

DN = nominal size, in millimetres.

D_m = mean outside diameter, in millimetres.

D_i = socket mouth mean inside diameter, in millimetres.

D_r = socket root mean diameter, in millimetres.

L = socket length, in millimetres.

t = wall thickness, in millimetres.

NOTE: Nominal size, DN, for ABS pipe is based on the bore diameter.

5 CLASSIFICATION. Fittings shall be classified at a fitting material temperature of 20°C as follows:

Class 9 — for use with pipes with a maximum static working pressure up to 0.9 MPa.

Class 12— for use with pipes with a maximum static working pressure up to 1.2 MPa.

Class 15— for use with pipes with a maximum static working pressure up to 1.5 MPa.

NOTES:

1. Selection of class should be based on consideration of all factors which may affect the operation of the fitting, e.g. temperature of operation, fluctuating pressure, external loading, etc.

2. It is usual to manufacture each type of fitting with a single wall thickness appropriate to the maximum pressure class of pipe with which it is intended to be used.

6 EFFECT OF TEMPERATURE ON MAXIMUM WORKING PRESSURE. The reduction of maximum working pressure with increasing temperatures above 20°C shall be not less for the fitting and joint than that specified for ABS pipe in AS 3518.1.

7 COMPOSITION. Fittings shall be manufactured from material which complies with the requirements of Clause 7 of AS 3518.1.

NOTE: Statutory Authorities may require that the manufacturer disclose the composition of the fitting.