

see Revision see DR97103  
~~LOAN COPY~~  
~~INFORMATION CENTRE~~  
~~STANDARDS AUSTRALIA~~

**SUPERSEDED BY:**  
AS 3582.1-1998

AS 3582.1-1991

**Australian Standard®**

---

**Supplementary cementitious  
materials for use with portland  
cement**

**Part 1: Fly ash**

---



**STANDARDS AUSTRALIA**

This Australian Standard was prepared by Committee BD/31, Supplementary Cementitious Materials for use with Portland Cement. It was approved on behalf of the Council of Standards Australia on 20 September 1990 and published on 11 February 1991.

---

The following interests are represented on Committee BD/31:

Association of Consulting Engineers Australia

AUSTROADS

Bureau of Steel Manufacturers of Australia

Cement and Concrete Association of Australia

CSIRO, Division of Building, Construction and Engineering

Electricity Commission of New South Wales

Engineering and Water Supply Department, S.A.

National Ash Association of Australasia

National Ready Mixed Concrete Association

Public Works Department, N.S.W

Rural Water Commission, Vic.

University of Queensland

University of Sydney

---

*Review of Australian Standards.* To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

---

*This Standard was issued in draft form for comment as DR 87242.*

Australian Standard®

---

**Supplementary cementitious  
materials for use with portland  
cement**

**Part 1: Fly ash**

---

AS 3582.1 first published in part as AS 1130—1971.  
AS 1129 first published 1971.  
AS 1130—1971 and part of AS 1129—1971  
revised, amalgamated and redesignated AS 3582.1—1991.

## PREFACE

This Standard was prepared by the Standards Australia Committee on Supplementary Cementitious Materials for use with Portland Cement and supersedes both AS 1129—1971, *Fly ash for use in concrete*, and AS 1130—1971, *Code of practice for use of fly ash in concrete*. This Standard has been redesignated AS 3582.1.

The method of testing for fineness is based on a reassessed reference material which increases the value of residue determined. To avoid confusion, fineness is expressed as a percentage passing a 45  $\mu\text{m}$  sieve.

Fineness based on the 150  $\mu\text{m}$  sieve has been discontinued since it is not applicable to the finer ashes. Also, the use of the Blaine surface-area determination is not used in this Standard as it has very limited application to fly ash; the 45  $\mu\text{m}$  sieve test is more appropriate and more convenient.

In this Standard the 45  $\mu\text{m}$  sieve test is based on a reference fly ash which is calibrated against a precision micromesh sieve rather than a variable woven wire sieve. The method of correction is also altered and these changes will result in a larger residue value more in line with values obtained by tests in other countries.

The limits placed on the requirements for the fine grade are very tight (i.e. 75 percent minimum passing the 45  $\mu\text{m}$  sieve and 4 percent loss on ignition). In previous versions of this Standard the proposed 75 percent passing corresponds to about 15 percent retained. The Committee felt that further limits on variability would be unnecessary.

New performance-based tests are introduced for the determination of relative water requirement and relative strength. These tests are based on BS 3892, *Specification for pulverized fuel ash for use as a cementitious component in structural concrete*, modified for Australian conditions and testing procedures.

## CONTENTS

	<i>Page</i>
FOREWORD .....	3
1 SCOPE .....	4
2 REFERENCED DOCUMENTS .....	4
3 DEFINITIONS .....	4
4 MARKING .....	4
5 GRADING .....	4
6 PROPERTIES .....	5
7 TEST METHODS .....	5
8 RETESTS .....	5
9 TEST CERTIFICATE .....	6
 APPENDICES	
A METHODS FOR DEMONSTRATING COMPLIANCE WITH THIS STANDARD	7
B SAMPLING AND PREPARATION OF SAMPLES .....	8

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the Head Office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

## FOREWORD

Since 1971, there have been many changes in the sources and quality of fly ash, and the technology of its use has been further developed. As a result of the expansion of production facilities over the period, it is now possible to select or modify the characteristics of fly ash, and this Standard recognizes this circumstance by providing for three grades of the material, viz. fine, medium and coarse. Gradation is based on fineness and loss of mass on ignition.

Fine and medium grades are used for normal concrete whereas coarse grades are mainly intended for soil stabilization, lean mix concrete or intergrinding with Portland cement clinker to produce blended cements. For many applications the medium grade is appropriate.

Tests performed at the instigation of Standards Australia provided useful predictions of likely performance of a combination of cement and fly ash in concrete. It should be noted that different fly ashes can behave differently with various cements. However, because of the short history of these tests in Australia, insufficient data exists to specify individual limits and, in consequence, no limits have been set. A limit on the magnesia content of fly ash has been introduced with a method of test for fly ash with a high magnesia content. No such fly ashes are produced at present in Australia.

As a result of the growing concern in Australia and overseas regarding alkali/aggregate reaction, fly ash may be more often used to mitigate this problem. For this reason a test for available alkali content, (AS 3583.12), has been introduced with this Standard for use in cases where fly ash is used to reduce the alkali/aggregate reaction. The test has been taken from ASTM C 311, Sampling and Testing Fly Ash or Natural Pozzolans for Use as a Mineral Admixture in Portland Cement Concrete.

The limits on sulfuric anhydride (sulfur trioxide,  $\text{SO}_3$ ) content are unchanged but due to the possibility of a fly ash and a Portland cement, both with a high anhydride content, being blended and the resulting combined anhydride content being higher than that allowed in AS 1317, a restriction is placed on the sulfuric anhydride content of fly ash.

## STANDARDS AUSTRALIA

## Australian Standard

## Supplementary cementitious materials for use with portland cement

## Part 1: Fly ash

**1 SCOPE** This Standard sets out requirements for fly ash as a component material for use in hydraulic cement/concrete.

NOTE: Alternative methods for determining compliance with this Standard are given in Appendix A.

**2 REFERENCED DOCUMENTS** The following documents are referred to in this Standard.

AS

- 1199 Sampling procedures and tables for inspection by attributes  
 1289 Methods of testing soil for engineering purposes  
 1289.A2 Part A—General and sample preparation—Preparation of disturbed soil samples for testing  
 1399 Guide to AS 1199, Sampling procedures and tables for inspection by attribute  
 3583 Methods of test for supplementary cementitious materials for use with portland cement  
 3583.1 Method 1: Determination of fineness by the 45 $\mu$ m sieve  
 3583.2 Method 2: Determination of moisture content  
 3583.3 Method 3: Determination of loss on ignition  
 3583.4 Method 4: Determination of autoclave expansion  
 3583.5 Method 5: Determination of relative density  
 3583.6 Method 6: Determination of relative water requirements and relative strength  
 3583.8 Method 8: Determination of sulfuric anhydride content  
 3583.9 Method 9: Determination of magnesia content  
 3583.12 Method 12: Determination of available alkali  
 3583.13 Method 13: Determination of chloride ion content  
 3900 Quality systems—Guide to selection and use  
 3904 Quality systems—Guide to quality management and quality system elements

ISO

Guide 44—1985 General Rules for ISO or IFC International Third Party Certification scheme for Products

**3 DEFINITIONS** For the purpose of this Standard the definitions below apply.

**3.1 Fly ash**—solid material extracted from the flue gases of a boiler fired with pulverized coal.

NOTE: The term does not apply to ash extracted from the bottom of a boiler (furnace ash) or economizer grits.

**3.2 Fine fly ash**—fly ash selected or processed to meet the requirements of 'fine fly ash' as set out in Table 1 of this Standard.

**3.3 Medium fly ash**—fly ash selected or processed to meet the requirements of 'medium fly ash' as set out in Table 1 of this Standard.

**3.4 Coarse fly ash**—fly ash selected or processed to meet the requirements of 'coarse fly ash' as set out in Table 1 of this Standard.

**4 MARKING** The following information shall appear on the container in which the fly ash is supplied or shall accompany bulk supplies of the fly ash:

(a) Name and section of power station.

NOTE: Where a power station is made up of various sections and these sections contain generating units which produce fly ash of significantly differing characteristics, the full identification is required; e.g. 'Vales Point B' or 'Thomas Ford A'.

(c) Grade of ash in accordance with Clause 5.

**5 GRADING** Fly ash shall be graded fine, medium or coarse in accordance with the requirements of Table 1. Fineness and loss on ignition shall be determined as specified in Table 2.

**TABLE 1**  
**GRADE REQUIREMENTS**

Grade	Fineness, percent by mass passing 45 $\mu$ m sieve, minimum	Loss on ignition, percent, maximum
Fine	75.0	4.0
Medium	60.0	6.0
Coarse	40.0	12.0