

Australian Standard[®]

**Supplementary cementitious
materials for use with portland
cement**

**Part 2: Slag—Ground granulated
iron blast-furnace**

This Australian Standard was prepared by Committee BD/31, Supplementary Cementitious Materials for Use with Portland Cement. It was approved on behalf of the Council of Standards Australia on 20 September 1990 and published on 11 February 1991.

The following interests are represented on Committee BD/31:

Association of Consulting Engineers, Australia
AUSTROADS
Bureau of Steel Manufacturers of Australia
Cement and Concrete Association of Australia
CSIRO, Division of Building, Construction and Engineering
Electricity Commission of New South Wales
Engineering and Water Supply Department, S.A.
National Ash Association of Australasia
National Ready Mixed Concrete Association
Public Works Department, N.S.W.
Rural Water Commission, Vic.
University of Queensland
University of Sydney

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

Australian Standard[®]

**Supplementary cementitious
materials for use with portland
cement**

**Part 2: Slag—Ground granulated
iron blast-furnace**

First published as AS 3582.2—1991.

PREFACE

This Standard was prepared by the Standards Australia Committee on Supplementary Cementitious Materials for use with Portland Cement.

Since 1966, in Australia, ground granulated iron blast-furnace slag has been used as a binder and, since 1972, for the production of blended cement in accordance with AS 1317. With recent developments in the industry, it has become necessary to lay down requirements for ground granulated iron blast-furnace slag when intended for use as a binder component in the manufacturing of concrete and mortar.

In preparing this Standard, it was the intention that the concrete manufactured using this material should be subject to the same requirements that apply to concrete and mortars produced from blended cements.

With this object, and in the interest of flexibility, it has been found necessary to stipulate that tests for strength and water demand be performed in conjunction with samples of the portland cement that is to be used for a particular mix.

CONTENTS

	<i>Page</i>
1 SCOPE	3
2 REFERENCED DOCUMENTS	3
3 DEFINITIONS	3
4 ADDITIONS	3
5 MARKING	3
6 PROPERTIES	4
7 TEST METHODS	4
8 RETESTS	4
9 TEST CERTIFICATE	5
TEST CERTIFICATE FOR GROUND GRANULATED IRON BLAST-FURNACE SLAG	5
APPENDICES	
A METHODS FOR DEMONSTRATING COMPLIANCE WITH THIS STANDARD	6
B SAMPLING AND PREPARATION OF TEST SAMPLES	7

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS AUSTRALIA

Australian Standard

Supplementary cementitious materials for use with portland cement

Part 2: Slag—Ground granulated iron blast-furnace

1 SCOPE This Standard sets out requirements for finely ground granulated iron blast-furnace slag for use as a cementitious material in concrete and mortar.

NOTE: Alternative methods for determining compliance with this Standard are given in Appendix A.

2 REFERENCED DOCUMENTS The following documents are referred to in this Standard:

AS

- 1199 Sampling procedures and tables for inspection by attributes
- 1289 Methods of testing soils for engineering purposes
- 1289.A2 Preparation of disturbed soil samples for testing
- 1317 Blended cement
- 1399 Guide to AS 1199, Sampling procedures and table for inspection by attributes
- 2350 Methods of testing portland and blended cements
- 2350.8 Method 8: Fineness index of portland cement by air permeability
- 3583 Methods of test for supplementary cementitious materials for use with portland cement
- 3583.3 Method 3: Determination of loss on ignition
- 3583.6 Method 6: Determination of relative water requirement and relative strength
- 3583.7 Method 7: Determination of sulfide sulfur content
- 3583.8 Method 8: Determination of sulfuric anhydride content
- 3583.9 Method 9: Determination of magnesia content
- 3583.10 Method 10: Determination of alumina and total iron content
- 3583.11 Method 11: Determination of manganese content
- 3583.13 Method 13: Determination of chloride ion content
- 3583.14 Method 14: Determination of insoluble residue content

3900 Quality systems — Guide to selection and use

3904 Quality systems — Guide to quality management and quality system elements

ASTM

C 465 Specification for processing additions for use in the manufacture of hydraulic cements

ISO

Guide 44 — 1985 General Rules for ISO or IEC International Third Party Certification scheme for Products

3 DEFINITIONS For the purpose of this Standard, the definitions below apply.

3.1 Iron blast-furnace slag — a non-metallic product, consisting essentially of silicates and aluminosilicates of calcium, produced simultaneously with iron in a blast furnace.

3.2 Granulated iron blast-furnace slag — the glassy granular material resulting from the rapid chilling of molten iron blast-furnace slag.

NOTE: Hereafter in this Standard, and in AS 3583 Ground granulated iron blast-furnace slag is usually referred to as 'Slag'.

4 ADDITIONS Unless the fact is clearly stated in writing by the manufacturer, additions of materials other than water or calcium sulfate containing not less than 30 percent sulfuric anhydride (SO_3), shall not be permitted. Where processing additions have been made, such materials shall not be deleterious to the end use and shall be in accordance with the recommendations of ASTM C 465.

NOTE: At the request of a purchaser, the manufacturer may state in writing the nature, proportion and identity of any processing additions that have been used together with test data showing compliance of such processing addition(s) with ASTM C 465.

5 MARKING The following information shall appear on the container in which the ground, granulated iron blast-furnace slag is supplied or shall accompany bulk supplies of the slag:

- (a) The sources of slag, the name of the manufacturer, and the name of the works in which it is processed.
- (b) A statement that a processing addition has been incorporated (if appropriate).