

Australian Standard[®]

**Conductors—Bare overhead,
aluminium and aluminium alloy—
Steel reinforced**

[Title allocated by Defence Cataloguing Authority: WIRE,
ELECTRICAL (Bare, Stranded, Aluminium and Aluminium Alloy,
Steel-reinforced, Overhead Use) NSC 6145]

This Australian Standard was prepared by Committee EL/10, Overhead Lines. It was approved on behalf of the Council of Standards Australia on 16 June 1988 and published on 14 April 1989.

The following interests are represented on Committee EL/10:

- Australian Electrical and Electronic Manufacturer's Association
 - Australian Porcelain Insulators Association
 - Confederation of Australian Industry
 - Electrical and Radio Federation of Victoria
 - Electrical Supply Association of Australia
 - Railways of Australia Committee
-

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standard users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 87099.

Australian Standard®

**Conductors—Bare overhead,
aluminium and aluminium alloy—
Steel reinforced**

[Title allocated by Defence Cataloguing Authority: WIRE,
ELECTRICAL (Bare Stranded, Aluminium and Aluminium Alloy,
Steel-reinforced, Overhead Use) NSC 6145]

First published as part of AS C75—1936 (endorsement of
BS 215:1934 without amendment).
Revised and redesignated AS C75.1—1963.
Revised and redesignated AS 1220.1—1973.
AS 1220.2 first published 1973.
AS 1220.3 first published 1973.
AS 1220.1, AS 1220.2 and AS 1220.3 revised,
amalgamated and redesignated AS 3607—1989.

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 5303 0

PREFACE

This Standard was prepared by the Standards Australia Committee on Overhead Lines to supersede all three parts of AS 1220, *Aluminium conductors steel reinforced for overhead power transmission purposes*:

Part 1: 1973 *Galvanized steel reinforced (ACSR/GZ)*

Part 2: 1973 *Aluminized steel reinforced (ACSR/AZ)*

Part 3: 1973 *Aluminium-clad steel reinforced (ACSR/AC)*

The Standard deals with composite conductors made with aluminium or aluminium alloy wires, reinforced with steel wires. Three types of steel wire are included as alternatives, i.e. zinc-coated (GZ), aluminium-coated (AZ) or aluminium-clad (AC).

In addition, the Standard provides for specific wire sizes in the range 1.60 mm to 4.75 mm, with a range of standard sizes of stranded construction conductors. Furthermore it provides for a range of new conductors containing steel and aluminium alloy wires which reflect actual usage of conductors throughout Australia.

This edition of the Standard differs from AS 1220—1973 as follows:

- (a) In determining conductor sizes, a range of wire sizes has been provided similar to the range of wires specified in the 1973 edition, but facility is also provided for conductors with other dimensions to be supplied by reference to this Standard.
- (b) To assist users in selecting the most suitable conductor for a particular application, the calculated equivalent aluminium area, conductor breaking load, and d.c. resistance for the standard conductors are given.
- (c) Section 2: Wire sizes have been rationalized.
- (d) Section 3: The number of standard sizes, especially in the alloy range, has been reduced and preferred sizes are indicated.
- (e) Section 4: For test purposes, requirements have been added to sequentially identify wire and conductor during production.
- (f) Appendix B: Now includes the theoretical basis for the calculation of modulus of elasticity and coefficient of linear expansion.
- (g) Appendix E: The code name system has been changed to permit the identification of alloy conductors by reference to existing ACSR code names.
- (h) Appendix F: This new Appendix has been included which highlights items which should be specified by the purchaser or agreed between purchaser and manufacturer at the time of order.

In the preparation of this Standard, reference was made to the following Standards:

IEC 207	<i>Aluminium stranded conductors</i>
IEC 208	<i>Aluminium alloy stranded conductors (aluminium-magnesium-silicon)</i>
IEC 210	<i>Aluminium alloy conductors, steel reinforced</i>
IEC 468	<i>Method of measurement of resistivity of metallic materials</i>
ASTM B 341	<i>Aluminium coated (aluminized) steel core wire for aluminium conductors, steel reinforced ACSR/AZ</i>
ASTM B 498M	<i>Zinc coated (galvanized) steel core wire for aluminium conductors, steel reinforced, ACSR (Metric)</i>
ASTM B 502	<i>Aluminium-clad steel core wire for aluminium conductors, aluminium-clad steel reinforced</i>
SS 424 08 13	<i>Aluminium alloy wire for stranded conductors for overhead lines</i>

Acknowledgment is made of the assistance received from those sources.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
SECTION 1. SCOPE AND GENERAL	
1.1 SCOPE	4
1.2 NOMENCLATURE	4
1.3 REFERENCED DOCUMENTS	4
1.4 DEFINITIONS	4
SECTION 2. MATERIAL REQUIREMENTS AND WIRE PROPERTIES	
2.1 GENERAL	5
2.2 MATERIALS	5
2.3 WIRE PROPERTIES	5
SECTION 3. CONDUCTOR REQUIREMENTS	
3.1 CONSTRUCTION	9
3.2 IDENTIFICATION OF ALUMINIUM ALLOY CONDUCTORS	9
3.3 JOINTS IN WIRES OF CONDUCTORS	9
3.4 LAY	9
3.5 STANDARD SIZES AND CALCULATED PROPERTIES OF CONDUCTORS	9
SECTION 4. TESTS	
4.1 SELECTION OF TEST SPECIMENS	13
4.2 MECHANICAL TESTS	13
4.3 COATING TESTS	15
4.4 RESISTIVITY TEST	15
4.5 LAY RATIO	16
4.6 PLACE OF TESTING	16
4.7 INSPECTION	16
4.8 TEST CERTIFICATE	16
SECTION 5. PACKING AND MARKING	
5.1 PACKING	17
5.2 MARKING	17
APPENDICES	
A CALCULATION OF CONDUCTOR PROPERTIES	18
B CALCULATION OF MODULUS OF ELASTICITY AND COEFFICIENT OF LINEAR EXPANSION	20
C A CONTINUITY OF COATING TEST FOR ALUMINIUM COATED STEEL	22
D DETERMINATION OF MASS OF ALUMINIUM COATING	23
E CODE NAMES FOR ALUMINIUM AND ALUMINIUM ALLOY CONDUCTORS, STEEL REINFORCED	24
F ITEMS TO BE SPECIFIED BY THE PURCHASER OR SUBJECT TO AGREEMENT BETWEEN THE PURCHASER AND MANUFACTURER	25

STANDARDS AUSTRALIA

Australian Standard

Conductors—Bare overhead, aluminium and aluminium alloy—Steel reinforced

SECTION 1. SCOPE AND GENERAL

1.1 SCOPE. This Standard specifies requirements and tests for composite bare electrical conductors for overhead power transmission purposes, incorporating aluminium or aluminium alloy wires and steel wires in their construction.

1.2 NOMENCLATURE. Aluminium and aluminium alloy conductors steel reinforced covered by this Standard include the following types, with the code for each in parentheses:

- (a) Aluminium 1350, zinc-coated (galvanized) steel reinforced (ACSR/GZ)².
- (b) Aluminium 1350, aluminium-coated (aluminized) steel reinforced (ACSR/AZ)².
- (c) Aluminium 1350, aluminium-clad steel reinforced (ACSR/AC)².
- (d) Aluminium alloy 1120, zinc-coated (galvanized) steel reinforced (AACSR/GZ/1120).
- (e) Aluminium alloy 1120, aluminium-coated (aluminized) steel reinforced (AACSR/AZ/1120).
- (f) Aluminium alloy 1120, aluminium-clad steel reinforced (AACSR/AC/1120).
- (g) Aluminium alloy 6201A, zinc-coated (galvanized) steel reinforced (AACSR/GZ/6201)³.
- (h) Aluminium alloy 6201A, aluminium-coated (aluminized) steel reinforced (AACSR/AZ/6201)³.
- (i) Aluminium alloy 6201A, aluminium-clad steel reinforced (AACSR/AC/6201)³.

NOTES:

1. A list of code names which may be used to refer to a specific type and construction of conductor is given in Appendix E.
2. An additional suffix may be used, as follows: '1350' for (a), (b) and (c).
3. The suffix 'A' has been omitted from the conductor code for (g), (h) and (i).

1.3 REFERENCED DOCUMENTS. The following documents are referred to in this Standard:

AS	
1391	Methods for tensile testing of metals
1442	Carbon steels and carbon-manganese steels — Hot-rolled bars and semi-finished products
1650	Galvanized coatings
1852	International electrotechnical vocabulary
2505	Methods for bend and related testing of metals
2507	Part 3: Torsion and wrapping tests on wire
2584	Aluminium and aluminium alloys — Compositions and designations
2838.1	Part 1: Wrought products
2857	Timber drums for insulated electric cables and bare conductors
C365	Drums for bare stranded conductors
C365.II	Part II: Metal drums

IEC

468 Methods of measurement of resistivity of metallic materials

ASTM

D 566 Dropping point of lubricating grease

1.4 DEFINITIONS. For the purpose of this Standard, the definitions in AS 1852 and those below apply.

1.4.1 Wire — A solid circular component from which stranded conductor is constructed.

1.4.2 King wire — a central core wire having a nominal diameter larger than that of the surrounding wires.

1.4.3 Conductor — a finished circular stranded conductor consisting of seven or more wires laid up together.

1.4.4 Diameter — the mean of two measurements at right angles taken at any one cross-section.

1.4.5 Direction-of-lay — the direction of lay is defined as right-hand or left-hand, as follows:

- (a) Right-hand lay — the slope of the wires is in the direction of the central part of the letter Z when the conductor is held vertically.
- (b) Left-hand lay — the slope of the wires is in the direction of the central part of the letter S when the conductor is held vertically.

1.4.6 Lay ratio — the ratio of the axial length of a complete turn of the helix formed by an individual wire in a conductor, to the external diameter of the helix.

1.4.7 Breaking load — the maximum load obtained in a tensile test.

1.4.8 Ultimate tensile stress — the breaking load divided by the original cross-sectional area of the test wire.

1.4.9 Ungreased conductor — a conductor which is dry and free from grease, other than a light residue of wire drawing lubricant that may be on the wires.

1.4.10 Partly greased conductor — a conductor of more than seven wires in which grease is applied only to the steel portion.

1.4.11 Fully greased conductor — a conductor in which grease is applied to all wires with the exception of the outermost layer.

1.4.12 Surface fracture — a crack on the surface of a wire visible to an observer with normal or corrected vision.

1.4.13 Spool — a container of wire which is to be installed on a stranding machine to manufacture the conductor.