

Australian Standard™

**Insulators—Porcelain stay type—
Voltages greater than 1000 V a.c.**

This Australian Standard was prepared by Committee EL-010, Overhead Lines. It was approved on behalf of the Council of Standards Australia on 23 May 2005. This Standard was published on 14 June 2005.

The following are represented on Committee EL-010:

Australasian Railway Association
Australian Chamber of Commerce and Industry
Australian Electrical and Electronic Manufacturers Association
Australian Porcelain Insulators Association
Electricity Engineers Association (New Zealand)
Energy Networks Association

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Web Shop at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

Australian Standards™ and other products and services developed by Standards Australia are published and distributed under contract by SAI Global, which operates the Standards Web Shop.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.org.au, or write to the Chief Executive, Standards Australia, GPO Box 5420, Sydney, NSW 2001.

Australian Standard™

**Insulators—Porcelain stav type—
Voltages greater than 1000 V a.c.**

Original standard S 137.4—1972.
Previous edition AS 3609—1989.
Second edition 2005.

COPYRIGHT

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia, GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 6774 5

PREFACE

This Standard was reviewed by the Australian members of the Joint Standards Australia/Standards New Zealand committee EL-010, Overhead Lines. After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to republish this Australian Standard without technical alterations. There are minor editorial changes and cross-references to referred Standards have been updated.

The Standard applies to porcelain stay insulators, used in conjunction with stay wires and it deals with general requirements, characteristics and methods of test.

The terms 'normative' and 'informative' have been used in this Standard to define the application of the appendix to which they apply. A 'normative' appendix is an integral part of a Standard, whereas an 'informative' appendix is only for information and guidance.

CONTENTS

	<i>Page</i>
1 SCOPE AND GENERAL	4
2 GENERAL REQUIREMENTS FOR TESTS.....	5
3 TESTS—TYPE, SAMPLE, AND ROUTINE	6
4 STANDARD CHARACTERISTICS	8

APPENDICES

A MECHANICAL STRENGTH RATINGS OF INSULATOR AND STAY WIRE COMBINATIONS.....	12
B ITEMS TO BE SPECIFIED BY THE PURCHASER OR SUBJECT TO AGREEMENT BETWEEN THE PURCHASER AND MANUFACTURER	13

STANDARDS AUSTRALIA

Australian Standard

Insulators—Porcelain stay type—Voltages greater than 1000 V a.c.

1 SCOPE AND GENERAL**1.1 Scope**

This Standard specifies requirements for porcelain stay insulators as defined in Clause 1.3.1 and which are incorporated with the stay wires used for poles supporting overhead lines.

NOTE: Appendix B lists information that should be specified by the purchaser of the insulators.

1.2 Referenced documents

The following documents are referred to in this Standard.

AS

1222 Steel conductors and stays—Bare overhead

1222.1 Part 1: Galvanized (SC/GZ)

1931 High-voltage test techniques

1931.1 Part 1: General definitions and test requirements

1.3 Definitions

For the purpose of this Standard the definitions below apply.

1.3.1 Stay insulator

Insulator consisting of one part, with two transverse holes for the insertion of stay wires and hereafter referred to as ‘insulator’.

1.3.2 Power-frequency wet flashover voltage

Arithmetic mean value of the measured voltages which cause flashover of the insulator under the conditions prescribed in Clause 2.2.

1.3.3 Flashover

Disruptive discharge external to the insulator, connecting those parts which normally have the operating voltage between them.

NOTE: In this Standard the term ‘flashover’ includes a flashover across the insulator surface as well as disruptive discharge by sparkover through air adjacent to the insulator.

1.3.4 Mechanical failing load

Maximum mechanical load at which failure occurs in an insulator when tested under the prescribed conditions.

1.3.5 Lot

Group of insulators offered for acceptance from the same manufacturer, of the same design, and manufactured under similar conditions of production.