

AS 3610 Supplement 2—1996

**Formwork for concrete—Commentary
(Supplement No. 2 AS 3610—1995)**

This Australian Standard supplement was prepared by Committee BD-043, Formwork. It was approved on behalf of the Council of Standards Australia on 18 October 1996 and published on 5 December 1996..

The following are represented on Committee BD-043:

Association of Consulting Engineers Australia
Australian Aluminium Council
AUSTROADS
Cement and Concrete Association of Australia
Department of Training and Industrial Relations (Qld)
Formwork Contractors of W.A.
Housing Industry Association
Metal Trades Industry Association of Australia
National Precast Concrete Association Australia
Plywood Association of Australia
Queenland University of Technology
WorkCover New South Wales
WorkSafe Western Australia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To remain in their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

AS 3610 Supplement 2—1996

Formwork for concrete—Commentary (Supplement No. 2 AS 3610—1995)

Originated as AS 3610 Supplement 2—1990.
Second edition 1996.
Reissued incorporating Amendment No. 1 (March 2003).

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 0816 1

PREFACE

This Supplement was prepared by the Standards Australia Committee BD-043 on Formwork as a commentary on AS 3610—1995, *Formwork for concrete*.

This new edition of this supplement incorporates several corrections and amendments to the previous edition. These include changes to Clauses C2.3, C3.2, C3.3.1, C3.5.1, C3.5.2, C4.4.3, C4.4.5.1, C4.4.5.2, C4.4.5.3, C4.4.5.7, C4.4.6, C4.4.7, C4.5.4.1, C4.5.5.1, C4.6.3, C4.7.1, C5.4.1.4, C5.4.1.7, C5.4.2, C5.6.2.2 and CA3.1; Paragraph CA4.4.4; Figures C4.1, C4.4.4, C4.4.5, C4.4.7, C4.4.8, C4.4.9, C4.4.10, C4.4.11, C5.4.1, C5.4.5, C5.4.7, C5.4.12, C5.4.15, CA1 and Addendum. The changes required by this Amendment are indicated in the text by a marginal bar and amendment number against the clause, note, table, figure, or part thereof affected.

This Standard incorporates Amendment No. 1 (March 2003). The changes required by the Amendment are indicated in the text by a marginal bar and amendment number against the clause, note, table, figure or part thereof affected.

The Supplement includes background information on the Standard, guidance on its use and suggestions on good practice.

The Paragraphs in this Commentary refer directly to the respective clauses in the Standard, e.g. Paragraph C5.3.1 refers to Clause 5.3.1, and Appendix CA refers to Appendix A. Gaps in the numerical sequence of this Commentary's Paragraph numbering means that no explanation of or background to the relevant Clauses is necessary.

Details on references and documents referred to in the Supplement are provided in the Addendum at the end of the document.

CONTENTS

	<i>Page</i>
FOREWORD	4
SECTION C2 THE PROJECT DOCUMENTATION	
C2.3 INFORMATION TO BE PROVIDED IN THE PROJECT DOCUMENTATION	5
SECTION C3 SURFACE FINISH	
C3.2 APPLICATION.....	11
C3.3 CLASSES OF SURFACE FINISH.....	2
C3.4 PHYSICAL QUALITY	15
C3.5 COLOUR CONTROL OF UNTREATED SURFACES	19
C3.6 TEST PANELS	22
SECTION C4 STRUCTURAL DESIGN AND DOCUMENTATION	
C4.1 SCOPE OF SECTION.....	25
C4.2 APPLICATION OF SECTION	25
C4.3 DESIGN REQUIREMENTS	25
C4.4 LOADS	32
C4.5 ANALYSIS AND DESIGN	52
C4.6 CONSTRUCTION CONSIDERATIONS.....	57
C4.7 FORMWORK DOCUMENTATION	58
SECTION C5 CONSTRUCTION	
C5.1 SCOPE OF SECTION.....	61
C5.3 GENERAL FORMWORK REQUIREMENTS—IN SITU CONCRETE	61
C5.4 FORMWORK CONSTRUCTION—IN SITU CONCRETE	70
C5.5 FORMWORK CONSTRUCTION—PRECAST CONCRETE	84
C5.6 EVALUATION OF COMPLETED WORK AND REPAIRS.....	86
APPENDIX CA COMMENTARY ON APPENDIX A, TESTING OF FORMWORK	92
ADDENDUM	98

FOREWORD

In this Commentary the terms ‘project designer’ and ‘formwork designer’ are used. Neither term should be taken as referring to a single individual, as each may comprise several organizations or individuals of varying qualifications.

Consider the following examples:

- (a) Within the term ‘formwork designer’—
 - (i) proprietary items used in the formwork assembly could be designed by the manufacturer;
 - (ii) forms, bearers and joists could be designed by personnel engaged by the formwork contractor; and
 - (iii) footings (if necessary) could be designed by personnel engaged by the building contractor.
- (b) Within the term ‘project designer’, a structural engineer could be responsible for the concrete structure, and an architect could be responsible for the surface finish.

STANDARDS AUSTRALIA

Australian Standard
Formwork for concrete—Commentary
(Supplement No. 2 AS 3610—1995)

SECTION C2 THE PROJECT
DOCUMENTATION

C2.3 INFORMATION TO BE PROVIDED IN THE PROJECT DOCUMENTATION

It is necessary for the project designer, through the project documentation, to communicate specific requirements. The list given in Clause 2.3 is only a general list. For particular projects many other aspects may require attention, with appropriate limitations on the formworker's actions being specified. This Clause covers only those matters affecting the structural aspects of the concrete. The quality of the surface finish is discussed in the commentary to Section 3: Surface finish.

- (a) *Minimum formwork stripping times* This is primarily directed towards in situ concrete, although much of it can apply to precast concrete. The stripping times provided in the formwork documentation should be in accordance with AS 3600 (see also Clause 5.4.3.2).

Three criteria apply generally to the removal of all forms and their supports, as follows:

- (i) *Structural* As a structure, the member needs to remain secure from collapse, and from damage that may affect its performance in later service, e.g. cracking or deformation in excess of that anticipated by the project designer.
- (ii) *Surface finish* Premature stripping may adversely affect the surface condition through scaling, spalling of edges or corners, or cause non-uniformity of colour.
- (iii) *Durability* An important factor in the achievement of optimum durability is adequate hydration. As economic considerations often call for early stripping, attention to curing is vital.

A controlling factor in these three matters is the strength development of the concrete at early ages, which is in turn related to the rate of hydration of the cement.

Although strength development is influenced by the ambient humidity, most recommended models for strength gain are related only to time and temperature. Figure C2.1 (see Ref. 1) shows the variations of strength growth with temperature.

It is recommended that the specification should state the minimum strength of the concrete to be attained before removal of the forms or shores. An effective method of strength determination is the testing of cylinders, stored and cured under the same conditions as the permanent structure, or non-destructive tests of the in-place concrete. In this way the effect of the actual temperature regime is reflected in the test results.