

# Australian Standard<sup>®</sup>

AS 3706.4—2012

## Geotextiles—Methods of test

### Method 4: Determination of burst strength—California bearing ratio (CBR)—Plunger method

#### FOREWORD

This test is a means of judging the resistance of geotextiles to puncture forces, for example from aggregate placed and compacted during road construction. It utilizes the California bearing ratio (CBR) apparatus and principles of the method, to determine burst strength of the geotextile and an approximate indication of the resulting strain.

#### METHOD

##### 1 SCOPE

This Standard sets out the method for determining the burst strength and deformation properties of geotextiles using the California bearing ratio (CBR) test apparatus for both atmospheric-conditioned and wet-conditioned specimens.\*

##### 2 APPLICATION

This Method is generally applicable to non-woven and composite geotextiles, and may also be used for geomembranes. It may be used for woven fabrics but, if the material is anisotropic, care should be taken in the interpretation of the results.

##### NOTES:

- 1 Being a burst test (the load applied normal to the plane of the specimen), this Method is specifically applicable to isotropic geotextiles. Where composite fabrics are tested, the face of the fabric that is to be tested needs to be specified.
- 2 This Method may not be suited for some woven fabrics with high tensile strengths exceeding approximately 200 N/m because of clamping and equipment limitations.

##### 3 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS	
1289	Methods of testing soil for engineering purposes
1289.6.1.1	Method 6.1.1: Soil strength and consolidation tests—Determination of the California Bearing Ratio of a soil—Standard laboratory method for a remoulded specimen

\* This method is based on DIN 54307, *Testing of textiles; plunger puncture test (CBR)*. The equipment has been modified to allow the use of a CBR mould that would normally be available in soil-testing laboratories.