

Australian Standard™

**Guide to the properties of paints for
buildings**

**Part 15: Primer—Latex—For metallic
zinc surfaces**

STANDARDS
Australia



This Australian Standard was prepared by Committee CH-003, Paints and Related Materials. It was approved on behalf of the Council of Standards Australia on 21 December 2005.
This Standard was published on 2 February 2006.

The following are represented on Committee CH-003:

AUSTROADS

Australian Paint Approval Scheme
Australian Paint Manufacturers Federation
Master Painters Australia
National Association of Testing Authorities Australia
Surface Coatings Association Australia
Telstra Corporation
Water Corporation Western Australia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Web Shop at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

Australian Standards and other products and services developed by Standards Australia are published and distributed under contract by SAI Global, which operates the Standards Web Shop.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.org.au, or write to the Chief Executive, Standards Australia, GPO Box 476, Sydney, NSW 2001.

This Standard was issued in draft form for comment as DR 03607.

Australian Standard™

**Guide to the properties of paints for
buildings**

**Part 15: Primer—Latex—For metallic
zinc surfaces**

Originally as AS 3730.15—1991.
Second edition 2006.

COPYRIGHT

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia GPO Box 476, Sydney, NSW 2001, Australia

ISBN 0 7337 7208 0

PREFACE

This Standard was prepared by the Australian members of the Joint Standards Australia/Standards New Zealand Committee CH-003, Paints and Related Materials, to supersede AS 3730.15—1991, *Guide to the properties of paints for buildings, Part 15: Primer—Latex—For metallic zinc surfaces*. After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this as an Australian, rather than an Australian/New Zealand Standard.

The AS 3730 series has been prepared as guides to the range of frequently used paints for buildings which are air-dried and generally applied on site. These guides include features of each product type and typical product characteristics. Typical product characteristics are to be taken as a guide only and are not mandatory. Because a product is used as part only of an overall painting system, the AS 3730 guides should not be used as a substitute for a detailed painting specification from the manufacturer, based on AS/NZS 2311:2000, *Guide to the painting of buildings*. Successful specifications are based on the proven performance of the total paint system, and not on the characteristics of individual paint products in isolation.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the appendix to which they apply. A ‘normative’ appendix is an integral part of a Standard, whereas an ‘informative’ appendix is only for information and guidance.

CONTENTS

	<i>Page</i>
FOREWORD.....	4
1 SCOPE.....	5
2 REFERENCED DOCUMENTS.....	5
3 DEFINITIONS.....	5
4 OCCUPATIONAL HEALTH AND SAFETY.....	5
5 TYPICAL PROPERTIES AND CHARACTERISTICS.....	5
6 PACKAGING.....	9
7 LABELLING.....	9
APPENDICES	
A LIST OF REFERENCED DOCUMENTS.....	10
B PREPARATION OF TEST PANELS FOR TESTING OF RESISTANCE TO WEATHERING.....	11

FOREWORD

Latex primers characterized by this guide are suitable for use metallic zinc surfaces.

Latex primers produce little odour during application and drying. As the paint is fast drying, painted areas can be recoated within a few hours of application.

Before painting, surfaces should be prepared in accordance with the manufacturer's instructions or the appropriate section of AS/NZS 2311.

Currently in preview, click buy full version

STANDARDS AUSTRALIA

Australian Standard

Guide to the properties of paints for buildings

Part 15: Primer—Latex—For metallic zinc surfaces

1 SCOPE

This document provides a guide to the features and typical properties that are expected of a water-borne latex, primer paint for interior and exterior use on zinc and zinc alloy surfaces (e.g., galvanized iron) when applied by brush, roller or spray, in accordance with manufacturer's instructions.

Paints covered by this guide are classified as Paint Type B12A of AS/NZS 2310.

The guide deals with primers that are to be further coated with latex paints or solvent-borne paints.

2 REFERENCED DOCUMENTS

The documents referred to in this guide are given in Appendix A.

3 DEFINITIONS

For the purpose of this guide, the definitions given in AS/NZS 2310 apply.

4 OCCUPATIONAL HEALTH AND SAFETY

Refer manufacturer's Materials Safety Data Sheet before using these paints.

5 TYPICAL PROPERTIES AND CHARACTERISTICS

NOTE: Table 1 provides a summary of typical properties.

5.1 Composition

The primer should consist essentially of pigments, extenders and latex binders in aqueous suspension. The product should meet the requirements of the Standard for the Uniform Scheduling of Drugs and Poisons, issued by the National Drugs and Poisons Schedule Committee.

5.2 Conditions of test

Unless otherwise indicated, the recommendations in this guide apply to products that are tested as follows:

- a) The test panel material is a piece of standard grade hardboard in accordance with AS/NZS 1580.104.1 sealed with one coat of the paint under test thinned 5 percent with water and dried for at least 24 h. Where reference panels are required, they should be made of the same material as the test panels and should be prepared by identical methods at the same time as the test panels.
- (b) The size of test panels is specified in Table 1 for the appropriate test.
- (c) The method of application for test purposes is by brush.
- (d) The spreading rate of the paint should be as specified by the manufacturer, typically 16 m²/L.