

WITHDRAWN June 1992.

Superseded by AS 2345-1992

AS 3796 (Int)—1990  
Expires 27 July 1992

Interim Australian Standard<sup>®</sup>

---

**Dezincification resistance of copper alloys**

---



STANDARDS AUSTRALIA

This Interim Australian Standard was prepared by Committee WS/—, Water Supply Sewerage and Drainage Standards Board. It was approved on behalf of the Council of Standards Australia on 8 August 1990 and published on 12 November 1990.

---

The following interests are represented on Committee WS/—:

ACT Electricity and Water  
AUSTAP  
Australian Institute of Building  
Australian Valve Manufacturers Association  
Board of Works, Melbourne  
Brisbane City Council  
Confederation of Australian Industry  
Department of Administrative Services—Australian Construction Services  
Department of Conservation and Environment, Victoria  
Division of Building, Construction and Engineering, CSIRO  
Engineering and Water Supply Department, South Australia  
Federated Master Plumbers of Australia  
Hobart City Council  
Hunter Water Board  
Institution of Engineers, Australia  
Institute of Plumbing, Australia  
Public Works Department, New South Wales  
Royal Australian Institute of Architects  
The Plastics Industry Association  
Water Authority of Western Australia  
Water Board, Sydney—Murrumbidgee—Blue Mountains  
Water Resources Commission, Queensland  
Western Australian Branch Committee

---

*Review of Australian Standards.* To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

---

Interim Australian Standard<sup>®</sup>

---

**Dezincification resistance of copper alloys**

---

AS 3796 (Int) first published as part of  
SAA MP52—1988.  
Second edition 1990.  
SAA MP52—1990 revised and redesignated in part as  
AS 3796 (Int)—1990.

## PREFACE

This interim Standard was prepared under the direction of the Water Supply Sewerage and Drainage Standards Board, to supersede in part Specification 016 in SAA MP52—1990, *Manual of authorization procedures for plumbing and drainage products*.

The information contained in this interim Standard was developed by Corrotec, Metallurgical Consultants for Brisbane City Council, who have made the information available on a nationwide basis. Standards Australia invites comment on this interim Standard from persons and organizations concerned with this subject. The date of expiry for comment is 27 July 1992 at which time this interim Standard will either be withdrawn or revised in the light of public comment, with the view to the preparation of an Australian Standard.

During the life of this document, Committee MT/14 will monitor all comment or field data and when it is received.

Attention is drawn to the fact that this document is an interim Australian Standard only and should be regarded as a draft Standard and hence liable to alteration after the expiry date.

This document is not to be regarded as an Australian Standard until issued as such by Standards Australia.

## CONTENTS

	<i>Page</i>
1 SCOPE .....	3
2 REFERENCED DOCUMENTS .....	3
3 MATERIAL REQUIREMENTS .....	3
4 PRODUCT REQUIREMENTS .....	3
APPENDIX A ALLOY CATEGORIES FOR DEZINCIFICATION ASSESSMENT ACCORDING TO CHEMICAL COMPOSITION .....	4

### © Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the Head Office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

## STANDARDS AUSTRALIA

**Interim Australian Standard**  
**Dezincification resistance of copper alloys**

**1 SCOPE** This interim Standard specifies requirements for dezincification-resistant copper alloys.

**2 REFERENCED DOCUMENTS** The following documents are referred to in this interim Standard:

AS

1565 Copper and copper alloys—Ingots and castings

1567 Copper and copper alloys—Wrought rods, bars and sections

2345 An accelerated laboratory test method for assessment of the susceptibility of brass to dezincification

2738 Copper and copper alloys, compositions and designations

2738.2 Part 2: Wrought products

2738.3 Part 3: Cast products

**3 MATERIAL REQUIREMENTS** Dezincification-resistant copper alloys are those alloys that either—

- (a) correspond in chemical composition to those alloys designated Category I alloys in Appendix A; or
- (b) when tested in accordance with AS 2345, satisfy the average depth of penetration criteria given in Table 1.

**4 PRODUCT REQUIREMENTS**

**4.1 Acceptance based on composition of alloy** Alloy composition, when NATA certified, shall be taken as the acceptance criterion. Where the alloy composition corresponds to that of—

- (a) Category I alloys (see Appendix A, Table A1), acceptance shall be without further testing;
- (b) Category II materials (see Appendix A, Table A2), testing in accordance with AS 2345 shall be carried out. Acceptance shall be based on the average depth of penetration being not greater than the values given in Table 1; or
- (c) Category III materials (see Appendix A, Table A3), they will not be accepted.

**4.2 Acceptance based on depth of penetration** Where alloy composition does not correspond to the Categories I, II or III, testing shall be carried out in accordance with AS 2345 for compliance with the acceptance criteria given in Table 1.

**TABLE 1**  
**DEPTH OF PENETRATION CRITERIA FOR ACCEPTANCE OF COPPER-BASE ALLOYS WHEN TESTED IN ACCORDANCE WITH AS 2345**

Form of product	Average depth limit, μm
Castings—thin and thick sections	100
Forgings—	300
	100
Machined items from extruded rod—	300
	100

**NOTES:**

- 1 Any brazing performed during manufacture or installation may change the dezincification-resistance properties of the product.
- 2 Where reheating processes are a necessary part of manufacture, e.g. fabrication by brazing or where temperatures may exceed 600°C, then the relevant depth criteria above may be increased by 100 μm.
- 3 The maximum depth of dezincification should not exceed 400 μm at any measured point.
- 4 Dezincification resistance may be assessed on the fitting after all manufacturing procedures are completed but prior to installation in the field.