

Australian Standard[®]

**Methods for the analysis of
copper, lead, zinc, gold and
silver ores**

**Part 1: Determination of gold
(Fire assay—Flame AAS method)**

This Australian Standard was prepared by Committee MN/5, Copper, Lead, Zinc, Gold and Silver Ores and Concentrates. It was approved on behalf of the Council of Standards Australia on 9 April 1991 and published on 10 June 1991.

The following interests are represented on Committee MN/5:

Australian Institute of Mining and Metallurgy
Australian Lead Development Association
Australian Mining Industry Council
CSIRO, Division of Mineral and Process Engineering
Royal Australian Chemical Institute

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications. This information is supplemented each month by the magazine 'The Australian Standard', which subscribers receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 90016.

Australian Standard[®]

**Methods for the analysis of
copper, lead, zinc, gold and
silver ores**

**Part 1: Determination of gold
(Fire assay—Flame AAS method)**

First published as AS 3895.1—1991.

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 6882 8

PREFACE

This Standard was prepared by the Standards Australia Committee on Copper, Lead, Zinc, Gold and Silver Ores and Concentrates under the direction of the Minerals Standards Board as part of its program of standardizing methods for determination of elements of commercial interest in such materials.

The accurate determination of gold in ores is vital in the economic evaluation of new and existing ore bodies as the gold value can determine if an ore body is commercially viable. Hence it was considered important that a standard method for determination of gold in ores with precision data be prepared.

Fire assay collection remains an important method for determination of precious metals in non-ferrous ores and concentrates.

CONTENTS

	<i>Page</i>
1 SCOPE	3
2 REFERENCED DOCUMENTS	3
3 PRINCIPLE	3
4 REAGENTS	3
5 APPARATUS	4
6 PROCEDURE	4
7 CALCULATION	5
8 TREATMENT OF ANALYTICAL VALUES	6
9 PRECISION	6
10 TEST REPORT	6

APPENDICES

A TRIAL FUSION AND FLUX FORMULATION	7
B BLANK DETERMINATION	9
C RESIDUES TREATMENT PROCEDURE	9
D FLOWSHEET OF THE PROCEDURE FOR THE ACCEPTANCE OF ANALYTICAL VALUES FOR TEST SAMPLES	10
E PARTICIPATING LABORATORIES	11

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS AUSTRALIA

Australian Standard

Methods for the analysis of copper, lead, zinc, gold and silver ores

Part 1: Determination of gold (Fire assay—Flame AAS method)

1 SCOPE This Standard sets out a fire assay collection and flame atomic absorption spectrometric finish method for the determination of gold content in copper, lead, zinc, gold and silver ores.

The method is applicable to the determination of gold contents from 0.1 g/t to 25 g/t in a range of gold bearing ores.

2 REFERENCED DOCUMENTS The following documents are referred to in this Standard:

AS

1152 Test sieves

2134 Recommended practice for chemical analysis by atomic absorption spectrometry

2134.1 Part 1: Flame atomic absorption spectrometry

2162 Code of practice for the use of volumetric glassware

2816 Copper, lead and zinc sulphide concentrates — Determination of microscopic moisture in the analysis sample

2850 Chemical analysis — Interlaboratory test programs — For determining precision of analytical method(s) — Guide to the planning and conduct

3 PRINCIPLE Fire assaying for the determination of gold comprises a reducing fusion in which two phases, a complex liquid borosilicate slag and a liquid lead phase, are formed. The lead phase collects the precious metals and the gangue elements are separated into the slag. The great differences in relative density between the lead and the slag allow easy separation after solidification. The second stage involves cupellation (oxidizing fusion) with silver acting as a collector for gold: in this process lead is oxidized to lead oxide and absorbed into a porous vessel known as a cupel, leaving the precious metal bead separated for analysis by dissolution and flame atomic absorption spectrometry.

4 REAGENTS

4.1 General requirements Unless otherwise specified, all reagents shall be of a recognized analytical reagent grade and distilled or deionized water shall be used throughout.

4.2 Sodium carbonate — anhydrous.

4.3 Litharge — assay reagent grade with gold content such as to conform with the total blank constraint of Appendix B.

4.4 Silica — precipitated grade.

4.5 Borax — fused anhydrous sodium tetraborate (borax glass powder).

4.6 Plain white flour

4.7 Lead foil — assay reagent grade with gold content such as to conform with the total blank constraint of Appendix B. Foil approximately 0.15 mm thick is suitable.

4.8 Silver wire — 99.99 percent silver.

4.9 Gold wire — 99.99 percent gold.

4.10 Hydrochloric acid — (ρ_{20} 1160 kg/m³ to 1190 kg/m³).

4.11 Dilute nitric acid (170 mL/L) To 800 mL of water carefully add, with stirring, 170 mL of nitric acid (ρ_{20} 1420 kg/m³). Cool, dilute to 1 L with water and mix.

4.12 Dilute nitric acid (700 mL/L) To 200 mL water carefully add, with stirring, 700 mL of nitric acid (ρ_{20} 1420 kg/m³). Cool, dilute to 1 L with water and mix.

4.13 Aqua regia solution To 50 mL of nitric acid (ρ_{20} 1420 kg/m³) carefully add, with stirring, 150 mL of hydrochloric acid (4.10). Prepare freshly before use.

4.14 Ammonia solution To 250 mL of ammonia solution (ρ_{20} 880 kg/m³), carefully add, with stirring, 250 mL of water.