

AS 4023—1992
Reconfirmed 2016

Australian Standard[®]

**Non-vitreous china used in
sanitary appliances**

This Australian Standard was prepared by Committee WS/3, Sanitary Plumbing Fixtures. It was approved on behalf of the Council of Standards Australia on 12 March 1992 and published on 15 May 1992.

The following interests are represented on Committee WS/3:

Australian Chamber of Manufactures
Australian Consumers Association
Brisbane City Council
Confederation of Australian Industry
Department of Health, N.S.W.
Engineering and Water Supply Department, S.A.
Housing Industry Association of Australia
Hunter Water Board, N.S.W.
Melbourne Water
Metal Trades Industry Association of Australia
Public Works Department, N.S.W.
Stainless Steel Products Manufacturers Association
Water Authority of Western Australia
Water Board, Sydney, Illawarra, Blue Mountains
Water Resources Commission, Qld

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments, etc.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 91135.

STANDARDS AUSTRALIA

RECONFIRMATION

OF

AS 4023—1992

Non-vitreous china used in sanitary appliances

RECONFIRMATION NOTICE

Technical Committee WS-003 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 30 September 2016.

The following are represented on Technical Committee WS-003:

Association of Accredited Certification Bodies
Australian Chamber of Commerce and Industry
CSIRO
Department of Agriculture and Water Resources (Australian Government)
Plastics New Zealand
Plumbing Distributors Association of New Zealand
Plumbing Products Industry Group
Testing Interests (Australia)

NOTES

Currently in preview, click buy full vers.

Australian Standard[®]

**Non-vitreous china used in
sanitary appliances**

First published as AS 4023—1992.

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 7444 5

PREFACE

This Standard was prepared by the Standards Australia Committee on Sanitary Plumbing Fixtures at the request of the water authorities. The Standard deals with the quality of non-vitreous china and details the tests by which that quality may be assessed. Requirements for vitreous china used in sanitary appliances are given in AS 1976.

 CONTENTS

	<i>Page</i>
1 SCOPE	3
2 DEFINITIONS	3
3 GLAZING	3
4 SURFACE QUALITY	3
5 TESTS	3
 APPENDICES	
A TEST FOR WATER ABSORPTION	5
B TEST FOR CRAZING	6
C TEST FOR CHEMICAL RESISTANCE	7

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS AUSTRALIA

Australian Standard

Non-vitreous china used in sanitary appliances

1 SCOPE This Standard specifies the quality of non-vitreous china for use in sanitary appliances, excluding water closet pans, water closet cisterns, slop-hoppers, bidets and urinal appliances and details the tests by which that quality shall be assessed.

2 DEFINITIONS For the purpose of this Standard, the definitions below apply.

2.1 Blister — a raised projection of the surface having a height or width greater than 1 mm.

2.2 Crazeing — cracks in the glaze.

2.3 Discolouration — a coloured spot over 6 mm maximum dimension, or a concentrated number of specks or spots that give the effect of a change in colour.

2.4 Finish — the texture and condition of a surface other than its colour.

2.5 Fire crack — a visible area crack in the body not covered with glaze in the visible area.

2.6 Grouping — a number of spots, blisters, pinholes, or specks within any pottery square.

2.7 Non-vitreous china — ceramic materials made from a mixture of clays and other materials and known as semi-vitreous (0.6 to 8% absorption), course-fireclay (8 to 15% absorption) and fine fireclay (8 to 15% absorption), (see Clause 5.2).

2.8 Pinhole — a hole in the glazed surface not greater than 0.5 mm.

2.9 Polishing mark — a spot, not greater than 10 mm maximum dimension, where a minor blemish has been ground off and the surface polished.

2.10 Pottery square — a square of side 50 mm, i.e. an area of 2500 mm².

2.11 Speck — an area of contrasting colour less than 1 mm maximum dimension. Specks less than 0.3 mm maximum dimension do not constitute a defect unless sufficient in number to form a discolouration.

2.12 Spot — an area of contrasting colour greater than 1 mm maximum dimension.

2.13 Visible surface — the surface that is readily visible, after installation of an appliance, to an observer in a normal standing position.

2.14 Wavy finish — a defect in the finish that has the appearance of numerous runs in the glaze; an irregular or mottled finish.

2.15 Normative — an appendix which is essential to the understanding or implementation of the Standard.

3 GLAZING The glaze shall be thoroughly fused to the body.

4 SURFACE QUALITY When viewed from a distance of between 500 mm and 600 mm with a surface illumination of not less than 50 lx, the surface defects shall not be in excess of those given in Table 1.

TABLE 1
MAXIMUM NUMBER OF BLEMISHES OR DEFECTS

Wavy finish	None
Warpage	Not noticeably warped
Discolouration	None
Spots, blisters, or pinholes	A total of not more than three, and no grouping
Bubbles or specks	A total of not more than five, and not more than three in one pottery square
Polishing marks	Only one; none permitted for coloured appliances
Dull or eggshell finish	Not permitted
Fire cracks	Not permitted

5 TESTS

5.1 Application of tests Each of the tests listed in Clauses 5.2 to 5.4 shall be carried out on an appliance of current production, selected as it is drawn from the exit kiln and the results recorded.