

Australian Standard™

Coal preparation

**Part 2.2: Higher rank coal—Froth
flotation—Sequential procedure**

This Australian Standard was prepared by Committee MN/1, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 10 July 1998 and published on 5 September 1998.

The following interests are represented on Committee MN/1:

Australasian Institute of Mining and Metallurgy
Australian Coal Association
Australian Coal Preparation Society
Australian Institute of Energy
Bureau of Steel Manufacturers of Australia
Coalfield Geology Council of New South Wales
CSIRO, Division of Energy Technology
Department of Mines and Energy, Queensland
Electricity Supply Association of Australia
Institution of Engineers, Australia
Minerals Council of Australia
Royal Australian Chemical Institute
University of Newcastle
University of New South Wales
University of Queensland

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 97517.

Australian Standard™

Coal preparation

**Part 2.2: Higher rank coal—Froth
flotation—Sequential procedure**

Originated as AS 4156.2.2—1994.
Second edition 1998.

PREFACE

This Standard was prepared by the Standards Australia Committee MN/1, Coal and Coke to supersede AS 4156.2.2—1994. It should be read in conjunction with AS 4156.2.1, *Coal preparation Part 2.1: Higher rank coal—Froth flotation—Basic test* which contains the basic test.

The objective of this Standard is to provide those conducting coal exploration programs with a comprehensive procedure that will allow a complete determination of the flotation characteristics of a coal.

The term 'informative' has been used in this Standard to define the application of the appendices to which it applies. An 'informative' appendix is for information and guidance only.

CONTENTS

	<i>Page</i>
FOREWORD	3
1 SCOPE	4
2 REFERENCED DOCUMENTS	4
3 DEFINITIONS	4
4 PRINCIPLE	4
5 SAMPLE	5
6 APPARATUS	5
7 FLOTATION CONDITIONS	5
8 PROCEDURE	5
9 CALCULATION OF RESULTS	6
10 REPORTING OF RESULTS	7
 APPENDICES	
A WORKED EXAMPLE OF CALCULATION OF RESULTS	8
B PRESENTATION OF RESULTS	12

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

FOREWORD

AS 4156.2.1 specifies apparatus, conditions and procedures for the preliminary assessment of the floatability of fine coals, and suggests a suitable form for the presentation of results. The procedure in AS 4156.2.1 gives only a semi-quantitative indication of the results that may be obtained in a practical industrial flotation process. It is recognized that flotation conditions may be changed in practice and scavenging or further cleaning stages employed to optimize product yield and quality. This Standard describes a procedure for the more complete determination of the flotation characteristics of a coal, using the apparatus and basic procedures described in AS 4156.2.1. The purpose of this extended procedure is to provide information similar to that provided by the sink/float curve, which is the basis for density separations. The data obtained are expressed as a yield-ash curve. The information can be used to define the limitations on the cleaning of coal by froth flotation.

Similar data may be obtained by other procedures*, but comparative test work has shown the recommended procedure to be the more generally applicable.

The procedures specified in this Standard are of practical significance in the development and evaluation of coal preparation plant flotation circuits, although the engineering design aspects, such as flotation kinetics and the selection of size and type of cell, are not addressed.

The flotation response curve (yield-ash curve) indicates the maximum possible yield at any specified ash level.

The procedure may be modified to test and compare the performance of different frother and collector types, the assessment of liberation by grinding, and the comparison of alternative feed size ranges. However, results of such tests should clearly indicate use of a non-standard procedure.

The general shape of the curve indicates the sensitivity of flotation performance to the nature of the coal and to operating conditions. By using the alternative Mayer curve presentation for the test results it is also possible to provide an indication of instantaneous ash at any point and of ash levels of secondary (middlings) products. Such information may be of significance in overall plant maximization and control.

* DELL, C.C. An improved release analysis procedure for determining coal washability. *J. Inst. of Fuel*, 1964, 37: 149-50.

CAVALLARO, J.A. and DEURBROUCK, A.W. Froth flotation washability data of various Appalachian coals using a timed release analysis technique. 1965 *U.S. Bureau of Mines RI* - 6652.

PRATEN, S.J., BENSLEY, C.N. AND NICOL, S.K. An evaluation of the flotation response of coals. *Int. J. of Miner. Process*, 1989, 27: 243-262.

STANDARDS AUSTRALIA

Australian Standard

Coal preparation

Part 2.2: Higher rank coal—Froth flotation—Sequential procedure

1 SCOPE This Standard sets out a laboratory sequential procedure for the froth flotation testing of fine coal, e.g. coal having a particle size of less than 0.5 mm. The procedure provides a means of evaluating for a coal the flotation characteristic (expressed as a yield-ash relationship) that may be expected from the froth flotation process.

Pulp samples that cannot be dewatered without the use of heat or chemical additives are not covered by this Standard; nor does it cover procedures for the investigation of flotation kinetics.

The test is not intended to provide plant design data.

This Standard should be read in conjunction with AS 4156.2.1.

2 REFERENCED DOCUMENTS The following documents are referred to in this Standard:

AS

- 1038 Coal and coke—Analysis and testing
- 1038.3 Part 3: Proximate analysis of higher rank coal
- 2096 Classification and coding systems for Australian coals
- 2418 Coal and coke—Glossary of terms
- 3881 Higher rank coal—Size analysis
- 4156 Coal preparation
- 4156.1 Part 1: Higher rank coal—Float and sink testing
- 4156.2.1 Part 2.1: Higher rank coal—Froth flotation—Basic test
- 4264 Coal and coke—Sampling
- 4264.1 Part 1: Higher rank coal—Sampling procedures

3 DEFINITIONS For the purpose of this Standard, the definitions given in AS 2418 and AS 4156.2.1, and that below, apply.

3.1 Higher rank coal (as defined in AS 2096)—coal having a gross specific energy of 21.00 MJ/kg or greater on an ash-free, moist (afm) basis *and* 27.00 MJ/kg or greater on a dry, ash-free (daf) basis.

4 PRINCIPLE A sequence of laboratory flotation tests is carried out on a single coal sample, using a procedure based on that described in AS 4156.2.1. Variations on that procedure are made to generate a number of products, by re-floating concentrates and tailings a number of times. The masses and ash percentages of the various products are used to construct a yield-ash curve showing the flotation response.