

AS 4470—1997  
ISO 1805:1973

Australian Standard<sup>®</sup>

---

**Fishing line—Determination of  
breaking load**

---

This Australian Standard was prepared by Committee CS/89, Testing of Fishing Line. It was approved on behalf of the Council of Standards Australia on 28 February 1997 and published on 5 May 1997.

---

The following interests are represented on Committee CS/89:

- Australian Chamber of Commerce and Industry
  - Australian National Sportfishing Association
  - Game Fish Association of Australia
  - N.S.W. Division Australian National Sportfishing Association
  - University of New South Wales
- 

**Review of Australian Standards.** To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, or of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made with the details in order that the matter may be investigated and appropriate action taken.

---

*This Standard was issued in draft form for comment as DR 96500.*

Australian Standard<sup>®</sup>

---

**Fishing line—Determination of  
breaking load**

---

First published AS 4470—1997.

## PREFACE

This Standard was prepared by the Standards Australia Committee CS/89 on Testing of Fishing Line. The Standard is based on and has been reproduced from, ISO 1805, *Fishing nets—Determination of breaking load and knot breaking load of netting yarns*.

Although the title of ISO 1805 has been amended to suit the intended use of the Standard for testing of fishing line, the scope and content are the same as ISO 1805. For fishing line testing, the clauses and method referring to ‘yarn breaking load’ rather than ‘knot breaking load’ should be followed. The term ‘netting yarns’ should be read as fishing line yarn or fishing line under these circumstances. Testing of fishing net can still be performed according to this Standard.

The Standard was written to provide a common ground for testing of competition fishing line by Australian Fishing Associations. The associations had all been using their own test methods and there was no means for comparison of breaking strength between competitions. In the process of considering this Standard, an attempt was made to align it with the method used by the International Game Fish Association (IGFA) which was based on US Government Specification CCC-T-191, Method 4102. The differences between the current methods used by the fishing associations and the method of the IGFA were too numerous to attempt an alignment. For example, the conditioning temperature, the time of pre-conditioning and the conversion of units from non-metric units introduced inconsistencies, so ISO 1805 was decided upon as a more suitable Standard.

The objective of this Standard is to provide testing bodies, fishing associations and competition fishermen with a uniform method of determining the breaking strength of fishing line, in order to enable the comparison of breaking strength results.

The term ‘normative’ has been used in this Standard to define the application of the appendix to which it applies. A normative appendix is an integral part of a Standard.

Appendix ZZ lists the Australian variations to ISO 1805. In the text of this Standard, marginal bars are added to the text wherever the requirements of the Standard have been varied to meet Australian requirements, and these variations are detailed in Appendix ZZ.

As this Standard is reproduced from an international Standard, the following applies:

- (a) Its number appears on the cover and title page while the International Standard number appears only on the cover.
- (b) In the source text, ‘this International Standard’ should read ‘this Australian Standard’.
- (c) A full point substitute for a comma when referring to a decimal marker.

References to International Standards should be replaced by equivalent Australian Standards, as follows:

<i>Reference to International Standard</i>	<i>Australian Standard</i>
ISO/IEC	AS
139 Textile — Standard atmospheres for conditioning and testing	2001 Methods of test for textiles 2001.1 Part 1: Conditioning procedures
858 Fishing nets—Designation of netting yarns in the Tex system	

## CONTENTS

	<i>Page</i>
1 SCOPE AND FIELD OF APPLICATION .....	1
2 REFERENCES .....	1
3 DEFINITIONS .....	1
4 PRINCIPLE .....	1
5 APPARATUS .....	1
6 SAMPLING .....	2
7 PREPARATION OF SPECIMENS .....	2
8 REQUIREMENTS FOR TESTING .....	2
9 NUMBER OF TESTS .....	3
10 TEST PROCEDURE .....	3
11 CALCULATION AND EXPRESSION OF RESULTS .....	3
12 TEST REPORT .....	4
13 APPENDIX ZZ .....	5

## © Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

Currently in preview, click buy full version

# Fishing line—Determination of breaking load

## 1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies a method of testing the breaking load and knot breaking load of netting yarns for fishing nets.

Tests may be carried out in both the dry and wet states but tests in the wet state on the knotted yarn are considered to be particularly appropriate in indicating the behaviour of the yarn in use.

## 2 REFERENCES

ISO 139, *Textiles — Standard atmospheres for conditioning and testing.*

ISO 858, *Fishing nets — Designation of netting yarns in the Tex system.*<sup>1)</sup>

## 3 DEFINITIONS<sup>2)</sup>

**3.1 breaking load:** The breaking load, equal to the maximum load observed during a breaking test.

Distinction is made between

- the dry yarn breaking load;
- the wet yarn breaking load;
- the dry knot breaking load;
- the wet knot breaking load.

**3.2 load at rupture:** The final load at the moment that the specimen or the first component of the specimen breaks at, or after, attainment of the breaking load. The load at rupture is usually, but not always, identical with the breaking load.

**3.3 tenacity:** The breaking load per unit resultant linear density of the unstrained specimen in the conditioned state.

**3.4 breaking length:** The calculated length of a specimen whose conditioned weight exercises a force equal to its breaking load. It is expressed in kilometres

and, when calculated in kgf units, is numerically equal to the tenacity calculated in gf units. When the calculations employ decanewtons and centinewtons respectively, the values obtained for both parameters, although equivalent, will be approximately 2 % lower, so that the value for breaking length will be slightly less than the traditional theoretical value.

**3.5 time-to-break:** The time, in seconds, taken to reach the breaking load, measured from the moment of application of the load.

## 4 PRINCIPLE

A length of yarn is extended in the dry or wet state until it reaches the point of rupture. The test is performed using a suitable apparatus that records or indicates the applied load.

## 5 APPARATUS

**5.1 Tensile testing machine.** Any of the following types may be used:

- a) constant rate of elongation machine;
- b) constant rate of load machine;
- c) constant rate of traverse machine.

Preference should be given to a constant rate of elongation machine.

**5.1.1** All tensile testing machines shall include a pair of suitable devices to hold the specimen, a means of loading or elongating the specimen at suitable rates, and a load-indicating mechanism which will indicate or continuously record the load applied to the specimen.

For determining the breaking load of netting yarns without knots, the specimens shall be mounted in special holding devices, for example of the types shown in Figure 1, to avoid slipping of the specimens or breaking due to damage caused by the holding devices.

1) At present at the stage of draft. (Revision of ISO/R 858.)

2) Symbolic abbreviations of the parameters defined have been omitted pending discussion of the general subject by Technical Committee ISO/TC 38.