

Australian Standard[®]

Plywood—Formwork

STANDARDS
Australia



This Australian Standard® was prepared by Committee TM-008, Plywood Timber Products. It was approved on behalf of the Council of Standards Australia on 31 May 2007. This Standard was published on 31 July 2007.

The following are represented on Committee TM-008:

- Australian Building Codes Board
- Engineered Wood Products Association of Australasia
- Engineers Australia
- Forests NSW
- New Zealand Plywood Manufacturers Association
- Scion
- Timber Development Association (NSW)

Additional Interests:

- Mr Kevin Lyngcoln
-

This Standard was issued in draft form for comment as DR 06603.

Standards Australia wishes to acknowledge the participation of the expert individuals that contributed to the development of this Standard through their representation on the Committee and through public comment received.

Keeping Standards up-to-date

Australian Standards® are living documents that reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued.

Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments that may have been published since the Standard was published.

Detailed information about Australian Standards, drafts, amendments and new projects can be found by visiting www.standards.org.au

Standards Australia welcomes suggestions for improvements, and encourages readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.org.au, or write to Standards Australia, GPO Box 476, Sydney, NSW 2001.

Australian Standard[®]

Plywood—Formwork

First published as AS 6669—2007.

COPYRIGHT

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia GPO Box 476, Sydney, NSW 2001, Australia

ISBN 0 7337 8296 5

PREFACE

This Standard was prepared by the members of the Joint Standards Australia/Standards New Zealand Committee TM-008, Plywood Timber Products. After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian Standard rather than an Australian/New Zealand Standard.

The objective of this Standard is to provide minimum performance requirements and specifications for the manufacture and application of plywood for use in the specific application of concrete formwork in Australia. This Standard describes formwork plywood products either overlaid or non-overlaid, which are suitable, subject to correct installation and design of the formwork, for providing a concrete surface finish meeting Class 2, 3, 4 and 5 off-form finishes as specified in AS 3610, *Formwork for concrete*. Attention is drawn to the mandatory requirements of AS 3610 for the need to undertake test pours where colour control or surface finishes of Class 2 or better are specified.

The plywood may be of either hardwood or softwood veneers, or a combination of both. The quality of veneers and surface quality is judged in the finished panel.

The quality of impregnated overlay papers is described using the paper/total weight ratio method.

Three veneer qualities, F, C, D, are prescribed as follows:

- F — A non-appearance grade, which is a suitable substrate for the bonding of overlay papers.
- C — A non-appearance grade with a solid surface.
- D — A non-appearance grade with permitted open imperfections.

Additionally two veneer qualities U2 and U3 are recommended for use as underlay veneer, as follows:

- U2 — A non-appearance grade suitable for use as an underlay veneer immediately beneath the face veneer in formwork plywood intended for a Class 2 surface finish. This grade permits solid defects but restricts the size of open imperfections, which may impair the surface quality meeting Class 2 surface requirements.
- U3 — A non-appearance grade suitable for use as an underlay veneer immediately beneath the face veneer in formwork plywood intended for a Class 3 surface finish. This grade permits solid defects but restricts the size of open imperfections, which may impair the surface quality meeting Class 3 surface requirements.

Three methods for determining the stress grade for the formwork plywood are described using the following bases:

- (a) Veneers of determined stiffness.
- (b) Mechanical F-grading of formwork plywood panels.
- (c) In-grade testing of formwork plywood panels.

Three bond types A, B and C are incorporated in the Standard to cover a range of bond durability requirements for formwork plywood across a range of applications and re-use conditions.

For the design of structures or elements incorporating the use of formwork plywood specified in this Standard, the structural grades will have characteristic strength and stiffness values as detailed in Table 5.1. These characteristic properties are to be assigned in accordance with the requirements of AS 1720.1, *Timber structures, Part 1: Design methods*.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the appendix to which they apply. A ‘normative’ appendix is an integral part of a Standard, where as an ‘informative’ appendix is only for information and guidance

Currently in preview, click buy full vers.

CONTENTS

	<i>Page</i>
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE	6
1.2 APPLICATION	6
1.3 REFERENCED DOCUMENTS	7
1.4 DEFINITIONS	7
1.5 GRADES OF FORMWORK PLYWOOD	8
1.6 DIMENSIONS AND SHAPE	8
1.7 MOISTURE CONTENT	9
1.8 EDGE FINISH	9
1.9 JOINTS IN SHEETS	10
1.10 IMMUNIZATION OF LYCTID-SUSCEPTIBLE SAPWOOD	10
1.11 BRANDING	10
SECTION 2 VENEER QUALITY	
2.1 GENERAL REQUIREMENTS FOR ALL VENEERS	12
2.2 QUALITY F VENEER	12
2.3 QUALITY C VENEER	14
2.4 QUALITY D VENEER	15
2.5 NON-STANDARD VENEER QUALITIES	15
SECTION 3 FORMWORK PLYWOOD SURFACE QUALITY	
3.1 GENERAL	16
3.2 CLASS 2 OR CLASS 3 SURFACE FINISH	16
3.3 CLASS 4 SURFACE FINISH	17
3.4 CLASS 5 SURFACE FINISH	17
SECTION 4 MANUFACTURING REQUIREMENTS	
4.1 JOINTS IN VENEER	18
4.2 STRUCTURAL JOINTS IN FORMWORK PLYWOOD SHEETS	18
4.3 BONDING	19
4.4 ASSEMBLY OF FORMWORK PLYWOOD	19
4.5 REQUIREMENTS FOR OVERLAYS	21
SECTION 5 APPLICATION OF STRESS GRADES AND MECHANICAL PROPERTIES	
5.1 TO FORMWORK PLYWOOD PANELS	
5.1 GENERAL	22
5.2 VENEERS OF DETERMINED ELASTIC MODULUS	22
5.3 MECHANICALLY F-GRADED FORMWORK PLYWOOD SHEETS	23
5.4 IN-GRADE TESTING	24
5.5 CAPACITY OF FORMWORK PLYWOOD	25

APPENDICES

A	STORAGE AND HANDLING OF FORMWORK PLYWOOD.....	26
B	SECTION PROPERTIES, SECOND MOMENT OF AREA (MOMENT OF INERTIA) AND SECTION MODULUS FOR FORMWORK PLYWOOD	27
C	METHOD FOR MECHANICALLY F-GRADING FORMWORK PLYWOOD PANELS.....	29
D	MEANS FOR DEMONSTRATING COMPLIANCE WITH THIS STANDARD	31
E	INFORMATION TO BE SUPPLIED WITH INQUIRIES AND ORDERS	32
F	TEST METHODS FOR OVERLAYS	33
G	RECOMMENDATION FOR UNDERLAY VENEER QUALITY	38
H	FORMWORK PLYWOOD CONSTRUCTION GUIDELINES RELATING TO SURFACE FINISH CLASS	40

Currently in preview, click buy full version

STANDARDS AUSTRALIA

Australian Standard
Plywood—Formwork

SECTION 1 SCOPE AND GENERAL

1.1 SCOPE

This Standard specifies requirements for the manufacture, grading, finishing and branding of plywood used specifically in formwork, with a maximum length of 3100 mm and width of 1500 mm, intended to meet off-form surface finish requirements Classes 2, 4 and 5 as specified in AS 3610. This Standard does not include specifications for formwork plywood intended to meet off-form surface finish Class 1.

Specifications for stress and surface grades, overlays, veneer quality, bond quality, standard lay-up construction, dimensional tolerances, joints, moisture content and characteristic strength and stiffness values for the nominated F-grades are provided.

The following alternative methods for the determination of stress grades for formwork plywood are specified:

- (a) Veneer stiffness determination.
- (b) Mechanical F-grading of the finished sheet of formwork plywood.
- (c) In-grade testing of finished formwork plywood panels.

Three outer veneer grades, based on the veneer quality of the face and back veneers, F, C and D are prescribed and four surface quality grades Class 2, Class 3, Class 4 and Class 5 are described.

Three bond types A, B and C are specified.

Formwork plywood is usually a multiple-use product. The physical and structural characteristics of formwork plywood products, as branded and specified in this Standard, are appropriate for the products as supplied. Inspection of the product is required between uses to ensure ongoing required performance across all characteristics. Structural adjustment factors for multiple uses are specified in AS 3610.

1.2 APPLICATION

The specification for any grade of formwork plywood shall consist of the requirements given in the following Sections:

- (a) General requirements Section 1.
- (b) Requirements for veneers Section 2.
- (c) Requirements for surface quality Section 3.
- (d) Manufacturing requirements Section 4.
- (e) Application of stress grades and mechanical properties Section 5.

Relevant requirements are also specified in the following normative Appendices:

- (i) Section properties Appendix B.
- (ii) Method for mechanically F-grading formwork plywood panels Appendix C.