



**Copper sulfide concentrates—
Determination of copper content—
Titrimetric methods**

STANDARDS
Australia

Currently in preview, click buy full version

This Australian Standard® was prepared by Committee MN-005, Copper, Lead, Zinc and Nickel Ores and Concentrates. It was approved on behalf of the Council of Standards Australia on 7 April 2016.

This Standard was published on 28 April 2016.

The following are represented on Committee MN-005:

- Australasian Institute of Mining and Metallurgy
 - Australian X-ray Analytical Association
 - CSIRO
 - Minerals Council of Australia
-

This Standard was issued in draft form for comment as DR A 5 ISO 10258:2016.

Standards Australia wishes to acknowledge the participation of the expert individuals that contributed to the development of this Standard through their representation on the Committee and through the public comment period.

Keeping Standards up-to-date

Australian Standards are living documents that reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued.

Standards may also be withdrawn. It is important that readers assure themselves they are using the current Standard, which should include any amendments that may have been published since the Standard was published.

Detailed information about Australian Standards, drafts, amendments and new projects can be found by visiting www.standards.org.au

Standards Australia welcomes suggestions for improvements, and encourages readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.org.au, or write to Standards Australia, GPO Box 476, Sydney, NSW 2001.

Australian Standard[®]

**Copper sulfide concentrates—
Determination of copper content—
Titrimetric methods**

Originally as AS 2917.1—1986.
Previous edition 1994.
Revised and redesignated as AS ISO 10258:2016.

COPYRIGHT

© Standards Australia Limited

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968.

Published by SAI Global Limited under licence from Standards Australia Limited, GPO Box 476, Sydney, NSW 2001, Australia

ISBN 978 1 76035 463 3

PREFACE

This Standard was prepared by the Standards Australia Committee MN-005, Copper, Lead, Zinc and Nickel Ores and Concentrates, to supersede AS 2917.1—1994.

The objective of this Standard is to specify two titrimetric methods for the determination of the copper content of copper sulfide concentrates in the range 15 % (m/m) to 50 % (m/m), using sodium thiosulfate after separation (method 1) or without separation (method 2) of copper from interfering elements.

This Standard is identical with, and has been reproduced from ISO 10258:2015, *Copper sulfide concentrates—Determination of copper content—Titrimetric methods*.

As this Standard is reproduced from an International Standard, the following applies:

- (a) In the source text ‘this International Standard’ should read ‘this Australian Standard’.
- (b) A full point substitutes for a comma when referring to a decimal marker.

References to International Standards should be replaced by references to Australian Standards, as follows:

<i>Reference to International Standard</i>		<i>Australian Standard</i>	
ISO		AS	
1042	Laboratory glassware—One-mark volumetric flasks	2164	Laboratory glassware—One-mark volumetric flasks
9599	Copper, lead and zinc sulfide concentrates—Determination of hygroscopic moisture content of the analysis sample—Gravimetric method	2816	Copper, lead and zinc sulfide concentrates—Determination of hygroscopic moisture in the analysis sample—Gravimetric method

Only normative references that have been adopted as Australian Standards have been listed.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the annexes to which they apply. A ‘normative’ annex is an integral part of a Standard, whereas an ‘informative’ annex is only for information and guidance.

CONTENTS

1	Scope	1
2	Normative references	1
3	Principle	1
3.1	Method 1 (Long iodide method).....	1
3.2	Method 2 (Short iodide method).....	1
4	Reagents	1
5	Apparatus	1
6	Sample	4
6.1	Test sample.....	4
6.2	Test portion.....	4
7	Procedure	4
7.1	Number of determinations.....	4
7.2	Blank test.....	4
7.3	Determination — method 1: Long iodide method.....	5
7.3.1	Decomposition of test portion.....	5
7.3.2	Separation of copper.....	5
7.3.3	Dissolution of copper precipitate.....	5
7.3.4	Titration.....	6
7.3.5	FAAS determination of copper in the insoluble residue, filtrate, and filter paper.....	6
7.4	Determination — method 2: Short iodide method.....	7
7.4.1	Decomposition of the test portion.....	7
7.4.2	Titration.....	7
8	Expression of results	8
9	Precision	8
9.1	Expression of precision.....	8
9.2	Method for obtaining the final result (see Annex B).....	9
9.3	Precision between laboratories.....	9
9.4	Check of trueness.....	10
10	Test report	11
Annex A (normative) Procedure for the preparation and determination of the mass of a predried test portion		12
Annex B (informative) Flowchart of the procedure for the acceptance of analytical values for test samples		14
Annex C (informative) Derivation of precision formulae		15
Bibliography		20

Copper sulfide concentrates—Determination of copper content— Titrimetric methods

1 Scope

This International Standard specifies two titrimetric methods for the determination of the copper content of copper sulfide concentrates in the range 15 % (m/m) to 50 % (m/m), using sodium thiosulfate after separation (method 1) or without separation (method 2) of copper from interfering elements.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385, *Laboratory glassware — Burettes*

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 4787, *Laboratory glassware — Volumetric instruments — Methods for testing of capacity and for use*

ISO 9599, *Copper, lead, zinc and nickel sulfide concentrates — Determination of hygroscopic moisture content of the analysis sample — Gravimetric method*

3 Principle

3.1 Method 1 (Long iodide method)

A test portion is decomposed in nitric and sulfuric acids, and arsenic, antimony, and tin are removed by treatment with hydrobromic acid. Copper is separated from interfering elements by precipitation of copper sulfide with sodium thiosulfate. The precipitate is dissolved in nitric and sulfuric acids, ammonium hydrogen difluoride is added to eliminate interference of residual iron, and excess potassium iodide is also added. Free iodine isolated by reaction between iodide ions and copper(II) ions is titrated with sodium thiosulfate using soluble starch as the indicator.

3.2 Method 2 (Short iodide method)

A test portion is decomposed in nitric and sulfuric acids, and arsenic, antimony, and tin are removed by treatment with hydrobromic acid. Ammonium hydrogen difluoride is added to eliminate interference of iron, and excess potassium iodide is also added. Free iodine isolated by reaction between iodide ions and copper(II) ions is titrated with sodium thiosulfate using soluble starch as the indicator.

4 Reagents

During the analysis, use only reagents of recognized analytical grade and distilled water or water of equivalent purity.

4.1 Copper metal, minimum purity 99,99 %.

4.2 Potassium iodide.