



Ceramic tiles

Method 8: Determination of linear thermal expansion



Currently in preview, click buy full version

AS ISO 10545.8:2020

This Australian Standard® was prepared by BD-044, Fixing of Ceramic, Natural and Reconstituted Stone Tiles. It was approved on behalf of the Council of Standards Australia on 25 February 2020.

This Standard was published on 6 March 2020.

The following are represented on Committee BD-044:

- Association of Consultants in Access Australia
- Australian Ceramic Society
- Australian Industry Group
- Australian Institute of Waterproofing
- Australian Stone Advisory Association
- Australian Tile Council
- CSIRO
- Master Builders Australia
- Surface Coatings Association Australia
- Swimming Pool and Spa Association of Australia
- TAFE NSW
- Tiles and Tiling Industry Association Australia

This Standard was issued in draft form for comment as DR AS ISO 10545.8:2020

Keeping Standards up-to-date

Ensure you have the latest versions of our publications and keep up-to-date about Amendments, Rulings, Withdrawals, and new projects by visiting:

www.standards.org.au

ISBN 978 1 76072 760 4



Ceramic tiles

Method 8: Determination of linear thermal expansion

Originates as AS 4459.8—1997.
Revised and redesignated as AS ISO 10545.8:2020.

COPYRIGHT

© ISO 2020 — All rights reserved
© Standards Australia Limited 2020

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Cth).

Preface

This Test Method was prepared by the Standards Australia Committee BD-044, Fixing of Ceramic, Natural and Reconstituted Stone Tiles to supersede AS 4459.8—1997, *Methods of sampling and testing ceramic tiles — Method 8: Determination of linear thermal expansion*.

The objective of this Test Method is to specify a method for determining the coefficient of linear thermal expansion of ceramic tiles.

This Test Method is identical with, and has been reproduced from, ISO 10545-8:2014, *Ceramic tiles — Part 8: Determination of linear thermal expansion*.

As this document has been reproduced from an International Standard, the following applies:

- (a) In the source text “this part of ISO 10545” should read “this Australian Standard”.
- (b) A full point substitutes for a comma when referring to a decimal marker.

Australian or Australian/New Zealand Standards that are identical adoption of international normative references may be used interchangeably. Refer to the online catalogue for information on specific Standards.

The terms “normative” and “informative” are used in Standards to define the application of the appendices or annexes to which they apply. A “normative” appendix or annex is an integral part of a Standard, whereas an “informative” appendix or annex is only for information and guidance.

Contents

Preface	ii
Foreword	iv
1 Scope	1
2 Principle	1
3 Apparatus	1
4 Test specimens	1
5 Procedure	1
6 Expression of results	2
7 Test report	2

Currently in preview, click buy full version

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 189, *Ceramic tile*.

This second edition cancels and replaces the first edition (ISO 10545-8:1994), which has been technically revised.

ISO 10545 consists of the following parts, under the general title *Ceramic tiles*:

- *Part 1: Sampling and basis for acceptance*
- *Part 2: Determination of dimensions and surface quality*
- *Part 3: Determination of water absorption, apparent porosity, apparent relative density and bulk density*
- *Part 4: Determination of modulus of rupture and breaking strength*
- *Part 5: Determination of impact resistance by measurement of coefficient of restitution*
- *Part 6: Determination of resistance to deep abrasion for unglazed tiles*
- *Part 7: Determination of resistance to surface abrasion for glazed tiles*
- *Part 8: Determination of linear thermal expansion*
- *Part 9: Determination of resistance to thermal shock*
- *Part 10: Determination of moisture expansion*
- *Part 11: Determination of crazing resistance for glazed tiles*
- *Part 12: Determination of frost resistance*
- *Part 13: Determination of chemical resistance*
- *Part 14: Determination of resistance to stains*
- *Part 15: Determination of lead and cadmium given off by glazed tiles*

— *Part 16: Determination of small colour differences*

Currently in preview, click buy full version

NOTES

Currently in preview, click buy full version

Australian Standard®

Ceramic tiles

Method 8: Determination of linear thermal expansion

1 Scope

This part of ISO 10545 defines a test method for determining the coefficient of linear thermal expansion of ceramic tiles.

2 Principle

Determination of the linear thermal expansion coefficient for the temperature range from ambient temperature to 100 °C.

3 Apparatus

3.1 Suitable thermal expansion apparatus, capable of a rate of heating of (5 ± 1) °C/min with uniform distribution of heat. Certain types of apparatus require a soaking time at 100 °C.

3.2 Vernier calipers, or other suitable device.

3.3 Drying oven, capable of being operated at (110 ± 5) °C. Microwave, infrared or other drying systems may be used provided that it has been determined that equal results are obtained.

3.4 Desiccator

4 Test specimens

Cut two test specimens at right angles from the central portion of one tile so that their lengths are suitable for the apparatus. The ends of the test specimens shall be ground flat and parallel.

If necessary, grind the test specimens so that the length of any side in cross-section is less than 6 mm and the area of cross-section is greater than 10 mm². The minimum length of the test specimens should be 25 mm. In the case of glazed tiles, the glaze shall not be ground off the test specimens.

5 Procedure

It is necessary to make a previous calibration of the apparatus with a standard test specimen. The dimensions of the standard test specimen shall be the same as the dimensions of the test specimen.

Dry the test specimens at (110 ± 5) °C until they reach constant mass, i.e. when the difference between two successive weightings at intervals of 24 h is less than 0,1 %. Allow them to cool in the desiccator (3.4) at ambient temperature.

Using vernier calipers (3.2), determine the lengths to an accuracy of 0,002 times the length.

Place a test specimen in the apparatus (3.1) and record the ambient temperature.

Initially, and throughout the heating procedure, measure the length to an accuracy of 0,01 mm. Take temperature and length measurements at temperature intervals of no more than 15 °C.

The rate of heating shall be (5 ± 1) °C/min.