

AS ISO 12742:2021
ISO 12742:2020



STANDARDS
Australia



Copper, lead and zinc sulfide concentrates — Determination of transportable moisture limits — Flow-table method



currently in review, click buy full version

AS ISO 12742:2021

This Australian Standard® was prepared by MN-005, Copper, Lead, Zinc and Nickel Ores and Concentrates. It was approved on behalf of the Council of Standards Australia on 26 May 2021.

This Standard was published on 4 June 2021.

The following are represented on Committee MN-005:

Australasian Institute of Mining and Metallurgy
Australian X-ray Analytical Association
Chamber of Minerals and Energy of Western Australia
CSIRO
Engineers Australia
International Copper Association Australia
Minerals Council of Australia

This Standard was issued in draft form for comment as DR AS ISO 12742:2021.

Keeping Standards up-to-date

Ensure you have the latest versions of our publications and keep up-to-date about Amendments, Rulings, Withdrawals, and new projects by visiting:

www.standards.org.au

ISBN 978 1 76113 364 0

Copper, lead and zinc sulfide concentrates — Determination of transportable moisture limits — Flow-table method

Originates as AS 4974—2008.
Revised and redesignated as AS ISO 12742:2021.

COPYRIGHT

© ISO 2021 — All rights reserved
© Standards Australia Limited 2021

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Cth).

Preface

This Standard was prepared by the Standards Australia Committee MN-005, Copper, Lead, Zinc and Nickel Ores and Concentrates, to supersede AS 4974—2008.

The objective of this document is to specify a flow-table method for the determination of the transportable moisture limit (TML) of copper, lead and zinc sulfide concentrates, which can liquefy during transport.

This document applies to the determination of the TML of concentrates containing 10 % to 80 % (mass fraction) of lead, 10 % to 65 % (mass fraction) of zinc or 10 % to 55 % (mass fraction) of copper and to TML values in the range 3 % to 28 % (mass fraction).

This document is identical with, and has been reproduced from, ISO 12742:2020, *Copper, lead and zinc sulfide concentrates — Determination of transportable moisture limits — Flow-table method*.

As this document has been reproduced from an International Standard, a full point substitutes for a comma when referring to a decimal marker.

Australian or Australian/New Zealand Standards that are identical adoptions of international normative references may be used interchangeably. Refer to the online catalogue for information on specific Standards.

The terms “normative” and “informative” are used in Standards to define the application of the appendices or annexes to which they apply. A “normative” appendix or annex is an integral part of a Standard, whereas an “informative” appendix or annex is only for information and guidance.

Contents

Preface.....	ii
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Apparatus.....	2
6 Sampling and sample preparation.....	3
6.1 General.....	3
6.2 Laboratory sample.....	3
6.3 Sample preparation.....	3
7 Procedure.....	4
7.1 General.....	4
7.2 Preparation of test portions.....	4
7.2.1 General.....	4
7.2.2 Filling the mould.....	4
7.2.3 Tamping pressure.....	5
7.2.4 Tamping procedure.....	5
7.2.5 Removal of the mould.....	5
7.2.6 Dropping the flow table.....	5
7.3 Identification of the flow state.....	6
7.4 Preliminary flow moisture point.....	8
7.4.1 Preparation of test portion.....	8
7.4.2 Determination of preliminary flow moisture point.....	8
7.4.3 Addition of water for preliminary flow moisture point test.....	8
7.4.4 Treatment of sample received above the flow moisture point.....	9
7.5 Main flow moisture point determination.....	9
7.5.1 Preparation of test portions.....	9
7.5.2 Determination of main flow moisture point.....	9
7.5.3 Addition of water for main flow moisture point determination.....	9
7.6 Graphical method.....	9
7.6.1 Preparation of test portions.....	9
7.6.2 Determination of flow moisture point.....	10
7.7 Moisture determination.....	10
8 Expression of results.....	10
8.1 Main flow moisture point.....	10
8.2 Flow moisture point determined by the graphical method.....	11
9 Variation of main flow moisture point.....	11
10 Test report.....	11
Annex A (normative) Description of equipment used to determine TML.....	12
Bibliography.....	21

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 163, *Copper, lead, zinc and nickel ores and concentrates*.

This third edition cancels and replaces the second edition (ISO 12742:2007), which has been technically revised. The main changes to the previous edition are as follows:

- [Clause 3](#), 'Terms and definitions', added.
- [6.2](#): reference to [7.4.4](#) for partial drying in event that sample received above transportable moisture limit (TML) added.
- [Clause 6](#): reference to ISO 17743 sampling procedures added.
- [7.3](#): description of the flow rate changed for clarity.
- [7.4.2](#): permission to deviate from the sample mass requirements of ISO 10251 for moisture determination added.
- [7.4.4](#): procedure for partial drying of sample received above TML added.
- [7.6.1](#): inclusion of data points with greater than 12 mm displacements in the graphical method provided that the points fall on the linear portion of the graph.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The first edition of this document was published in 2000 as a guidance document because there had been insufficient test programme participants to allow precision data to be derived.

The second edition included the addition of the graphical method for determination of the flow point as a means of validating the bracket method. This version has been revised to make it easier to understand and follow.

Currently in preview, click buy full version

NOTES

Currently in preview, click buy full version

Australian Standard®

Copper, lead and zinc sulfide concentrates — Determination of transportable moisture limits — Flow-table method

WARNING — This document could involve hazardous materials, operations and equipment. It is the responsibility of the user of this document to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This document specifies a flow-table method for the determination of the transportable moisture limit (TML) of copper, lead and zinc sulfide concentrates, which can liquefy during transport.

It is applicable to the determination of the TML of concentrates containing 10 % to 80 % (mass fraction) of lead, 10 % to 65 % (mass fraction) of zinc or 10 % to 55 % (mass fraction) of copper and is applicable to TML values in the range 3 % to 28 % (mass fraction).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10251, *Copper, lead, zinc and nickel concentrates — Determination of mass loss of bulk material on drying*

ISO 12743, *Copper, lead, zinc and nickel concentrates — Sampling procedures for determination of metal and moisture content*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

flow moisture point
percentage of moisture at which a flow state is reached

3.2

transportable moisture limit
maximum percentage of moisture that a cargo can contain during transport without the risk of liquefaction

4 Principle

The moisture content of the sample is adjusted by mixing with water. The mixture is converted to a conical shape using a mould and tamper. The sample is placed on the flow table and the mould is removed. The flow characteristics are determined by repeated dropping of the flow table while observing the behaviour of the sample. When sufficient water has been added to the sample so that plastic deformation occurs during the dropping of the flow table, the sample is considered to be at its flow moisture point.

The TML is calculated as 90 % of the flow moisture point.