

American Society of Civil Engineers

Specification for the Design of Cold-Formed Stainless Steel Structural Members

This document uses both International System of Units (SI) and customary units.



Published by the American Society of Civil Engineers
1801 Alexander Bell Drive
Reston, Virginia 20191-4400



ABSTRACT

ASCE's standard *Specification for the Design of Cold-Formed Stainless Steel Structural Members* (ASCE 8-02) provides design criteria for the determination of the strength of stainless steel structural members and connections for use in buildings and other statically loaded structures. The members may be cold-formed to shape from annealed and cold-rolled sheet, strip, plate, or flat bar stainless steel material. Design criteria are provided for axially loaded tension or compression members, flexural members subjected to bending and shear, and members subjected to combined axial load and bending. The specification provides the design strength criteria using the load and resistance factor design (LRFD) and the allowable stress design (ASD) methods. The reasoning behind, and the justification for, various provisions of the specification are also presented. The design strength requirements of this standard are intended for use by structural engineers and those engaged in preparing and administering local building codes.

Library of Congress Cataloging-in-Publication Data

Specification for the design of cold-formed stainless steel structural members / American Society of Civil Engineers.

p. cm.

"Revision of ANSI/ASCE 8-90."

Includes bibliographical references and index.

ISBN 0-7844-0556-5

1. Building, Iron and steel—Specifications—United States.
2. Steel, Structural—Specifications—United States. 3. Load factor design. I. American Society of Civil Engineers.

TA684 .S652 2001

624.1'821—dc21

2001022355

Photocopies. Authorization to photocopy material for internal or personal use under circumstances not falling within the fair use provisions of the Copyright Act is granted by ASCE to libraries and other users registered with the Copyright Clearance Center (CCC) Transactional Reporting Service, provided that the base fee of \$8.00 per article plus \$.50 per page is paid directly to CCC, 222 Rosewood Drive, Danvers, MA 01923. The identification for ASCE Books is 0-7844-0556-5/02/\$8.00 + \$.50 per page. Requests for special permission or bulk copying should be addressed to Permissions & Copyright Dept., ASCE.

Copyright ©2002 by the American Society of Civil Engineers.

All Rights Reserved.

Library of Congress Catalog Card No: 2001022355

ISBN 0-7844-0556-5

Manufactured in the United States of America.

STANDARDS

In April 1980, the Board of Direction approved ASCE Rules for Standards Committees to govern the writing and maintenance of standards developed by the Society. All such standards are developed by a consensus standards process managed by the Management Group F (MGF), Codes and Standards. The consensus process includes balloting by the balanced standards committee made up of Society members and nonmembers, balloting by the membership of ASCE as a whole, and balloting by the public. All standards are updated or reaffirmed by the same process at intervals not exceeding 5 years.

The following Standards have been issued.

- ANSI/ASCE 1-82 N-725 Guideline for Design and Analysis of Nuclear Safety Related Earth Structures
- ANSI/ASCE 2-91 Measurement of Oxygen Transfer in Clean Water
- ANSI/ASCE 3-91 Standard for the Structural Design of Composite Slabs and ANSI/ASCE 9-91 Standard Practice for the Construction and Inspection of Composite Slabs
- ASCE 4-98 Seismic Analysis of Safety-Related Nuclear Structures
- Building Code Requirements for Masonry Structures (ACI 530-99/ASCE 5-99/TMS 402-99) and Specifications for Masonry Structures (ACI 530.1-99/ASCE 6-99/TMS 602-99)
- ASCE 7-98 Minimum Design Loads for Buildings and Other Structures
- ASCE 8-90 Standard Specification for the Design of Cold-Formed Stainless Steel Structural Members
- ANSI/ASCE 9-91 listed with ASCE 3-91
- ASCE 10-97 Design of Latticed Steel Transmission Structures
- SEI/ASCE 11-99 Guideline for Structural Condition Assessment of Existing Building
- ANSI/ASCE 12-91 Guideline for the Design of Urban Subsurface Drainage
- ASCE 13-93 Standard Guideline for Installation of Urban Subsurface Drainage
- ASCE 14-93 Standard Guidelines for Operation and Maintenance of Urban Subsurface Drainage
- ASCE 15-98 Standard Practice for Direct Design of Buried Precast Concrete Pipe Using Standard Installations (SIDD)
- ASCE 16-95 Standard for Load and Resistance Factor Design (LRFD) of Engineered Wood Construction
- ASCE 17-96 Air-Supported Structures
- ASCE 18-96 Standard Guidelines for In-Process Oxygen Transfer Testing
- ASCE 19-96 Structural Applications of Steel Cables for Buildings
- ASCE 20-96 Standard Guidelines for the Design and Installation of Pile Foundations
- ASCE 21-96 Automated People Mover Standards—Part 1
- ASCE 21-98 Automated People Mover Standards—Part 2
- ASCE 21-00 Automated People Mover Standards—Part 3
- SEI/ASCE 23-97 Specification for Structural Steel Beams with Web Openings
- SEI/ASCE 24-98 Flood Resistant Design and Construction
- ASCE 25-97 Earthquake-Actuated Automatic Gas Shut-Off Devices
- ASCE 26-97 Standard Practice for Design of Buried Precast Concrete Box Sections
- ASCE 27-00 Standard Practice for Direct Design of Precast Concrete Pipe for Jacking in Trenchless Construction
- ASCE 28-00 Standard Practice for Direct Design of Precast Concrete Box Sections for Jacking in Trenchless Construction
- SEI/ASCE 30-00 Guideline for Condition Assessment of the Building Envelope
- EWRI/ASCE 33-01 Comprehensive Transboundary International Water Quality Management Agreement
- EWRI/ASCE 34-01 Standard Guidelines for Artificial Recharge of Ground Water
- EWRI/ASCE 35-01 Guidelines for Quality Assurance of Installed Fine-Pore Aeration Equipment
- CI/ASCE 36-01 Standard Construction Guidelines for Microtunneling
- SEI/ASCE 37-02 Design Loads on Structures During Construction

Currently in preview, click buy full version

FOREWORD

Prior to 1990, the design of cold-formed stainless steel structural members was based on the allowable stress design specification issued by the American Iron and Steel Institute. Based on the initiative of Chromium Steels Research Group at Rand Afrikaans University in 1989, a new ASCE Standard Specification for the Design of Cold-Formed Stainless Steel Structural Members was developed at the University of Missouri-Rolla under the Sponsorship of the American Society of Civil Engineers. It was subsequently reviewed and approved by the ASCE Stainless Steel Cold-Formed Sections Standards Committee in 1990. This ASCE project was financially supported by the Chromium Centre in South Africa, the Nickel Development Institute in Canada, and the Specialty Steel Industry of the United States. The development of this new ASCE Standard Specification was primarily based on the 1974 Edition of the AISI specification for stainless steel design and the recent extensive research conducted by Chromium Steels Research Group at Rand Afrikaans University under the sponsorship of Columbus Stainless Steel (the Middleburg Steel and Alloys) in South Africa.

This new ASCE Standard Specification includes both the load and resistance factor design (LRFD) method and the allowable stress design (ASD) method. In the LRFD method, separate load and resistance factors are applied to specified loads and nominal resistance to ensure that the probability of reaching a limit state is acceptably small. These factors reflect the uncertainties of analysis, design, loading, material properties, and fabrication.

The material presented in this publication has been prepared in accordance with recognized engineering principles. This Standard and Commentary should not be used without first securing competent advice with respect to suitability for any given application. The publication of the material contained herein is not intended as a representation or warranty on the part of the American Society of Civil Engineers, or of any other person named herein, that this information is suitable for any general or particular use or promises freedom from infringement of any patent or patents. Anyone making use of this information assumes all liability from such use.

Currently in preview, click buy full version

ACKNOWLEDGMENTS

The American Society of Civil Engineers (ASCE) acknowledges the devoted efforts of Wei-Wen Yu, Theodore V. Galambos, and Shin-Hua Lin for developing this Standard Specification. Appreciation is expressed to the American Iron and Steel Institute for relinquishing to ASCE the 1974 edition of AISI Specification for the Design of Cold-Formed Stainless Steel Structural Members for revision and publication as an ASCE standard.

ASCE acknowledges the work of the Stainless Steel Cold-Formed Section Standards Committee of

the Management Group F. Codes and Standards. This group comprises individuals from many backgrounds including: consulting engineering, research, construction industry, education, government, design, and private practice.

This Standard was prepared through the consensus standards process by balloting in compliance with procedures of ASCE's Management Group F. Codes and Standards. Those individuals who serve on the Standards Committee are:

Prodyot K. Basu
Adrian F. Dier
Mark W. Fantozzi
Theodore Galambos, Chairman
Joseph C. Kotlarz
Roger A. LaBoube
Shin-Hua Lin, Secretary
Robert R. McCluer

Albert C. Nuhn
Clarkson W. Pinkham
Kim Rasmussen
James D. Redmond
Reinhold M. Schuster
John G. Tack
Torkel Stenquist
Cosmas A. Tzavelis

Gert J. Van der Bergh
Pieter Van Der Merwe
Ivan M. Viet
Shien T. Wang
Vernon Watwood
Donald W. Welford, Vice Chairm.
Wei-Wen Yu
John P. Ziemianski

Currently in preview, click buy full version

CONTENTS

Acknowledgments	vii
Notation	xiii
1. General Provisions	1
1.1 Limits of Applicability and Terms	1
1.1.1 Scope and Limits of Applicability	1
1.1.2 Terms	1
1.1.3 Units of Symbols and Terms	1
1.2 Nonconforming Shapes and Constructions	2
1.3 Material	2
1.3.1 Applicable Stainless Steels	2
1.3.2 Other Stainless Steels	2
1.3.3 Ductility	2
1.3.4 Delivered Minimum Thickness	2
1.4 Loads	2
1.4.1 Dead Load	2
1.4.2 Live and Snow Load	2
1.4.3 Impact Load	2
1.4.4 Wind and Earthquake Load	2
1.4.5 Ponding	2
1.5 Structural Analysis and Design	2
1.5.1 Design Basis	2
1.5.1.1 Design for Strength	3
1.5.1.2 Design for Serviceability	3
1.5.2 Loads, Load Factors, and Load Combinations	3
1.5.3 Resistance Factors	3
1.5.4 Yield Strength and Strength Increase from Cold Work of Forming	3
1.5.4.1 Yield Strength	3
1.5.4.2 Strength Increase from Cold Work of Forming	3
1.5.4.2.1 Type of Sections	4
1.5.4.2.2 Limitations	4
1.5.5 Design Tables and Figures	4
1.6 Reference Documents	4
2. Elements	4
2.1 Dimensional Limits and Considerations	4
2.1.1 Flange Flat-Width-to-Thickness Considerations	4
2.1.2 Maximum Web Depth-to-Thickness Ratio	5
2.2 Effective Widths of Stiffened Elements	5
2.2.1 Uniformly Compressed Stiffened Elements	5
2.2.2 Effective Widths of Webs and Stiffened Elements with Stress Gradient	6
2.3 Effective Widths of Unstiffened Elements	7
2.3.1 Uniformly Compressed Unstiffened Elements	7
2.3.2 Unstiffened Elements and Edge Stiffeners with Stress Gradient	7
2.4 Effective Widths of Elements with Edge Stiffener or One Intermediate Stiffener	8
2.4.1 Uniformly Compressed Elements with Intermediate Stiffener	8
2.4.2 Uniformly Compressed Elements with Edge Stiffener	9
2.5 Effective Widths of Edge-Stiffened Elements with Intermediate Stiffeners or Stiffened Elements with More Than One Intermediate Stiffener	10
2.6 Stiffeners	11
3. Members	11
3.1 Properties of Sections	11
3.2 Tension Members	11

CONTENTS

3.3 Flexural Members	11
3.3.1 Strength for Bending Only	11
3.3.1.1 Nominal Section Strength	11
3.3.1.2 Lateral Buckling Strength	13
3.3.2 Strength for Shear Only	14
3.3.3 Strength for Combined Bending and Shear	14
3.3.4 Web Crippling Strength	14
3.3.5 Combined Bending and Web Crippling Strength	16
3.4 Centrically Loaded Compression Members	17
3.4.1 Sections Not Subject to Torsional or Torsional-Flexural Buckling	17
3.4.2 Doubly or Point-Symmetric Sections Subject to Torsional Buckling	17
3.4.3 Singly Symmetric Sections Subject to Torsional-Flexural Buckling	17
3.4.4 Nonsymmetric Sections	18
3.5 Combined Axial Load and Bending	18
3.6 Cylindrical Tubular Members	19
3.6.1 Bending	19
3.6.2 Compression	19
3.6.3 Combined Bending and Compression	19
3.7 Arc-and-Tangent Corrugated Sheets	19
4. Structural Assemblies	19
4.1 Built-Up Sections	19
4.1.1 I-Sections Composed of Two Channels	19
4.1.2 Spacing of Connections in Compression Elements	20
4.2 Mixed Systems	21
4.3 Lateral Bracing	21
4.3.1 Symmetrical Beams and Columns	21
4.3.2 Channel-Section and Z-Section Beams	21
4.3.2.1 Bracing When One Flange Is Connected	21
4.3.2.2 Neither Flange Connected to Sheathing	21
4.3.3 Laterally Unbraced Box Beams	21
5. Connections and Joints	22
5.1 General Provisions	22
5.2 Welded Connections	22
5.2.1 Groove Welds in Butt Joints	22
5.2.2 Fillet Welds	22
5.2.3 Resistance Welds	23
5.3 Bolted Connections	23
5.3.1 Spacing and Edge Distance	23
5.3.2 Tension in Connected Part	24
5.3.3 Bearing	24
5.3.4 Shear and Tension in Stainless Steel Bolts	25
6. Tests	26
6.1 Determination of Stress-Strain Relationships	26
6.2 Tests for Determining Structural Performance	26
6.3 Tests for Determining Mechanical Properties of Full Sections	27
Appendices	
Appendix A Design Tables and Figures	29
Appendix B Modified Ramberg-Osgood Equation	29
Appendix C Stiffeners	29
C.1 Transverse Stiffeners	29
C.2 Shear Stiffeners	30

	C.3 Nonconforming Stiffeners	30
Appendix D	Allowable Stress Design (ASD)	48

Tables

Table 1.	Short, Wide Flanges: Maximum Allowable Ratio of Effective Design Width to Actual Width	5
Table 2.	Nominal Web Crippling Strength, P_n	15
Table 3.	Nominal Shear Strength of Arc Spot Welding	23
Table 4.	Nominal Shear Strength of Pulsation Welding	23
Table 5.	Maximum Size of Bolt Holes	24
Table 6.	Nominal Shear and Tensile Stresses for Stainless Steel Bolts	25
Table A1.	Specified Yield Strengths of Stainless Steels	30
Table A2a.	Secant Moduli for Deflection Calculations (Types 201, 301, 304, and 316)	31
Table A2b.	Secant Moduli for Deflection Calculations (UNS S20400)	32
Table A3.	Secant Moduli for Deflection Calculations (Types 409, 430, and 439)	34
Table A4a.	Initial Moduli of Elasticity and Initial Shear Moduli (Types 201, 301, 304, and 316)	34
Table A4b.	Initial Moduli of Elasticity and Initial Shear Moduli (UNS S20400)	34
Table A5.	Initial Moduli of Elasticity and Initial Shear Moduli (Types 409, 430, and 439) ..	35
Table A6a.	Plasticity Reduction Factors for Stiffened Elements (Types 201, 301, 304, and 316)	35
Table A6b.	Plasticity Reduction Factors for Stiffened Elements (UNS S20400)	36
Table A7.	Plasticity Reduction Factors for Stiffened Elements (Types 409, 430, and 439) ..	36
Table A8a.	Plasticity Reduction Factors for Unstiffened Elements (Types 201, 301, 304, and 316)	37
Table A8b.	Plasticity Reduction Factors for Unstiffened Elements (UNS S20400)	38
Table A9.	Plasticity Reduction Factors for Unstiffened Elements (Types 409, 430, and 439)	39
Table A10a.	Plasticity Reduction Factors for Lateral Buckling Strengths (Types 201, 301, 304, and 316)	40
Table A10b.	Plasticity Reduction Factors for Lateral Buckling Strengths (UNS S20400)	41
Table A11.	Plasticity Reduction Factors for Lateral Buckling Strengths (Types 409, 430, and 439)	42
Table A12.	Plasticity Reduction Factors for Shear Strengths	42
Table A13a.	Tangent Moduli for Design of Columns (Types 201, 301, 304, and 316)	43
Table A13b.	Tangent Moduli for Design of Columns (UNS S20400)	44
Table A14.	Tangent Moduli for Design of Columns (Types 409, 430, and 439)	45
Table A15.	Tensile Strength of Weld Metal	46
Table A16.	Tensile Strengths of Annealed, 1/16 Hard, 1/4 Hard, and 1/2 Hard Base Metals ..	46
Table A17.	Ratio of Effective Proportional Limit-to-Yield Strength	47
Table B.	Coefficient n Used for Modified Ramberg-Osgood Equation	47
Table D.	Safety Factors by Subjects and Sections of the Specification for the Design of Cold-Formed Stainless Steel Structural Members	47

Figures

Figure 1.	Stiffened Elements with Uniform Compression*	6
Figure 2.	Stiffened Elements with Stress Gradient and Webs*	7
Figure 3.	Unstiffened Elements with Uniform Compression*	8
Figure 4.	Elements with Intermediate Stiffener*	8
Figure 5.	Elements with Edge Stiffener*	9
Figure A1a.	Secant Moduli for Deflection Calculations (Types 201, 301, 304, and 316)	48
Figure A1b.	Secant Moduli for Deflection Calculations (S20400, Compression)	49

CONTENTS

Figure A2. Secant Moduli for Deflection Calculations (Types 409, 430, and 439) 51

Figure A3a. Plasticity Reduction Factors for Stiffened Compression Elements
(Types 201, 301, 304, and 316) 53

Figure A3b. Plasticity Reduction Factors for Stiffened Compression Elements (S20400) 53

Figure A4. Plasticity Reduction Factors for Stiffened Compression Elements
(Types 409, 430, and 439) 54

Figure A5a. Plasticity Reduction Factors for Unstiffened Compression Elements
(Types 201, 301, 304, and 316) 56

Figure A5b. Plasticity Reduction Factors for Unstiffened Compression Elements (S20400) 56

Figure A6. Plasticity Reduction Factors for Unstiffened Compression Elements
(Types 409, 430, and 439) 57

Figure A7a. Plasticity Reduction Factors for Design of Laterally Unbraced Single
Web Beams (Types 201, 301, 304, and 316) 59

Figure A7b. Plasticity Reduction Factors for Design of Laterally Unbraced Single
Web Beams 59

Figure A8. Plasticity Reduction Factors for Design of Laterally Unbraced Single
Web Beams (Types 409, 430, and 439) 60

Figure A9. Plasticity Reduction Factors for Shear Stresses in Webs
(Types 201, 301, 304, and 316) 62

Figure A10. Plasticity Reduction Factors for Shear Stresses in Webs
(Types 409, 430, and 439) 63

Figure A11a. Tangent Moduli for Design of Columns (Types 201, 301, 304, and 316) 64

Figure A11b. Tangent Moduli for Design of Columns (Type 204) 64

Figure A12. Tangent Moduli for Design of Columns (Types 409, 430, and 439) 65

* Reproduced with permission of the American Iron and Steel Institute from AISI Specification for the Design of Cold-Formed Steel Structural Members with Commentary (1986).

COMMENTARY CONTENTS

(This Commentary is not a part of the standard. It is included for information purposes.)
Commentary on ASCE Standard Specification for the Design of Cold-Formed Stainless Steel
Structural Members

Introduction	67
1. General Provisions	67
1.1 Limits of Applicability and Terms	67
1.1.1 Scope and Limits of Applicability	67
1.1.2 Terms	67
1.1.3 Units of Symbols and Terms	70
1.2 Nonconforming Shapes and Constructions	70
1.3 Material	70
1.3.1 Applicable Stainless Steels	70
1.3.2 Other Stainless Steels	75
1.3.3 Ductility	75
1.3.4 Delivered Minimum Thickness	75
1.4 Loads	75
1.5 Structural Analysis and Design	76
1.5.1 Design Basis	76
1.5.4 Yield Strength and Strength Increase from Cold Work of Forming	81
1.5.5 Design Tables and Figures	82
1.6 Reference Documents	82
2. Elements	82
2.1 Dimensional Limits and Considerations	82
2.1.1 Flange Flat-Width-to-Thickness Considerations	82
2.1.2 Maximum Web Depth-to-Thickness Ratio	83
2.2 Effective Widths of Stiffened Elements	83
2.2.1 Uniformly Compressed Stiffened Elements	84
2.2.2 Effective Widths of Webs and Stiffened Elements with Stress Gradient	85
2.3 Effective Widths of Unstiffened Elements	86
2.3.1 Uniformly Compressed Unstiffened Elements	86
2.3.2 Unstiffened Elements and Edge Stiffeners with Stress Gradient	86
2.4 Effective Widths of Elements with Edge Stiffener or One Intermediate Stiffener	86
2.4.1 Uniformly Compressed Elements with Intermediate Stiffener	86
2.4.2 Uniformly Compressed Elements with Edge Stiffener	86
2.5 Effective Widths of Edge-Stiffened Elements with Intermediate Stiffeners or Stiffened Elements with More Than One Intermediate Stiffener	86
2.6 Stiffeners	87
3. Members	87
3.1 Properties of Sections	87
3.2 Tension Members	87
3.3 Flexural Members	87
3.3.1 Strength for Bending Only	87
3.3.1.1 Nominal Section Strength	87
3.3.1.2 Lateral Buckling Strength	88
3.3.2 Strength for Shear Only	89
3.3.3 Strength for Combined Bending and Shear	89
3.3.4 Web Crippling Strength	89
3.3.5 Combined Bending and Web Crippling Strength	92

COMMENTARY CONTENTS

- 3.4 Concentrically Loaded Compression Members 92
 - 3.4.1 Sections Not Subject to Torsional or Torsional-Flexural Buckling 93
 - 3.4.2 Doubly or Point-Symmetric Sections Subject to Torsional Buckling 93
 - 3.4.3 Singly Symmetric Sections Subject to Torsional-Flexural Buckling 93
 - 3.4.4 Nonsymmetric Sections 93
- 3.5 Combined Axial Load and Bending 93
- 3.6 Cylindrical Tubular Members 94
 - 3.6.1 Bending 94
 - 3.6.2 Compression 94
- 3.7 Arc-and-Tangent Corrugated Sheets 94
- 4. Structural Assemblies 95
 - 4.1 Built-Up Sections 95
 - 4.1.1 I-Sections Composed of Two Channels 95
 - 4.1.2 Spacing of Connections in Compression Elements 95
 - 4.2 Mixed Systems 97
 - 4.3 Lateral Bracing 97
 - 4.3.1 Symmetrical Beams and Columns 97
 - 4.3.2 Channel-Section and Z-Section Beams 97
 - 4.3.2.1 Bracing When One Flange Is Connected 97
 - 4.3.2.2 Neither Flange Connected to Sheathing 97
 - 4.3.3 Laterally Unbraced Box Beams 97
- 5. Connections and Joints 97
 - 5.1 General Provisions 97
 - 5.2 Welded Connections 98
 - 5.2.1 Groove Welds in Butt Joints 98
 - 5.2.2 Fillet Welds 98
 - 5.2.3 Resistance Welds 99
 - 5.3 Bolted Connections 99
 - 5.3.1 Spacing and Edge Distance 100
 - 5.3.2 Tension in Connected Part 100
 - 5.3.3 Bearing 100
 - 5.3.4 Shear and Tension in Stainless Steel Bolts 100
- 6. Tests 101
 - 6.1 Determination of Stress-Strain Relationships 101
 - 6.2 Tests for Determining Structural Performance 101
 - 6.3 Tests for Determining Mechanical Properties of Full Sections 101

Appendices

- Appendix A Design Tables and Figures 103
- Appendix B Modified Ramberg-Osgood Equation 103
- Appendix C Stiffeners 104
- Appendix D Allowable Stress Design (ASD) 105
- References 105

Tables

- Table C1. ASTM Requirements for Mechanical Properties of Types 409, 430, and 439 72
- Table C2. ASTM Requirements for Mechanical Properties of Types 201, S20400, 301, 304, and 316 72
- Table C3. Tested Mechanical Properties of Annealed and Strain-Flattened Types 201-2 and 304 Austenitic Stainless Steels, Adapted from Reference 13 73
- Table C4. Tested Mechanical Properties of 1/4-Hard and 1/2-Hard Type 301 Austenitic Stainless Steels, Adapted from Reference 14 73

Table C5.	Tested Mechanical Properties of 1/4-Hard and 1/2-Hard Types 201 and 301 Austenitic Stainless Steels, Adapted from Reference 15	74
Table C6.	Tested Mechanical Properties of Types 409, 430, and 439 Ferritic Stainless Steels	74
Table C7.	Statistics on Yield Strengths of Types 409, 430, and 439 Ferritic Stainless Steels . .	75
Table C8.	Computed Safety Indices, β , for Cold-Formed Stainless Steels Using Fillet Welds ($D_n/L_n = 0.2$)	98
Table C9.	AWS Requirements for Mechanical Property of All-Weld Metal	99
Figures		
Figure C1.	Members with Stiffened and Partially Stiffened Compression Elements*	68
Figure C2.	Members with Unstiffened Compression Elements*	69
Figure C3.	Members with Multiple-Stiffened Compression Elements*	70
Figure C4.	Stress-Strain Diagram Showing Yield Strength Determination	71
Figure C5.	Frequency Distributions of Resistance and Load Effect	77
Figure C6.	Probability Distribution of $1n(R/Q)$	78
Figure C7.	Local Buckling and Post-Buckling Strength of Stiffened Compression Element . . .	83
Figure C8.	Correlation Between Effective Width Formula and Test Data	85
Figure C9.	Application of Design Equations Listed in Table 2*	90
Figure C10.	Assumed Distribution of Reaction or Load*	91
Figure C11.	Sections Used for One Exception Clause of Section 3.3.5*	92
Figure C12.	Ultimate Moment Capacity of Stainless Steel Cylindrical Tubes	94
Figure C13.	I-Beam Composed of Two Channels*	96
Figure C14.	Spacing of Connections in Compression Element*	96

* Reproduced with permission of the American Iron and Steel Institute from AISI Specification for the Design of Cold-Formed Steel Structural Members with Commentary (1986).

NOTATION

Symbol	Definition	Section
A	Full, unreduced cross-sectional area of the member	3.3.1.2,3.4
A_b	$b_1t + A_s$, for transverse stiffeners at interior support and under concentrated load, and $b_2t + A_s$, for transverse stiffeners at end support	App. C.1
A_b	Gross cross-sectional area of bolt	5.3.4
A_c	$18t^2 + A_s$, for transverse stiffeners at interior support and under concentrated load, and $10t^2 + A_s$, for transverse stiffeners at end support	App. C.1
A_e	Effective area at the stress F_n	3.4,3.6.2
A_n	Net area of cross section	3.2,5.3.2
A_o	Reduced area of cross section	3.6.2
A_s	Cross-sectional area of transverse stiffeners	2.4,2.4.1,2.4.2, App. C.1
A'_s	Effective area of stiffener	2.4,2.4.1,2.4.2
A_{st}	Gross area of shear stiffener	App. C.2
a	For a reinforced web element, the distance between transverse stiffeners	App. C.2
a	Length of bracing interval	4.3.2.2
b	Effective design width of compression element	2.2.1,2.2.2,2.3.1,2.3.2, 2.4.1,2.4.2,2.5
b_d	Effective width for deflection calculation	2.2.1,2.2.2
b_e	Effective design width of sub-element or element	2.2.2,2.5
b_o	See Figure 4	2.4,2.4.1,2.5
b_1, b_2	Effective widths, see Figure 2	2.2.2
C	Ratio of effective proportional limit-to-yield strength, F_{pr}/F_y	3.6.1
C_b	Bending coefficient dependent on moment gradient	3.3.1.2
C_m	End moment coefficient in interaction formula	3.5
C_{mx}	End moment coefficient in interaction formula	3.5
C_{my}	End moment coefficient in interaction formula	3.5
C_s	Coefficient for lateral torsional buckling	3.3.1.2
C_v	Shear stiffener coefficient	App. C.2
C_w	Torsional warping constant of cross section	3.3.1.2
C_y	Compression strain factor	3.3.1.1
C_1	Coefficient as defined in Figures 4 and 5	2.4,2.4.2
C_2	Coefficient as defined in Figures 4 and 5	2.4,2.4.2
c_f	Amount of curling	2.1.1
D	Outside diameter of cylindrical tube	3.6.1,3.6.2
D	Dead load, includes weight of test specimen	6.2
D	Overall depth of lip	2.1.1,2.4,2.4.2,4.1.1
D	Shear stiffener coefficient	App. C.2
D_n	Nominal dead load	1.5.2
d	Depth of section	2.4,2.1.1,3.3.1, 4.1.1,4.3.2.2
d	Diameter of bolt	5.3,5.3.1,5.3.2,5.3.3
d_h	Diameter of standard hole	5.3.1
d_s	Reduced effective width of stiffener	2.4,2.4.2
d'_s	Actual effective width of stiffener	2.4,2.4.2
E_n	Nominal earthquake load	1.5.2

NOTATION

Symbol	Definition	Section
E_o	Initial modulus of elasticity	2.2.1,2.3.1,2.4,2.5, 3.3.1.1,3.3.1.2,3.3.2, 3.3.5,3.6.1,3.6.2, 4.3.3,App. B
E_r	Reduced modulus of elasticity	2.2.1
E_s	Secant modulus	3.3.1.1,3.4,App. B
E_{sc}	Secant modulus in compression flange	2.2.1
E_{st}	Secant modulus in tension flange	2.2.1
E_s/E_o	Plasticity reduction factor for unstiffened compression elements	3.3.1.1,3.4,App. B
E_t	Tangent modulus in compression	3.3.1.1,3.4,App. B, 3.4.1,3.6.2
E_t/E_o	Plasticity reduction factor for lateral buckling	3.3.1.2,3.6.2,App. B
$\sqrt{E_t/E_o}$	Plasticity reduction factor for stiffened compression elements	3.3.1.1,3.4,App. B
e	Distance measured in line of force from centerline of standard hole to nearest edge of adjacent hole or to end of connected part toward which force is directed	5.3.1
e_y	Yield strain = F_y/E_o	3.3.1.1
F_{cr}	Critical buckling stress	3.3.1.1,3.4
F_D	Dead load factor	6.2
F_L	Live load factor	6.2
F_n	Nominal buckling stress	3.4,3.6.2
F_{nt}	Nominal tensile strength of bolts	5.3.4
F_{nv}	Nominal shear strength of bolts	5.3.4
F'_{nt}	Nominal tensile strength for bolts subject to combination of shear and tension	5.3.4
F_p	Nominal bearing stress	5.3.3
F_{pr}	Effective proportional limit	3.6.1
F_t	Nominal tension stress limit on net section	5.3.2
F_u	Tensile strength in longitudinal direction	5.3.1,5.3.2,5.3.3,5.3.4
F_{ua}	Tensile strength of annealed base metal	5.2.1,5.2.2
F_{xx}	Strength level designation in AWS electrode classification	5.2.2
F_y	Yield strength used for design, not to exceed specified yield strength or established in accordance with Section 6.4, or as increased for cold work of forming in Section 1.5.4.2	1.5.4.2,2.2.1,2.5,3.2, 3.3.1,3.3.2,3.3.4,3.3.5, 3.6.1,3.6.2,5.2.1, App. C.1,App. B
F_{yc}	Yield strength in compression	3.3.1.1
F_{yt}	Yield strength in tension	3.3.1.1
F_{ys}	Yield strength of stiffener steel	App. C.1
F_{yv}	Shear yield strength	3.3.2
F_{yw}	Lower value of yield strength in beam web F_y or stiffener section F_{ys}	App. C.1
f	Stress in compression element computed on the basis of the effective design width	2.2.1,2.2.2, 2.3.2,2.4,2.4.1
f_{av}	Average computed stress in full, unreduced flange width	2.1.1
f_b	Perceptible stress for local distortion	3.3.1.1,3.4
f_d	Computed compressive stress in element being considered. Calculations are based on effective section at load for which deflections are determined.	2.2.1,2.2.2, 2.3.1,2.4.1,2.4.2
f_{d1}, f_{d2}	Computed stresses f_1 and f_2 as shown in Figure 2. Calculations are based on the effective section at the load for which deflections are determined	2.2.2

Symbol	Definition	Section
f_{d3}	Computed stress f_3 in edge stiffener, as shown in Figure 5. Calculations are based on the effective section at the load for which deflections are determined.	2.3.2
f_v	Computed shear stress on bolt	5.3.4
f_1, f_2	Web stresses defined by Figure 2	2.2.2
f_3	Edge stiffener stress defined by Figure 5	2.3.2
G_o	Initial shear modulus	3.3.2
G_s	Secant shear modulus	3.3.2
G_s/G_o	Plasticity reduction factor for shear stress	3.3.2
g	Vertical distance between two rows of connections nearest to top and bottom flanges	4.1.1
h	Depth of flat portion of web measured along plane of web	2.1.2, 3.3.2, 3.3.4, App. C.2
I_a	Adequate moment of inertia of stiffener so that each component element will behave as stiffened element	2.4.1, 2.4.2
I_b	Moment of inertia of full, unreduced section about axis of bending	3.5
I_s	Actual moment of inertia of full stiffener about its own centroidal axis parallel to the element to be stiffened	2.1.1, 2.4, 2.4.1, 2.4.2, 2.5
I_{sf}	Moment of inertia of full area of multiple stiffened element, including intermediate stiffeners, about its own centroidal axis parallel to element to be stiffened	2.5
I_x, I_y	Moments of inertia of full section about principal axes	4.1.1, 4.3.2.2
I_{xy}	Product of inertia of full section about major and minor centroidal axes	4.3.2.2
I_{yc}	Moment of inertia of compression portion of section about gravity axis of the entire section about the y-axis	3.3.1.2
J	St. Venant torsion constant	3.3.1.2
j	Section property for torsional-flexural buckling	3.3.1.2
K	Effective length factor	3.4, 3.4.1
K'	A constant	4.3.2.2
K_b	Effective length factor in plane of bending	3.5
K_c	Reduction factor due to local buckling	3.6.1, 3.6.2
K_t	Effective length factor for torsion	3.3.1.2
K_x	Effective length factor for bending about x-axis	3.3.1.2
K_y	Effective length factor for bending about y-axis	3.3.1.2
k	Plate buckling coefficient	2.2.1, 2.2.2, 2.3.1, 2.3.2, 2.4.1, 2.4.2
k_v	Shear buckling coefficient	App. C.2
L	Full span for simple beams, distance between inflection points for continuous beams, twice length of cantilever beams	4.1.1, 2.1.1
L	Length of fillet weld	5.2.2
L	Unbraced length of member	3.3.1.2, 3.4.1
L_b	Actual unbraced length in plane of bending	3.5
L_n	Nominal live load	1.5.2
L_{rn}	Nominal roof live load	1.5.2
L_{st}	Length of transverse stiffener	App. C.1
L_t	Unbraced length of compression member for torsion	3.3.1.2
L_x	Unbraced length of compression member for bending about x-axis	3.3.1.2
L_y	Unbraced length of compression member for bending about y-axis	3.3.1.2
M_c	Critical moment	3.3.1.2
M_{ld}	Permissible moment for local distortions	3.3.1.1

NOTATION

Symbol	Definition	Section
M_n	Nominal moment strength	3.3.1.1,3.3.1.2, 3.3.3,3.3.5,3.6.1
M_{nx},M_{ny}	Nominal flexural strength about centroidal axes determined in accordance with Section 3.3	3.5
M_u	Required flexural strength	3.3.3,3.3.5
M_{ux}	Required flexural strength bent about x -axis	3.5
M_{uy}	Required flexural strength bent about y -axis	3.5
M_y	Moment causing maximum strain ϵ_y	2.2.1,3.3.1.2
M_1	Smaller end moment	3.3.1.2,3.5
M_2	Larger end moment	3.3.1.2,3.5
m	Distance from shear center of one channel to mid-plane of its web	4.1.1,4.3.2.2
N	Actual length of bearing	3.3.4
n	Coefficient	App. B
P	Concentrated load or reaction	4.1.1
P_E	$\pi^2 E_o I_b / (K_b L_b)^2$	3.5
P_L	Force to be resisted by intermediate beam brace	4.3.2.2
P_{ld}	Permissible load for load distortions	3.4
P_n	Nominal axial strength of member	3.3.4,3.3.5,3.4,3.6.2
P_n	Nominal strength of connection	5.2.1,5.2.2,5.2.3, 5.3.1,5.3.2,5.3.3,5.3.4
P_{no}	Nominal axial load determined in accordance with Section 3.4 for $F_n = F_y$.	3.5
P_u	Required axial strength	3.3.5,3.5
q	Uniformly distributed factored load in plane of web	4.1.1
R_p	Average tested value	6.2
R	Inside bend radius	3.3.4
R_a	Allowable design strength	App. D
R_{rn}	Nominal roof rain load	1.5.2
R_n	Nominal strength	1.5.1.1,1.5.3
r	Radius of gyration of full, unreduced cross section	3.3.1.1,3.4.1
r	Force transmitted by the bolt or bolts at the section considered, divided by the tension force in the member at that section	5.3.2
r_{cy}	Radius of gyration of one channel about its centroidal axis parallel to web	4.1.1
r_I	Radius of gyration of I-section about the axis perpendicular to the direction in which buckling would occur for given conditions of end support and intermediate bracing	4.1.1
r_o	Polar radius of gyration of cross section about shear center	3.3.1.2,3.4.3
r_x, r_y	Radius of gyration of cross section about centroidal principal axes	3.3.1.2
S	$1.28\sqrt{E_o}/f$	2.4,2.4.1
S_c	Elastic section modulus of effective section calculated at stress M_c/S_f in extreme compression fiber	3.3.1.1,3.3.1.2
S_e	Elastic section modulus of effective section calculated with extreme compression or tension fiber at F_y	3.3.1.1
S_F	Elastic section modulus of full, unreduced section for the extreme compression fiber	3.3.1.1,3.3.1.2,3.6.1
S_n	Nominal snow load	1.5.2
s	Fastener spacing	4.1.2

Symbol	Definition	Section
s	Spacing in line of stress of welds, rivets, or bolts connecting a compression cover plate or sheet to a nonintegral or other element	5.3.2
s	Weld spacing	4.1.1
s_{\max}	Maximum permissible longitudinal spacing of welds or other connectors joining two channels to form I-section	4.1.1
T_n	Nominal tensile strength	3.2
T_s	Strength of connection in tension	4.1.1
t	Base steel thickness of any element or section	1.1.2,1.3.4,1.5.2.1, 2.1.1,2.1.2,2.2.1,2.4, 2.4.1,2.4.2,2.5,2.6.1, 3.3.1.1,3.3.1.3,3.3.2, 3.3.4,3.3.5,3.4,3.6.1, 3.6.2,4.1.2,5.2.2,5.3.2, App. C
t	Thickness of thinnest connected part	5.3.1
t_s	Equivalent thickness of multiple-stiffened element	2.5, App. C1
t_w	Effective throat of weld	5.2.2
V	Actual shear strength	3.3.3
V_n	Nominal shear strength	3.3.2
V_u	Required shear strength	3.3.3
w	Flat width of element exclusive of radii	1.1.2,2.1.2,2.2.1,2.4, 2.4.1,2.4.2,2.5,3.3.1.1, 3.3.1.3,3.3.2,3.3.4, 3.3.5,3.4,3.6.1, 3.6.2,4.1.2
w	Flat width of bearing plate	3.3.5
w_f	Width of flange projection beyond web or half distance between webs for box- or U-type sections	2.1.1c
w_f	Projection of flanges from inside face or web	2.1.1b
W_n	Nominal wind load	1.5.2
x	Distance from concentrated load to brace	4.3.2
x_o	Distance from shear center to centroid along the principal x -axis	3.3.1.2,3.4.3
Y	Yield strength of web steel divided by yield strength of stiffener steel	App. C.2
α	Reduction factor for computing effective area of stiffener section	2.5
α	Coefficient, for sections with stiffening lips, $\alpha = 1.0$; for sections without stiffening lips, $\alpha = 0$	4.1.1
$1/\alpha_{nx}$	Magnification factor	3.5
$1/\alpha_{ny}$	Magnification factor	3.5
β	Coefficient	3.4.3
η	Plasticity reduction factor	3.3.1.1,3.4, App. B
θ	Angle between web and bearing surface $\geq 45^\circ$ but no more than 90°	3.3.4
μ	Poisson's ratio in elastic range = 0.3	3.3.1.1,3.4
σ_{ex}	Buckling stress about x -axis	3.4.2,3.4.3
σ_{ey}	Buckling stress about y -axis	3.3.1.2
σ_t	Torsional buckling stress	3.3.1.2,3.4.3
σ	Normal stress	App. B
ε	Normal strain	App. B
ρ	Reduction factor	2.2.1
λ	Slenderness factor	2.2.1

NOTATION

Symbol	Definition	Section
λ_c	3.048C	3.6.1
ψ	f_2/f_1	2.2.2
ϕ	Resistance factor	1.1.1,1.5.1.1,5.2,5.2.1, 5.2.2,5.2.3,5.3.1,5.3.2, 5.3.3,5.3.4,6.2, App. D
ϕ_b	Resistance factor for bending strength	3.3.1,3.3.1.1,3.3.1.2, 3.3.3,3.3.5,3.5, 3.6.1,3.7
ϕ_c	Resistance factor for concentrically loaded compression member	3.4,3.5,3.6.2,App. C
ϕ_d	Resistance factor for local distortion	3.3.1.1,3.4
ϕ_t	Resistance factor for tension member	3.2
ϕ_v	Resistance factor for shear strength	3.3.2,3.3.3,App. C
ϕ_w	Resistance factor for web crippling strength	3.3.4,3.3.5
Ω	Safety factor	App. D

CONVERSION TABLE

This table contains some conversion factors between US Customary and SI Metric Units. The formulas included in this Specification are generally nondimensional, except that some adjustments are required for SI Unit in Section 3.3.4.

Metric Conversion Table

	To convert	to	Multiply by
Length	in.	mm	25.4
	mm	in.	0.03937
	ft	m	0.30480
	m	ft	3.28084
Area	in. ²	mm ²	645.160
	mm ²	in. ²	0.00155
	ft ²	m ²	0.09290
	m ²	ft ²	10.76391
Forces	kip force	kN	4.448
	lb	N	4.448
	kN	kip	0.2248
Stresses	ksi	MPa	6.895
	MPa	ksi	0.145
Moments	ft-kip	kN-m	1.356
	kN-m	ft-kip	0.7376
Uniform loading	kip/ft	kN/m	14.59
	kN/m	kip/ft	0.06852
	kip/ft ²	kN/m ²	47.88
	kN/m ²	kip/ft ²	0.02089
	psf	N/m ²	47.88
Angle	degree	radian	0.01745
	radian	degree	57.29579

Specification for the Design of Cold-Formed Stainless Steel Structural Members

1. GENERAL PROVISIONS

1.1 Limits of Applicability and Terms

1.1.1 Scope and Limits of Applicability

This ASCE Standard Specification shall apply to the design of structural members cold-formed to shape from annealed and cold-rolled sheet, strip, plate, or flat bar stainless steels when used for load-carrying purposes in buildings and other statically loaded structures. It may also be used for structures other than buildings provided appropriate allowances are made for thermal and/or dynamic effects. Appendices to this Specification shall be considered as integral parts of the Specification.

This ASCE Standard supersedes the 1974 edition of the Specification for the Design of Cold-Formed Stainless Steel Structural Members issued by the American Iron and Steel Institute.

1.1.2 Terms

Where the following terms appear in this Specification they shall have the meaning herein indicated:

1. *Stiffened or Partially Stiffened Compression Elements.* A stiffened or partially stiffened compression element is a flat compression element (i.e., a plane compression flange of a flexural member or a plane web or flange of a compression member) of which both edges parallel to the direction of stress are stiffened by a web, flange, stiffening lip, intermediate stiffener, or the like.
2. *Unstiffened Compression Elements.* An unstiffened compression element is a flat compression element which is stiffened at only one edge parallel to the direction of stress.
3. *Multiple-Stiffened Elements.* A multiple-stiffened element is an element that is stiffened between webs, or between a web and a stiffened edge, by means of intermediate stiffeners which are parallel to the direction of stress. A sub-element is the portion between adjacent stiffeners or between web and intermediate stiffener or between edge and intermediate stiffener.
4. *Flat-Width-to-Thickness Ratio.* The flat width of an element measured along its plane, divided by its thickness.
5. *Effective Design Width.* Where the flat width of an element is reduced for design purposes, the reduced design width is termed the effective width or effective design width.
6. *Stress.* Stress as used in this Specification means force per unit area.
7. *Performance Test.* A performance test is a test made on structural members, connections, and assemblies whose performance cannot be determined by the provisions of Sections 1 through 5 of this Specification or its specific references.
8. *Specified Minimum Yield Strength.* The specified minimum yield strength is the lower limit of yield strength which varies with the rolling direction (transverse or longitudinal) and the type of stress (tension or compression) must be equalled or exceeded in a specification test to qualify a lot of steel for use in a cold-formed stainless steel structural member designed at that yield strength.
9. *Cold-Formed Stainless Steel Structural Members.* Cold-formed stainless steel structural members are shapes which are manufactured by press-braking blanks sheared from sheets, cut lengths of coils or plates, or by roll forming slit widths from cold- or hot-rolled coils or sheets; both forming operations being performed at ambient room temperature, that is, without manifest addition of heat such as would be required for hot forming.
10. *Load and Resistance Factor Design (LRFD).* A method of proportioning structural components (members, connectors, connecting elements and assemblies) such that no applicable limit state is exceeded when the structure is subjected to all appropriate load combinations.
11. *Design Strength.* Factored resistance or strength (force, moment, as appropriate), ϕR_n , provided by the structural component.
12. *Required Strength.* Load effect (force, moment, as appropriate) acting on the structural component determined by structural analysis from the factored loads (using most appropriate critical load combinations).
13. *Nominal Loads.* The magnitudes of the loads specified by the applicable code.
14. *Allowable Stress Design (ASD).* A method of proportioning structural components on the basis of working loads and allowable capacities.

1.1.3 Units of Symbols and Terms

The Specification is written so that any compatible system of units may be used except where explicitly stated otherwise in the text of these provisions.