

ASME B31T-2021
(Revision of ASME B31T-2018)

Standard Toughness Requirements for Piping

ASME Code for Pressure Piping, B31

AN AMERICAN NATIONAL STANDARD



**The American Society of
Mechanical Engineers**

ASME B31T-2021
(Revision of ASME B31T-2018)

Standard Toughness Requirements for Piping

ASME Code for Pressure Piping, B31

AN AMERICAN NATIONAL STANDARD



**The American Society of
Mechanical Engineers**

Two Park Avenue • New York, NY • 10016 USA

Date of Issuance: July 30, 2021

The next edition of this Standard is scheduled for publication in 2024.

ASME issues written replies to inquiries concerning interpretations of technical aspects of this Standard. Interpretations are published on the Committee web page and under <http://go.asme.org/Interpretations>. Periodically certain actions of the ASME B31 Committee may be published as Cases. Cases are published on the ASME website under the B31 Committee Page at <http://go.asme.org/B31committee> as they are issued.

Errata to codes and standards may be posted on the ASME website under the Committee Pages of the associated code and standards to provide corrections to incorrectly published items, or to correct typographical or grammatical errors in codes and standards. Such errata shall be used on the date posted.

The B31 Committee Page can be found at <http://go.asme.org/B31committee>. The associated B31 Committee Pages for each code and standard can be accessed from this main page. There is an option available to automatically receive an e-mail notification when errata are posted to a particular code or standard. This option can be found on the appropriate Committee Page after selecting "Errata" in the "Publication Information" section.

ASME is the registered trademark of The American Society of Mechanical Engineers.

This code or standard was developed under procedures agreed to as meeting the criteria for American National Standards. The Standards Committee that approved the code or standard was balanced to assure that individuals from competent and concerned interests have had an opportunity to participate. The proposed code or standard was made available for public review and comment that provides an opportunity for additional public input from industry, academia, regulatory agencies, and the public-at-large.

ASME does not "approve," "rate," or "endorse" an item, construction, proprietary device, or activity.

ASME does not take any position with respect to the validity of any patent rights asserted in connection with any items mentioned in this document, and does not undertake to insure anyone utilizing a standard against liability for infringement of any applicable letters patent, nor assume any such liability. Users of a code or standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

Participation by federal agency representative(s) or person(s) affiliated with industry is not to be interpreted as government or industry endorsement of this code or standard.

ASME accepts responsibility for only those interpretations of this document issued in accordance with the established ASME procedures and policies, which precludes the issuance of interpretations by individuals.

No part of this document may be reproduced in any form,
in an electronic retrieval system or otherwise,
without the prior written permission of the publisher.

The American Society of Mechanical Engineers
Two Park Avenue, New York, NY 10016-5990

Copyright © 2021 by
THE AMERICAN SOCIETY OF MECHANICAL ENGINEERS
All rights reserved
Printed in U.S.A.

CONTENTS

Foreword	i
Committee Roster	v
Correspondence With the B31 Committee	vi
Introduction	viii
Summary of Changes	x
1 General	1
2 Glossary	1
3 Low-Temperature Ranges and Requirements	1
4 Impact Testing Methods and Acceptance Criteria	6
5 References	8
 Mandatory Appendices	
I Impact Test Exemption Curves	37
II Stress Ratio Curves	43
III Material Groupings by T-Number	45
 Nonmandatory Appendices	
A Flowchart of Requirements	53
B Guidelines for Establishing T-Number Group	55
 Figures	
I-1 Impact Test Exemption Curves for T-Number Groups CS A, CS B, CS C, and CS D (U.S. Customary Units)	38
I-1M Impact Test Exemption Curves for T-Number Groups CS A, CS B, CS C, and CS D (SI Units) ..	39
II-1 Stress Ratio Curves (U.S. Customary Units)	43
II-1M Stress Ratio Curves (SI Units)	44
A-1 Flowchart of Requirements	54
 Tables	
3.1-1 Low-Temperature Service Requirements by Material Group	12
3.2-1 Material Groupings by Material Specification	28
4.1.2-1 Charpy Impact Test (Absorbed Energy) Temperature Reduction for Material or Specimens <10 mm (0.394 in.)	35
4.3.1-1 Minimum Required Charpy V-Notch Impact Values	36
4.4.1 Tabular Values for Figures I-1 and I-1M	40
III-1 Material Groupings by T-Number	46

FOREWORD

In 2000, the ASME B31 Code for Pressure Piping, Materials Technical Committee (MTC) determined that there was a need to develop a standard set of toughness requirements for piping components that can be adopted by reference by various codes, standards, and specifications. At the time, the requirements of the ASME B31 Code books varied, with some having no requirements at all.

This Standard is intended to provide requirements for evaluating the suitability of materials used in piping systems for piping that may be subject to brittle failure due to low-temperature service conditions.

Under direction of ASME Standards and Certification, both SI and U.S. Customary units are provided. The 2010 edition of this Standard was approved by the American National Standards Institute (ANSI) on April 20, 2010.

The 2015 edition of this Standard was approved by ANSI on October 21, 2015.

The 2018 edition of this Standard was approved by ANSI on December 6, 2018.

The 2021 edition of this Standard was approved by ANSI on July 15, 2021.

ASME B31 COMMITTEE

Code for Pressure Piping

(The following is the roster of the Committee at the time of the approval of this Standard.)

STANDARDS COMMITTEE OFFICERS

C. H. Eskridge, Jr., *Chair*
K. A. Vilminot, *Vice Chair*
J. Oh, *Secretary*

STANDARDS COMMITTEE PERSONNEL

D. D. Anderson , TransCanada Pipeline US	G. A. Jolly , Samshin, Ltd.
R. J. T. Appleby , Consultant	K. Kaplan , Consultant
K. C. Bodenhamer , TRC Pipeline Services	C. Kolovich , Quest Integrity
R. Bojarczuk , Retired	W. J. Mauro , Consultant
M. R. Braz , MRBraz and Associates, PLLC	J. E. Meyer , CDM Smith – Industrial Division
M. Burkhardt , The Burkhardt Group, Inc.	T. Monday , Team Industries, Inc.
R. D. Campbell , Bechtel Corp.	J. Oh , The American Society of Mechanical Engineers
J. S. Chin , TC Energy	D. W. Rahoi , CCM 2000
D. D. Christian , Victaulic	R. Reamer , Furness Industries Group, LLC
R. P. Deubler , Becht Engineering Co., Inc.	M. J. Rosefeldt , RSI Pipeline Solutions, LLC
D. Diehl , Retired	J. S. Schmitz , Southwest Gas Corp.
M. Engelkemier , Cargill	S. K. Sinha , Lucius Pitkin, Inc.
C. H. Eskridge, Jr. , Worley ECR	W. J. Sperko , Sperko Engineering Services, Inc.
D. J. Fetzner , Retired	W. W. Tatar , FM Global
D. R. Frikken , Becht Engineering Co., Inc.	K. A. Vilminot , Commonwealth Associates, Inc.
R. A. Grichuk , S&B Engineers and Constructors, Ltd.	P. D. Flenner , <i>Contributing Member</i> , Flenner Engineering Services
R. W. Haupt , Pressure Piping Engineering Associates, Inc.	M. L. Nayyar , <i>Contributing Member</i> , NICE

B31 MATERIALS TECHNICAL COMMITTEE

R. P. Deubler , <i>Chair</i> , Becht Engineering Co., Inc.	A. A. Hassan , Power Generation Engineering and Services Co.
C. Henley , <i>Vice Chair</i> , Kiewit Engineering Group, Inc.	L. Henderson, Jr. , Kiewit Engineering Group, Inc.
C. E. Rodrigues , <i>Secretary</i> , The American Society of Mechanical Engineers	G. A. Jolly , Samshin, Ltd.
J. Oh , <i>Secretary</i> , The American Society of Mechanical Engineers	C. J. Melo , S&B Engineers and Constructors, Ltd.
B. Bounds , Bechtel Corp.	K. Pham , Fluor Enterprises, Inc.
W. P. Collins , WPC Solutions, LLC	D. W. Rahoi , CCM 2000
C. H. Eskridge, Jr. , Worley ECR	R. A. Schmidt , Canadoil Forge
A. Esmaeili , APA Group	S. Tonkins , BP Americas
R. A. Grichuk , S&B Engineers and Constructors, Ltd.	D. K. Verma , Bechtel Oil Gas and Chemicals
J. Gundlach , Michigan Seamless Tube and Pipe	Z. Djilali , <i>Contributing Member</i> , Sonatrach
	M. L. Nayyar , <i>Contributing Member</i> , NICE

CORRESPONDENCE WITH THE B31 COMMITTEE

General. ASME Standards are developed and maintained with the intent to represent the consensus of concerned interests. As such, users of this Standard may interact with the Committee by requesting interpretations, proposing revisions or a case, and attending Committee meetings. Correspondence should be addressed to:

Secretary, B31 Standards Committee
The American Society of Mechanical Engineers
Two Park Avenue
New York, NY 10016-5990
<http://go.asme.org/Inquiry>

Proposing Revisions. Revisions are made periodically to the Standard to incorporate changes that appear necessary or desirable, as demonstrated by the experience gained from the application of the Standard. Approved revisions will be published periodically.

The Committee welcomes proposals for revisions to this Standard. Such proposals should be as specific as possible, citing the paragraph number(s), the proposed wording, and a detailed description of the reasons for the proposal, including any pertinent documentation.

Proposing a Case. Cases may be issued to provide alternative rules when justified, to permit early implementation of an approved revision when the need is urgent, or to provide rules not covered by the existing provisions. Cases are effective immediately upon ASME approval and shall be posted on the ASME Committee web page.

Requests for Cases shall provide a Statement of Need and Background information. The request should identify the Standard and the paragraph, figure, or table number(s), and be written as a Question and Reply in the same format as existing Cases. Requests for Cases should also indicate the applicable edition(s) of the Standard to which the proposed Case applies.

Interpretations. Upon request, the B31 Standards Committee will render an interpretation of any requirement of the Standard. Interpretations can only be rendered in response to a written request sent to the Secretary of the B31 Standards Committee.

Requests for interpretation should preferably be submitted through the online Interpretation Submittal Form. The form is accessible at <http://go.asme.org/InterpretationRequest>. Upon submittal of the form, the Inquirer will receive an automatic e-mail confirming receipt.

If the Inquirer is unable to use the online form, he/she may mail the request to the Secretary of the B31 Standards Committee at the above address. The request for an interpretation should be clear and unambiguous. It is further recommended that the Inquirer submit his/her request in the following format:

Subject: Cite the applicable paragraph number(s) and the topic of the inquiry in one or two words.
Edition: Cite the applicable edition of the Standard for which the interpretation is being requested.
Question: Phrase the question as a request for an interpretation of a specific requirement suitable for general understanding and use, not as a request for an approval of a proprietary design or situation. Please provide a condensed and precise question, composed in such a way that a "yes" or "no" reply is acceptable.
Proposed Reply(ies): Provide a proposed reply(ies) in the form of "Yes" or "No," with explanation as needed. If entering replies to more than one question, please number the questions and replies.
Background Information: Provide the Committee with any background information that will assist the Committee in understanding the inquiry. The Inquirer may also include any plans or drawings that are necessary to explain the question; however, they should not contain proprietary names or information.

Requests that are not in the format described above may be rewritten in the appropriate format by the Committee prior to being answered, which may inadvertently change the intent of the original request.

Moreover, ASME does not act as a consultant for specific engineering problems or for the general application or understanding of the Standard requirements. If, based on the inquiry information submitted, it is the opinion of the Committee that the Inquirer should seek assistance, the inquiry will be returned with the recommendation that such assistance be obtained.

ASME procedures provide for reconsideration of any interpretation when or if additional information that might affect an interpretation is available. Further, persons aggrieved by an interpretation may appeal to the cognizant ASME Committee or Subcommittee. ASME does not “approve,” “certify,” “rate,” or “endorse” any item, construction, proprietary device, or activity.

Attending Committee Meetings. The B31 Standards Committee regularly holds meetings and/or telephone conferences that are open to the public. Persons wishing to attend any meeting and/or telephone conference should contact the Secretary of the B31 Standards Committee.

INTRODUCTION

The ASME B31 Code for Pressure Piping consists of a number of individually published Sections and Standards, each an American National Standard, under the direction of the ASME B31 Code for Pressure Piping Committee.

Rules for each Section reflect the kinds of piping installations considered during its development, as follows:

- B31.1 Power Piping: piping typically found in electric-generating stations, industrial and institutional plants, geothermal and solar power applications, and central and district heating and cooling systems
- B31.3 Process Piping: piping typically found in petroleum refineries; onshore and offshore petroleum and natural gas production facilities; chemical, pharmaceutical, textile, paper, ore-processing, semiconductor, and cryogenic plants; food- and beverage-processing facilities; and related processing plants and terminals
- B31.4 Pipeline Transportation Systems for Liquids and Slurries: piping that transports products that are predominately liquid between plants and terminals, and within terminals and pumping, regulating, and metering stations
- B31.5 Refrigeration Piping and Heat Transfer Components: piping for refrigerant and secondary coolants
- B31.8 Gas Transportation and Distribution Piping Systems: piping that transports products that are predominately gas between sources and terminals, including compressor, regulating, and metering stations and gas-gathering pipelines
- B31.9 Building Services Piping: piping typically found in industrial, institutional, commercial, and public buildings and multi-unit residences that do not require the range of sizes, pressures, and temperatures covered by ASME B31.1
- B31.12 Hydrogen Piping and Pipelines: piping in gaseous and liquid hydrogen service and pipelines for gaseous hydrogen service

The following Codes and Standards provide guidance for a specific task found in one or more ASME B31 Section publications:

- B31E Seismic Design and Retrofit of Above-ground Piping Systems: establishes a method for the seismic design of above-ground metallic piping systems in the scope of the ASME B31 Code for Pressure Piping
- B31G Remaining Strength of Corroded Pipelines: provides a simplified procedure to determine the effect of wall loss due to corrosion or corrosion-like defects on the pressure integrity in pipeline systems
- B31J Stress Intensification Factors (*i*-Factors), Flexibility Factors (*k*-Factors), and Their Determination for Metallic Piping Components: provides a standardized method to develop the stress intensification factors (*i*-factors), flexibility factors (*k*-factors), and sustained stress factors used in ASME B31 piping analysis
- B31P Standard Heat Treatments for Fabrication Processes: provides requirements for heat treatment of piping assemblies that meet the requirements of ASME B31 Code Sections
- B31Q Pipeline Personnel Qualification: establishes the requirements for developing and implementing an effective Pipeline Personnel Qualification Program
- B31T Standard Toughness Requirements for Piping: provides requirements for evaluating the suitability of materials used in piping systems for piping that may be subject to brittle failure due to low-temperature service conditions

This is ASME B31T, Standard Toughness Requirements for Piping. Hereafter, in this Introduction and in the text of ASME B31T, where the word “Standard” is used without specific identification, it means ASME B31T.

This Standard provides requirements for evaluating the suitability of materials used in piping systems for piping that may be subject to brittle failure due to low-temperature service conditions. While low-temperature service is

usually considered to be below ambient temperature, brittle failure can occur at temperatures above ambient temperature for certain combinations of materials, thicknesses, and stress levels. The definition of “low-temperature service” as used in this Standard, therefore, varies widely across the many applications for which piping systems are used. For a building service air line, low temperature may be 0°C (32°F), whereas for a cryogenic piping system, it could easily be -185°C (-300°F). However, the principles used to evaluate the suitability of a piping system as related to service temperature by evaluating the toughness of the material can be applied across a wide temperature range, and this Standard has been established to provide uniform guidance in this area.

Suitability of piping systems for low-temperature service is a function of several variables, including material properties, design loadings, and fabrication procedures. The three primary factors that generally control the susceptibility for brittle fracture are material toughness, crack size, and tensile stress level. There are a wide variety of services where low-temperature suitability need not even be considered; however, a screening criterion is necessary to determine this.

One objective of this Standard is to provide a simple approach to evaluate whether additional consideration is necessary to evaluate suitability for low-temperature service. This is done by establishing a low-temperature service limit for various materials. Services at or warmer than this limit are not considered low temperature, and additional considerations relative to suitability are not required.

For services colder than this limit, various requirements are provided that, when met, qualify the material for low-temperature services. These requirements include impact testing, qualification of welding and other fabrication procedures, and limiting the design loadings.

The low-temperature service limit established herein is based on a reasonable degree of assurance that at this temperature, the material will have a ductile failure mode. The actual ductile-to-brittle transition temperature for a given material specification will vary based on actual heat chemistry of the material and subsequent processing. For critical applications, the design engineer can select materials with a lower low-temperature service limit or require impact testing. On less-critical applications, material with a higher low-temperature service limit

may be acceptable. The final selection is left to the code, standard, or specification referencing this Standard and the design engineer (when permitted by the code, standard, or specification referencing this Standard).

To keep the number of sets of requirements to a minimum, material groupings have been established, and a unique set of requirements have been provided for each group. These groups are assigned “T numbers” for easy reference. Although most materials used in piping systems are listed, some are not and these unlisted materials are not addressed in this Standard. Where permitted by the code, standard, or specification referencing this Standard, these requirements may be used for unlisted materials. The code, standard, or specification referencing this Standard may establish the correct T-number group for the material or may invoke the testing and other requirements of this Standard using the worst-case assumption that the design minimum temperature is colder than the temperatures that would allow exemption from any of the requirements of this Standard. The guidelines for establishing the correct T-number group are provided in [Nonmandatory Appendix P](#).

Either International System (SI, also known as metric) or U.S. Customary (USC) units may be used with this edition. Local customary units may also be used to demonstrate compliance with this Standard. One system of units should be used consistently for requirements applying to a specific installation. It is the responsibility of the organization performing calculations to ensure that a consistent system of units is used.

The ASME B31 Committee is organized and operates under procedures of ASME that have been accredited by the American National Standards Institute. The Committee is continuing and keeps all Code Sections and Standards current with new developments in methods, materials, construction, and industrial practice.

This Standard may be invoked in whole or in part by various codes, standards, or specifications and is only mandatory when so invoked. The applicable edition of this Standard shall be as specified by the code, standard, or specification referencing this Standard. It is intended that this edition of the ASME B31T Standard not be retroactive. Users of this Standard are cautioned against making use of Standard revisions without assurance that they are acceptable to the proper authorities in the jurisdiction where the material is to be installed.

ASME B31T-2021

SUMMARY OF CHANGES

Following approval by the ASME B31 Committee and ASME, and after public review, ASME B31T-2021 was approved by the American National Standards Institute on July 15, 2021.

ASME B31T-2021 has replaced the word “Code” with “Standard” in all references to itself. In addition, this edition includes the following changes identified by a margin note, **(21)**.

<i>Page</i>	<i>Location</i>	<i>Change</i>
viii	Introduction	Added
1	1	Revised in its entirety
1	2	(1) Definition of <i>fully deoxidized steel</i> revised (2) Definition of <i>governing thickness</i> added
1	3.2	First sentence revised
2	3.3	Revised in its entirety
2	3.4	Revised
2	3.5	Revised
3	3.7.1	First two paragraphs revised
3	3.7.2.2	Second paragraph revised
3	3.7.2.3	First two paragraphs revised
5	3.7.4.2	Last paragraph revised
6	3.7.4.3	Revised
6	4.1	Revised
6	4.2	Second paragraph and subpara. (a) revised
8	5	Added
12	Table 3.1-1	Second column head revised
28	Table 3.2-1	(1) First A134 row and A167, A202, A226, A325, and A570 rows deleted (2) Last A134 row, A283 row, and first two A320 rows revised (3) Penultimate A193 row, last A453 row, A1011 row, and General Note (a) added
36	Table 4.5.1-1	First column revised to show SI units as primary
37	Mandatory Appendix I	Title and first paragraph revised
38	Figure I-1	Title, axis and curve labels, and curve CS B revised
39	Figure I-1M	Title and axis and curve labels revised
40	Table I-1	Column heads revised
46	Table III-1	(1) CS –20, A226 and A325; CS A, A570; CS B, first A134; LA –20, A202; SS –325, A167; and SS –20, A167 rows deleted (2) CS –20, F3125; CS A, A1011; SS –425, A193; SS –325, A453; and General Note (a) added (3) CS A, last A134 and A283; SS -425, A320; and SS -325, A193 and A320 rows revised

<i>Page</i>	<i>Location</i>	<i>Change</i>
54	Figure A-1	First two boxes under “Low-Temperature Service Requirements Evaluation” revised
55	Nonmandatory Appendix B	“T-number(s)” revised to “T-number group(s)” throughout

INTENTIONALLY LEFT BLANK

STANDARD TOUGHNESS REQUIREMENTS FOR PIPING

(21) 1 GENERAL

1.1 Scope

This Standard provides requirements for evaluating the suitability of materials used in piping systems for piping that may be subject to brittle failure due to low-temperature service conditions.

1.2 Units of Measure

This Standard states values in both International System (SI, also known as metric) and U.S. Customary (USC) units. Within the text, the USC units are shown in parentheses or in separate tables. The values stated in each system are not exact equivalents; therefore, each system of units should be used independently of the other.

When separate equations are provided for SI and USC units, those equations shall be executed using variables in the units associated with the specific equation. The result obtained from execution of these equations may be converted to other units.

When necessary to convert from one system of units to another, conversion should be made by rounding the values to the number of significant digits of implied precision in the starting value but not less than four significant digits for use in calculations.

(21) 2 GLOSSARY

CVN: the abbreviation for Charpy V-notch.

design minimum temperature: the lowest component temperature expected in service.

fully deoxidized steel: steel that has been deoxidized, either by the addition of strong deoxidizing agents or by vacuum treatment, to reduce the oxygen content to such a level that no reaction occurs between the carbon and oxygen during solidification. Also known as killed steel. Steels that are not fully deoxidized include rimmed, semi-killed, and capped steels. Limitations on the use of steels that are not fully deoxidized may be imposed by the code, standard, or specification referencing this Standard.

governing thickness: the thickness used in determining the low-temperature service limit of T-number groups CS A, CS B, CS C, and CS D in [Table 3.1-1](#). Unless defined differently in the code, standard, or specification referencing this Standard, this thickness is the nominal thickness

of the component or, for blind flanges and line blanks, $\frac{1}{4}$ of the total thickness, where the total thickness is the thickness of the blind flange or line blank, including the thickness of the facing(s), if applicable.

lower critical temperature: the temperature at which the first phase change occurs when heating a metal.

low-temperature service limit: the design minimum temperature at which additional requirements for low-temperature service do not apply.

NDT temperature: the nil ductility transition temperature.

stress ratio: the ratio of the design stress to an allowable stress. (See [para. 3.6.2](#).)

T-number: a number assigned to a group of similar materials with similar low-temperature requirements. The number consists of the material type and a temperature characteristic, and possibly a suffix.

3 LOW-TEMPERATURE RANGES AND REQUIREMENTS

3.1 Low-Temperature Service Requirements

Low-temperature service requirements are contained in [Table 3.1-1](#). These requirements are established for T-number groups of materials with similar requirements. In addition to T-number group, in some cases, requirements are dependent on thickness and/or other characteristics as listed in [Table 3.1-1](#).

3.2 Material Groupings (Column 1 of [Table 3.1-1](#)) (21)

Listed materials are assigned T-number groups in [Table 3.2-1](#). (In addition, a table sorted by material type and T-number group that lists all materials in each T-number group is provided in [Mandatory Appendix III](#).) In determining the applicable T-number group for a material from [Table 3.2-1](#), consideration shall be given to the material specification, grade, and any other variables as established in the notes. The table separates the materials into types (carbon steels, low-alloy steels, etc.), and the group number is representative of the low-temperature service limit for the material; however, the low-temperature service limit may vary based on the design and fabrication requirements. Low-temperature service limits shall be determined from [Table 3.1-1](#). An "(A)" in the T-number group [e.g., CS -20(A)] indicates that materials of that group may not be used