

STP-NU-040

# UPDATE AND IMPROVE SUBSECTION NH – SIMPLIFIED ELASTIC AND INELASTIC DESIGN ANALYSIS METHODS



STP-NU-040

# UPDATE AND IMPROVE SUBSECTION NH – SIMPLIFIED ELASTIC AND INELASTIC DESIGN ANALYSIS METHODS

*Prepared by:*

Jerry J. Abou-Hanna

Douglas L. Marriott

Timothy E. McGreevy

Advanced Consulting Engineering Services, Inc.

ASME STANDARDS  
TECHNOLOGY, LLC

Date of Issuance: October 19, 2012

This report was prepared as an account of work sponsored by the U.S. Department of Energy (DOE) and the ASME Standards Technology, LLC (ASME ST-LLC).

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Neither ASME, ASME ST-LLC, the authors nor others involved in the preparation or review of this report, nor any of their respective employees, members or persons acting on their behalf, make any warranty, express or implied, or assume any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe upon privately owned rights.

Reference herein to any specific commercial product, process or service by trade name, trademark, manufacturer or otherwise does not necessarily constitute or imply its endorsement, recommendation or favoring by ASME ST-LLC or others involved in the preparation or review of this report, or any agency thereof. The views and opinions of the authors, contributors and reviewers of the report expressed herein do not necessarily reflect those of ASME ST-LLC or others involved in the preparation or review of this report, or any agency thereof.

ASME ST-LLC does not take any position with respect to the validity of any patent rights asserted in connection with any items mentioned in this document, and does not undertake to insure anyone utilizing a publication against liability for infringement of any applicable Letters Patent, nor assumes any such liability. Users of a publication are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, is entirely their own responsibility.

Participation by federal agency representative(s), or person(s) affiliated with industry is not to be interpreted as government or industry endorsement of this publication.

ASME is the registered trademark of the American Society of Mechanical Engineers.

No part of this document may be reproduced in any form,  
in an electronic retrieval system or otherwise,  
without the prior written permission of the publisher.

ASME Standards Technology, LLC  
Three Park Avenue, New York, NY 10016-5990

ISBN No. 978-0-7918-3392-6

Copyright © 2012 by  
ASME Standards Technology, LLC  
All Rights Reserved

## TABLE OF CONTENTS

Foreword .....	xi
Abstract .....	xii
1 SUBTASK 9.1 – Outline of an “Ideal” High Temperature Code .....	1
1.1 Definition of “High Temperature” .....	1
1.2 Design Loads and Failure Mechanisms to Consider .....	2
1.3 Design Criteria .....	3
1.4 Design Evaluation .....	6
1.4.1 Analysis.....	6
1.4.2 Testing.....	8
1.4.3 Surveillance.....	9
1.5 Material Properties Required to Perform a Design Assessment.....	9
1.6 Documentation .....	10
1.7 Conclusion.....	10
2 SUBTASK 9.2 OBJECTIVE .....	11
2.1 R5 .....	11
2.1.1 R5 – High Temperature.....	12
2.1.2 R5 – Design Loads .....	12
2.1.3 R5 – Failure Mechanisms.....	12
2.1.4 R5 – Design Criteria/Procedures.....	13
2.2 Monju.....	27
2.2.1 Monju – High Temperature.....	27
2.2.2 Monju – Design Loads .....	28
2.2.3 Monju – Failure Mechanisms.....	29
2.2.4 Monju – Design Criteria / Procedures.....	29
2.2.5 Monju – Summary.....	30
2.3 RCC-MR .....	45
2.3.1 RCC-MR – High Temperature.....	45
2.3.2 RCC-MR – Design Loads .....	46
2.3.3 RCC-MR – Failure Mechanisms.....	46
2.3.4 RCC-MR – Design Criteria/Procedures.....	47
2.4 ASME NH .....	64
2.4.1 ASME NH – High Temperature.....	66
2.4.2 ASME NH – Design Loads .....	66
2.4.3 ASME NH - Failure Mechanisms .....	66
2.4.4 ASME NH – Design Criteria / Procedures.....	67
2.5 API579 .....	80
2.5.1 API579 – High Temperature .....	81
2.5.2 API579 – Design Loads .....	81
2.5.3 API579 – Failure Mechanisms .....	82
2.5.4 API579 – Design Criteria / Procedures .....	83
2.6 Summary .....	98
3 SUBTASK 9.3 OBJECTIVE .....	99
3.1 Executive Summary .....	99

3.1.1	ASME NH – Summary.....	99
3.1.2	R5 – Summary.....	101
3.1.3	RCC-MR – Summary.....	103
3.1.4	MONJU – Summary.....	104
3.1.5	API579 – Summary.....	106
3.2	ASME NH.....	109
3.2.1	Primary Load Limits.....	110
3.2.2	Deformation Controlled Limits.....	112
3.3	R5 vs. ASME.....	119
3.3.1	Primary Load Limits.....	120
3.3.2	Deformation Controlled Limits.....	126
3.4	RCC-MR vs. ASME.....	131
3.4.1	Primary Load Limits.....	132
3.4.2	Deformation Controlled Limits.....	133
3.4.3	Procedures for Analyzing Creep-Fatigue.....	136
3.4.4	SUMMARY:.....	138
3.5	MONJU vs. ASME.....	139
3.5.1	Primary Load Limits.....	139
3.5.2	Deformation Controlled Limits.....	140
3.5.3	Other Deformation Related Issues.....	140
3.5.4	Material Properties.....	141
3.6	API-579 vs. ASME.....	141
3.6.1	General Comments on API 579.....	141
3.6.2	Definition of “Elevated Temperature”.....	141
3.6.3	Primary Load Limits.....	142
3.6.4	Deformation Controlled Limits.....	142
3.6.5	Material Properties.....	143
4	SUBTASK 9.4 OBJECTIVE.....	144
4.1	Executive summary.....	144
4.2	A Historical Perspective of the Limit Load and Foundations of the ASME B&PV Code.....	146
4.3	Marriage of Modern Analysis Tools with Foundations of the ETD Code.....	151
4.4	Part 1: Terminology.....	154
4.5	Part 2: A Summary of Limit Analysis and Various Numerical Approaches.....	155
4.5.1	General Procedure for Limit Analysis.....	155
4.5.2	Shakedown and Ratcheting Proofs.....	156
4.5.3	Elastic Compensation.....	157
4.5.4	Linear Programming.....	158
4.5.5	Numerical Optimization Methods for Limit and Shakedown Analysis.....	158
4.5.6	Summary.....	159
4.6	Part 3: Primary Load Limits.....	159
4.6.1	The European ‘Pressure Equipment Directive’.....	159
4.6.2	DOE-ORNL Gen IV / NGNP Supported Investigations.....	164
4.6.3	ASME SG-ETD Exposure to the Reference Stress Approach.....	168
4.6.4	Reference Stress and Weldments.....	168
4.6.5	Summary.....	170
4.7	Part 4: Deformation Controlled Limits.....	170

4.7.1	Steady Cyclic State and Rapid vs. Slow Cycle .....	171
4.7.2	Core Stress and Shakedown/Ratcheting Reference Stress .....	172
4.7.3	Types of Cyclic Limit Analysis.....	174
4.7.4	Approaches Not Based Upon an Elastic Core.....	175
4.7.5	Approaches Based Upon an Elastic Core.....	178
4.7.6	Summary .....	184
4.8	Summary .....	184
5	SUBTASK 9.5 OBJECTIVE.....	186
5.1	Review of Existing ETD Aspects of the ASME Code .....	186
5.2	Recommendations .....	188
5.2.1	General Comments on the Needs for Change .....	188
5.2.2	Summary of Recommendations .....	194
6	SUBTASK 9.6 OBJECTIVE.....	196
6.1	Recommendations for Round-Robin Benchmark Problems .....	196
6.1.1	Introduction .....	196
6.1.2	Subtask Objective.....	196
6.1.3	Information Sought .....	196
6.1.4	Purpose.....	197
6.1.5	Details sought:.....	197
6.2	Presentation of Round-Robin Benchmark Problems/Cases .....	198
6.3	Issues and Purpose of Round-Robin Problems: .....	198
6.4	Simplified Methods Recommended for a Round-Robin .....	199
6.5	Description of Round-Robin Benchmark Problems.....	203
6.5.1	C1: Y-Junction and V Liner Support (V-Ring).....	203
6.5.2	C2: The Harwell Thermal Ratcheting Experiment.....	205
6.5.3	CP3 and CP4: Westinghouse/ORNL Validation of Inelastic Analysis by Full-Scale Component Testing of Nozzles and Elbows.....	207
6.5.4	P5: Analysis of the Typical Failures of Three Welded Ferritic Pressure Vessels... 212	
6.5.5	C6: ORNL Creep Ratcheting Studies of Beams, Circular Plates and Stepped Cylinders .....	215
6.5.6	P7: Penny and Marriott - Creep of Aluminum Alloy Spherical Pressure Vessel Nozzle to Failure.....	218
6.5.7	CP8: Goodall's Experiments of Simple Plates, Plates with Notches and Cylinder-Cylinder Intersections .....	219
6.5.8	CP9: NLEFFS Project- Experimental and Analytical Investigation of the Elevated Temperature Performance of a Number of Welded and Unwelded Pressure Vessels .....	222
6.5.9	CP10: Igari's Ratcheting Response of Pipes and Elbows under Cyclic Displacement Controlled Loads .....	222
6.5.10	P11: Corum-Battiste Experimental and analytical data on a typical nozzle for LMFBR/CRBRP-IHX.....	225
6.5.11	P12: D.L. Marriott – Welded Spacer Connecting Adjacent Legs of a Serpentine Boiler Tube Platen.....	227
6.6	Useful Other Cases and Resources.....	229
6.6.1	Use of Isochronous curves to predict inelastic strain: .....	229
6.6.2	Shakedown, Ratchet and Reversed Plasticity Limits .....	229
6.6.3	Inelastic Strain in Variable Cycle Loading at Elevated Temperatures:.....	229
6.6.4	The ECCC Database of Component Tests and Assessments: .....	229

6.7 Minimum Material Data Requirements.....	230
6.8 Summary .....	232
References .....	233
APPENDIX B.....	257
Acknowledgments.....	269

Currently in preview, click buy full versi

## LIST OF TABLES

Table 1: R5 High Temperature.....	14
Table 2: R5 Design Loads.....	15
Table 3: R5 Design Loads.....	16
Table 4: R5 Failure Mechanisms.....	17
Table 5: R5 Failure Mechanisms.....	18
Table 6: R5 Failure Mechanisms.....	19
Table 7: R5 Design Criteria/Procedures.....	20
Table 8: R5 Design Criteria / Procedures.....	21
Table 9: R5 Design Criteria / Procedures.....	22
Table 10: R5 Design Criteria / Procedures.....	23
Table 11: R5 Design Criteria / Procedures.....	24
Table 12: R5: Design Criteria / Procedures.....	25
Table 13: R5 Design Criteria / Procedures.....	26
Table 14: Monju High Temperature.....	32
Table 15: Monju Design Loads.....	33
Table 16: Monju Design Loads.....	34
Table 17: Monju Failure Mechanisms.....	35
Table 18: Monju Failure Mechanisms.....	36
Table 19: Monju Failure Mechanisms.....	37
Table 20: Monju Design Criteria / Procedures.....	38
Table 21: Monju Design Criteria / Procedures.....	39
Table 22: Monju Design Criteria / Procedures.....	40
Table 23: Monju Design Criteria / Procedures.....	41
Table 24: Monju Design Criteria / Procedures.....	42
Table 25: Monju Design Criteria / Procedures.....	43
Table 26: Monju Design Criteria / Procedures.....	44
Table 27: RCC-MR High Temperature.....	49
Table 28: RCC-MR Procedure Design Loads.....	50
Table 29: RCC-MR Procedure: Design Loads.....	51
Table 30: RCC-MR Failure Mechanisms.....	53
Table 31: RCC-MR Failure Mechanisms.....	55
Table 32: RCC-MR Design Criteria.....	57
Table 33: RCC-MR Design Criteria.....	58

Table 34: RCC-MR Design Criteria.....	60
Table 35: RCC-MR Design Criteria.....	61
Table 36: RCC-MR Design Criteria.....	63
Table 37: ASME NH High Temperature.....	69
Table 38: ASME NH Design Loads.....	70
Table 39: ASME NH Design Loads.....	71
Table 40: ASME NH Failure Mechanisms.....	72
Table 41: ASME NH Failure Mechanisms.....	73
Table 42: ASME NH Design Criteria / Procedures.....	74
Table 43: ASME NH Design Criteria / Procedures.....	75
Table 44: ASME NH Design Criteria / Procedures.....	76
Table 45: ASME NH Design Criteria / Procedures.....	77
Table 46: ASME NH Design Criteria / Procedures.....	78
Table 47: ASME NH Design Criteria / Procedures.....	79
Table 48: API579 High Temperature.....	85
Table 49: API579 Design Loads.....	86
Table 50: API579 Design Loads.....	87
Table 51: API579 Failure Mechanisms.....	88
Table 52: API579 Failure Mechanisms.....	88
Table 53: API579 Failure Mechanisms.....	90
Table 54: API579 Design Criteria / Procedures.....	91
Table 55: API579 Design Criteria / Procedures.....	92
Table 56: API579 Design Criteria / Procedures.....	93
Table 57: API579 Design Criteria / Procedures.....	94
Table 58: API579 Design Criteria / Procedures.....	95
Table 59: API579 Design Criteria / Procedures.....	96
Table 60: API579 Design Criteria / Procedures.....	97
Table 61: Efficiency index.....	134
Table 62: Efficiency index.....	134
Table 63: Summary of DBA Gross Plastic Distortion Limits (Primary Load Limits) [36].....	163
Table 64: Ratchet boundary problems investigated [58].....	180
Table 65: Summary of Round-Robin Benchmark Problems.....	201
Table 66: Round-Robin Benchmark Problem - C1 “Y-Junction Component and PBMR V-Ring”.....	204

Table 67: Round-Robin Benchmark Problem -C2 “The Harwell Thermal Ratcheting Experiment”.....	206
Table 68: Round-Robin Benchmark Problem - CP3 “Westinghouse-ORNL Full-Scale Nozzle Testing” .....	208
Table 69: Round-Robin Benchmark Problem - CP4 “Westinghouse Full-scale Elbow Testing” .....	210
Table 70: Round-Robin Benchmark Problem – P5 “Analysis of the Type IV Failures of Three Welded Ferritic Pressure Vessels” .....	213
Table 71: Round-Robin Benchmark Prob.C6 - “ORNL Creep Ratcheting Studies of Beams, Circ. Plates and Stppd Cylinders .....	216
Table 72: Round-Robin Benchmark Problem - CP7 ”Penny and Marriott - Creep of Aluminum Alloy Pressure Vessel Nozzle to Rupture”.....	218
Table 73: Round-Robin Benchmark Problem – CP8 “Goodall’s Experiments of Plain Plates, Plates with Notches and Cylinder/Cylinder Intersection” .....	220
Table 74: Round-Robin Benchmark Problem – CP9 “NIL_FFS Project.....	222
Table 75: Round-Robin Benchmark Problem –CP10 “Igaris’ Ratcheting Response of Pipes and Elbows under Cyclic Displacement Controlled Loads” .....	224
Table 76 Round-Robin Benchmark Problem – P11 “Corum-Battelle Experimental and analytical data on a typical nozzle for LMFBR/CFBRP-1HX” .....	226
Table 77: Round-Robin Benchmark Problem – P12 “E. L. Marriott – Welded spacer connecting adjacent legs of a serpentine boiler tube platen”.....	228
Table 78: Minimum material data requirement for primary load analysis, (deformation and/or rupture) .....	231
Table 79: Minimum material data requirement for cyclic load analysis .....	231

## LIST OF FIGURES

Figure 1: Timeline of ASME NH development .....	65
Figure 2: Post 1980 U.S. ETD R&D limited relative to that internationally.....	65
Figure 3: Dimensions (inches) of several simply notched structures[37] .....	165
Figure 4: Dimensions (in.) and x-section of sphere/nozzle and cylinder/nozzle intersection [37] .....	165
Figure 5: Beams, plate and flathead structures with uniformly distributed loads were investigated (dimensions in inches) [37] .....	166
Figure 6: Several illustrations of finite element models and meshes for notched bars and structures that were analyzed [37].....	166
Figure 7: Comparison of predicted creep lives at constant reference stress for notched specimens, pressure vessel components, beams and plates [37] .....	167
Figure 8: Alloy 617 main steam girth weld [46] .....	170
Figure 9: LDYM ratchet boundary verification for the Holed Plate under biaxial loading, zero mean [58].....	181
Figure 10: LDYM ratchet boundary verification - Holed Plate: biaxial loading. non-zero mean [58].....	181
Figure 11: LDYM verification with Holed Plate: constant pressure + nonlinear thermal gradient [58] .....	182
Figure 12: Effect of temperature on material properties .....	188

## FOREWORD

This document is the result of work resulting from Cooperative Agreement DE-FC07-05ID14712 between the U.S. Department of Energy (DOE) and ASME Standards Technology, LLC (ASME ST-LLC) for the Generation IV (Gen IV) Reactor Materials Project. The objective of the project is to provide technical information necessary to update and expand appropriate ASME materials, construction and design codes for application in future Gen IV nuclear reactor systems that operate at elevated temperatures. The scope of work is divided into specific areas that are tied to the Generation IV Reactors Integrated Materials Technology Program Plan. This report is the result of work performed under Task 9 titled “ Update and Improve Subsection NH – Simplified Elastic and Inelastic Design Analysis Methods.”

ASME ST-LLC has introduced the results of the project into the ASME volunteer standards committees developing new code rules for Generation IV nuclear reactors. The project deliverables are expected to become vital references for the committees and serve as important technical bases for new rules. These new rules will be developed under ASME’s voluntary consensus process, which requires balance of interest, openness, consensus and due process. Through the course of the project, ASME ST-LLC has involved key stakeholders from industry and government to help ensure that the technical direction of the research supports the anticipated codes and standards needs. This directed approach and early stakeholder involvement is expected to result in consensus building that will ultimately expedite the standards development process as well as commercialization of the technology.

ASME has been involved in nuclear codes and standards since 1956. The Society created Section III of the Boiler and Pressure Vessel Code, which addresses nuclear reactor technology, in 1963. ASME Standards promote safety, reliability and component interchangeability in mechanical systems.

Established in 1880, the American Society of Mechanical Engineers (ASME) is a professional not-for-profit organization with more than 127,000 members promoting the art, science and practice of mechanical and multidisciplinary engineering and allied sciences. ASME develops codes and standards that enhance public safety, and provides lifelong learning and technical exchange opportunities benefiting the engineering and technology community. Visit [www.asme.org](http://www.asme.org) for more information.

The ASME Standards Technology, LLC (ASME ST-LLC) is a not-for-profit Limited Liability Company, with ASME as the sole member, formed in 2004 to carry out work related to newly commercialized technology. The ASME ST-LLC mission includes meeting the needs of industry and government by providing new standards-related products and services, which advance the application of emerging and newly commercialized science and technology and providing the research and technology development needed to establish and maintain the technical relevance of codes and standards. Visit [www.stllc.asme.org](http://www.stllc.asme.org) for more information.

## **ABSTRACT**

This report is the result of work performed under Task 9 titled “ Update and Improve Subsection NH – Simplified Elastic and Inelastic Design Analysis Methods.” ASME ST-LLC has introduced the results of the project into the ASME volunteer standards committees developing new code rules for Generation IV nuclear reactors. The project deliverables are expected to become vital references for the committees and serve as important technical bases for new rules. These new rules will be developed under ASME’s voluntary consensus process, which requires balance of interest, openness, consensus and due process. Through the course of the project, ASME ST-LLC has involved key stakeholders from industry and government to help ensure that the technical direction of the research supports the anticipated codes and standards needs. This directed approach and early stakeholder involvement is expected to result in consensus building that will ultimately expedite the standards development process as well as commercialization of the technology.

## **1 SUBTASK 9.1 – OUTLINE OF AN “IDEAL” HIGH TEMPERATURE CODE**

The objective of this subtask is to develop a template for the “Ideal” high temperature design Code, in which individual topics can be identified and worked on separately in order to provide the detail necessary to comprise a comprehensive Code.

Like all ideals, this one may not be attainable as a practical matter. The purpose is to set a goal for what is believed the “Ideal” design Code should address, recognizing that some elements are not mutually exclusive and that the same objectives can be achieved in different way. Most, if not all existing Codes may therefore be found to be lacking in some respects, but this does not mean necessarily that they are not comprehensive.

While this subtask does attempt to list the elements which individually or in combination are considered essential in such a Code, the authors do not presume to recommend how these elements should be implemented or even, that they should all be implemented at all.

The scope of this subtask is limited to compiling the list of elements thought to be necessary or at minimum, useful in such an ‘Ideal’ Code; suggestions are provided as to their relationship to one another. Except for brief descriptions, where these are needed for clarification, neither this subtask, nor the report as a whole, attempts to address details of the contents of all these elements. Some, namely primary load limits (elastic, limit load, reference stress), and ratcheting (elastic, e-p, reference stress) are dealt with specifically in other subtasks of this report. All others are merely listed; the expectation is that they will either be the focus of attention of other active DOE-ASME GenIV Materials Tasks, e.g., creep-fatigue, or to be considered in future DOE-ASME GenIV Materials Tasks.

Since the focus of this report is specifically approximate methods, the authors have deemed it necessary to include some discussion on what is meant by “approximate.” However, the topic will be addressed in one or more later subtasks.

### **1.1 Definition of “High Temperature”**

“High temperature” is taken to refer here to the operating range of temperature within which time dependent, thermally activated deformation and damage processes, even under nominally steady loads below yield, become a significant factor in the behavior of load bearing components.

This definition is commonly taken to mean the appearance of creep as a significant mechanism, but others, such as thermal ageing and oxidation/corrosion are also important.

In practice, time dependency is a smooth function of temperature. Consequently, there is no clear context free boundary separating time-independent from time-dependent behavior. For specific forms of service conditions and material response, it is possible to define a temperature limit below which “high temperature” may be considered negligible in that the time dependent phenomena associated with high temperature behavior do not have a significant effect on design decisions. For the purpose of defining the applicability of a high temperature design Code, the threshold temperature marking the point above which time dependency first reaches significance is one valid criterion defining “high temperature” design.

The threshold temperature is not unique. It is strictly a function of the mode of failure being considered, as well as the design lifetime. For instance, the threshold temperature for constant loading conditions, where stresses are expected to relax to a relatively low steady state, will be higher than one based on cyclic conditions which cause stresses to be repeatedly reset to the yield stress by cyclic plastic deformation. The specified design lifetime will also influence the