

INVESTIGATION OF TEMPERATURE DERATING FACTORS FOR HIGH-STRENGTH LINE PIPE



Currently in preview, click buy full version

STP-PT-049

INVESTIGATION OF TEMPERATURE DERATING FACTORS FOR HIGH-STRENGTH LINE PIPE

Prepared by:

Donovan A. Picone and M. J. Rosenfeld, PE
Picone and Associates, Inc.

ASME STANDARDS
TECHNOLOGY, LLC

Date of Issuance: September 28, 2012

This report was prepared as an account of work sponsored by ASME Pressure Technologies Codes and Standards and the ASME Standards Technology, LLC (ASME ST-LLC).

Neither ASME, ASME ST-LLC, the authors, nor others involved in the preparation or review of this report, nor any of their respective employees, members or persons acting on their behalf, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe upon privately owned rights.

Reference herein to any specific commercial product, process or service by trade name, trademark, manufacturer or otherwise does not necessarily constitute or imply its endorsement, recommendation or favoring by ASME ST-LLC or others involved in the preparation or review of this report, or any agency thereof. The views and opinions of the authors, contributors and reviewers of the report expressed herein do not necessarily reflect those of ASME ST-LLC or others involved in the preparation or review of this report or any agency thereof.

ASME ST-LLC does not take any position with respect to the validity of any patent rights asserted in connection with any items mentioned in this document, and does not undertake to insure anyone utilizing a publication against liability for infringement of any applicable Letters Patent, nor assumes any such liability. Users of a publication are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, is entirely their own responsibility.

Participation by federal agency representative(s) or person(s) affiliated with industry is not to be interpreted as government or industry endorsement of this publication.

ASME is the registered trademark of the American Society of Mechanical Engineers.

No part of this document may be reproduced in any form, in an electronic retrieval system or otherwise, without the prior written permission of the publisher.

ASME Standards Technology, LLC
Three Park Avenue, New York, NY 10016-5990

ISBN No. 978-0-7918-3426-8

Copyright © 2012 by
ASME Standards Technology, LLC
All Rights Reserved

TABLE OF CONTENTS

Foreword	v
Executive Summary	vi
1 BACKGROUND, APPROACH, AND FINDINGS	1
1.1 Introduction	1
1.2 Background	2
1.3 Technical Approach	3
1.4 Findings	3
2 A REVIEW OF THE AVAILABLE DATA	5
2.1 Introduction	5
2.2 Study by Benfell, Morris and Barsanti	5
2.3 Study by Bredenbruch, Gehrman, Schmidt, and Träger	8
2.4 Study by Gray	12
2.5 Other pipeline design standards	14
2.5.1 CSA Z662	14
2.5.2 AS 2885	15
2.5.3 ISO 13623	15
2.5.4 DNV-OS-F101	15
3 AN OVERVIEW OF THE STRENGTHENING MECHANISMS AND ROLLING PROCESSES OF HSLA STEELS FOR MODERN LINE PIPE	17
3.1 Introduction	17
3.2 Strengthening Mechanisms	17
3.3 Rolling Processes	17
4 AN ASSESSMENT OF THE AVAILABLE DATA	19
4.1 Introduction	19
4.2 Variables Related to Pipe Manufacturing	19
4.3 Variables Related to the Tensile Test Procedure	23
5 IMPLICATIONS OF THE AVAILABLE DATA FOR ASME CODES	25
5.1 Other ASME Codes affected	25
5.2 Possible B31.8 Code Committee Response	26
6 RECOMMENDATIONS FOR ADDITIONAL TENSILE TESTING	28
Reference	30
Acknowledgements	31
Abbreviations, Acronyms and Variables	32

LIST OF TABLES

Table 1—Effect of Elevated Temperature on the Microstructure in X60 Line Pipe	8
Table 2—Plate Rolling Processes and Microstructures in X52-X120 Line Pipe	20
Table 3—Pipe Forming and Seam Welding Methods for X52-X120 Line Pipe	20

Table 4—Alloying Approaches and Microstructures in X52-X120 Line Pipe.....	21
Table 5—Variables Related to Pipe Manufacturing in Each Study.....	22
Table 6—Variables Related to the Tensile Test Procedures in Each Study	24
Table 7—Pipe Manufacturing Variables to Include in a Future Test Program	28
Table 8—Tensile Test Procedures for a Future Test Program.....	28

LIST OF FIGURES

Figure 1—Transverse Yield Strength in X52-X70 Line Pipe as a Function of Temperature.....	1
Figure 2—Longitudinal Yield Strength in X60-X70 Line Pipe Steel.....	6
Figure 3—Derating Factors for Transverse Yield Strength in X52-X70 Line Pipe Steel	7
Figure 4—Derating Factors for Longitudinal Yield Strength of X60-X70 Line Pipe Steels.....	7
Figure 5—Longitudinal Yield Strength of X70 Line Pipe.....	9
Figure 6—Longitudinal Yield Strength of X60 Line Pipe.....	9
Figure 7—Longitudinal Yield Strength of X65 Line Pipe.....	10
Figure 8—Derating Factors for Longitudinal Yield Strength of X70 Line Pipe	11
Figure 9—Derating Factors for Longitudinal Yield Strength of X60 Line Pipe	11
Figure 10—Derating Factors for Longitudinal Yield Strength of X65 Line Pipe	12
Figure 11—Yield Strength of ASTM A841, Grade F Plate Steel.....	13
Figure 12—Derating factors of ASTM A841, Grade F Plate steel.....	14

FOREWORD

This report reviews the ASME derating factors, identifies the range of line pipe steel grades that may be affected and the potential impacts to ASME pipeline and piping design standards, and makes recommendations for further study or experimental investigation as necessary.

Established in 1880, the American Society of Mechanical Engineers (ASME) is a professional not-for-profit organization with more than 127,000 members promoting the art, science and practice of mechanical and multidisciplinary engineering and allied sciences. ASME develops codes and standards that enhance public safety, and provides lifelong learning and technical exchange opportunities benefiting the engineering and technology community. Visit www.asme.org for more information.

The ASME Standards Technology, LLC (ASME ST-LLC) is a not-for-profit Limited Liability Company, with ASME as the sole member, formed in 2004 to carry out work related to newly commercialized technology. The ASME ST-LLC mission includes meeting the needs of industry and government by providing new standards-related products and services, which advance the application of emerging and newly commercialized science and technology and providing the research and technology development needed to establish and maintain the technical relevance of codes and standards. Visit www.stllc.asme.org for more information.

EXECUTIVE SUMMARY

The current ASME B31.8 code gives no derating of line pipe steels for temperatures below 250°F. For pipeline steels in the Grade X60-X70 range, data show that a reduction of the yield strength may be exhibited at temperatures below 250°F in some cases. Some pipeline design standards developed for other countries (e.g., Norway, Netherlands, and Australia) already apply derating factors at temperatures well below 250°F. Thus, the ASME derating factors appeared to be in need of review.

This report reviews the available information, identifies the range of line pipe steel grades that may be affected, identifies the potential impacts to ASME pipeline and piping design standards, and makes recommendations for further study or experimental investigation as necessary.

A review of data suggests that (a) there is a high likelihood of some decrease in the actual yield strength of high-strength low-alloy grades of line pipe in current usage at temperatures between 70°F and 250°F; (b) against a limited set of data the current Code derating factors appear to be adequate, provided room temperature yield strength is at least 5% above specified minimum levels; (c) there are insufficient data to recommend a change in the Code at this time; (d) there are insufficient data to determine whether the present Code derating factor is adequate for all variables of alloy, design and steel processing used with current grades of high strength pipe; and (e) further investigation by testing a broader sample base is needed to adequately address these issues.