

Australian/New Zealand Standard

Methods of test for pulp and paper

Part 206s: Freeness of pulp



## **AS/NZS 1301.206s:2015**

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee PK-019, Methods of Test for Pulp and Pulp. It was approved on behalf of the Council of Standards Australia on 30 March 2015 and on behalf of the Council of Standards New Zealand on 27 March 2015.

This Standard was published on 29 April 2015.

---

The following are represented on Committee PK-019:

Appita  
Australian Forest Products Association  
Australian Institute of Packaging  
New Zealand Paper Forum  
Scion

---

### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at [www.saiglobal.com.au](http://www.saiglobal.com.au) or Standards New Zealand web site at [www.standards.co.nz](http://www.standards.co.nz) and looking up the relevant Standard in the on-line catalogue.

For more frequent listings or notification of revisions, amendments and withdrawal, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of either Standards Australia or Standards New Zealand at the address shown on the back cover.

---

*This Standard was issued in draft form for comment as DR AS/NZS 1301.206s:2014.*

---

# Australian/New Zealand Standard™

## Methods of test for pulp and paper

### Part 206s: Freeness of pulp

Originated in Australia as AS P1.P206m—1961.  
Originated in New Zealand as NZS P1.P206m:1961.  
Previous edition AS/NZS 1301.206s:2002.  
Second edition 2015.

#### **COPYRIGHT**

© Standards Australia Limited/Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Australia) or the Copyright Act 1994 (New Zealand).

Jointly published by SAI Global Limited under licence from Standards Australia Limited, GPO Box 476, Sydney, NSW 2001 and by Standards New Zealand, Private Bag 2439, Wellington 6140.

## PREFACE

This Standard was prepared by Joint Standards Australia/Standards New Zealand Committee PK-019, Methods of Test for Pulp and Paper, to supersede AS/NZS 1301.206s:2002.

This Standard prescribes one procedure for determining the drainage properties of pulp stock.

This revision has been made to align the Standard more closely with ISO 5267-2:2001, *Pulps—Determination of drainability—Part 2: ‘Canadian Standard’ freeness method*. In particular, in the procedure, the extent of disintegration of the sample prior to measurement of freeness has been substantially reduced from the former 75 000 revolutions. Further, because several different designs of test equipment have been in common use, this revision permits either of two designs to be used, but requires that the test report specify which design was utilized for the test.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the appendix to which they apply. A ‘normative’ appendix is an integral part of a Standard, whereas an ‘informative’ appendix is only for information and guidance.

## CONTENTS

	<i>Page</i>
FOREWORD.....	4
1 SCOPE.....	5
2 NORMATIVE REFERENCES .....	5
3 PRINCIPLE .....	5
4 APPARATUS .....	5
5 PREPARATION OF TEST SAMPLE.....	6
6 PROCEDURE.....	7
7 REPORT .....	8
APPENDICES	
A 'CANADIAN STANDARD' FREENESS TEST EQUIPMENT.....	11
B ALTERNATIVE DESIGN OF FREENESS TEST EQUIPMENT.....	17
C CALIBRATION OF FREENESS INSTRUMENTS .....	21
D CARE OF FREENESS INSTRUMENTS .....	22
E BIBLIOGRAPHY.....	24

## FOREWORD

This Standard prescribes the procedure to be used in measuring the freeness of pulp, which is an arbitrary measure of the drainage properties of pulp stock.

The freeness test described in this Standard is designed to provide a measure of the rate at which a dilute suspension of pulp is dewatered under specified conditions. It has been shown that the drainability is related to the surface conditions and swelling of the fibres, and constitutes a useful index of the amount of mechanical treatment to which the pulp has been subjected.

In principle, this method is applicable to all kinds of pulp in aqueous suspension.

The design of the instrument is such that the result is strongly influenced by the drainage rate in the initial stages of drainage. The result of the freeness test depends mainly on the quantity of fines and debris present<sup>[1]</sup> and on the degree of fibrillation of fibres, their flexibility and their fineness.

The test was originally designed to yield information for the control of the manufacture of groundwood pulp, but it is also used in studies of the behaviour of various pulps during beating, and in the control of beaters and refiners. Freeness measurements do not necessarily correlate with drainage behaviour on the wire of a paper machine.

In this method stainless steel is listed as a preferred material of construction for some components of the freeness tester. Certain stocks will corrode bronze, and corrosion effects on screen plates, orifice pieces and side tubes change the performance of the instrument. In addition, some stocks readily give rise to deposits at these places, and it is convenient to be able to clean the parts by drastic chemical methods such as are permissible with a corrosion resistant material.

This Standard is similar to, but not identical with, ISO 5267-2:2001, *Pulps—Determination of drainability—Part 2: 'Canadian Standard' freeness method*. A similar method is TAPPI T221cm-09, *Drainage Time of Pulp*.

Freeness is different from drainage time which is covered by TAPPI method T221cm-09om-93. Another method for measuring drainability is the Schopper-Riegler method. Schopper-Riegler freeness is different from Canadian Standard Freeness. There is no AS/NZS Standard for the Schopper-Riegler method. However, it is described in ISO 5267-1:1999, *Pulps—Determination of drainability, Part 1: Schopper-Riegler method*.

## STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

---

**Australian/New Zealand Standard**  
**Methods of test for pulp and paper**

---

---

**Part 206s: Freeness of pulp**

---

**1 SCOPE**

This Standard specifies the procedure to be used in measuring the freeness of pulp.

**2 REFERENCED DOCUMENTS**

The following documents are referred to in this Standard.

NOTE: Bibliographic references are indicated in the text by superscript reference numbers (e.g. <sup>[1]</sup>) and the documents are listed in Appendix E.

## AS/NZS

- 1301 Methods of test for pulp and paper  
1301.207s Part 207s: Determination of stock concentration  
1301.214s Part 214s: Equipment for preparation of handsheets

## ISO

- 5267 Pulps—Determination of drainability  
5267-2 Part 2: 'Canadian Standard' freeness method

**3 PRINCIPLE**

A specified volume of stock drains from a cylindrical chamber into a cone with two orifices, one at the side and one at the bottom. The volume of water which passes through the side orifice is measured. This volume, measured in millimetres, and corrected if the temperature and concentration of the stock is different from that specified, is the freeness.

**4 APPARATUS****4.1 Freeness tester**

Consisting of a drainage chamber (cylinder) and a rate measuring funnel mounted on a vibration free support so that their axes of symmetry are vertical and coincide, and the top of the funnel is 18 ± 5 mm below the bottom of the screen plate attached to the cylinder. Except where stated otherwise, the components of the tester may be fabricated from stainless steel or phosphor bronze or from metal wholly plated with nickel or hard chrome. The drainage chamber consists of a cylinder closed at the top with a rigid lid capable of providing an air-tight closure. The inside surface of the lid is fitted with a thick rubber gasketing. An air-cock is provided in the centre of the lid as a means of admitting air to the cylinder. The bottom of the cylinder is fitted with a perforated screen plate, preferably fabricated from stainless steel, but brass may be used. Stainless steel shall conform in composition to AISI Type No 316 or similar. The screen plate is held in place by the flange of a ring which is screwed on to the bottom of the cylinder. The bottom of the cylinder is closed with a rigid bottom lid, which is covered with a thick soft rubber gasket which fits against the flange holding the screen plate in position.